

PRODUCT DATA SHEET

Sika® Plastiment® PZ 392

(formerly MPozzolith 392)

HIGH PERFORMANCE RETARDING PLASTICISER FOR CONCRETE

DESCRIPTION

Sika® Plastiment® PZ 392 is a high-performance plasticising retarder, beneficial in maintaining workability especially in high ambient temperatures. Suitable for use in hot and tropical climatic conditions.

USES

- Ready mixed concrete where high workability retention and retardation are highly required.
- Hot weather concreting of all types.
- Reduction in permeability, reducing effect of ground-water salts on concrete and steel.
- To improve cohesion, workability and compact ability in concretes using poorly graded/shaped fine aggregates.

FEATURES

- Reduces placing problems in hot weather by improved workability and workability retention in conjunction with extended setting times.
- Improves surface finish.
- Improves trowellability.
- Reduces honeycombing / cold joint effects.
- Considerably improves the cohesion of concrete, reducing segregation and bleed water.
- Improves pumpability of concrete.
- Reduces effects of various modes of attack on concrete and embedded steel by considerable reduction in permeability.

CERTIFICATES AND TEST REPORTS

Sika® Plastiment® PZ 392 follows the requirements of ASTM C494; Types B and D and BS EN 934-2

PRODUCT INFORMATION

Composition	Modified organic compounds
Packaging	210 L drums, 1000 L flowbin or bulk supply in tanker
Appearance and colour	Dark brown liquid
Shelf life	12 months from date of production if stored properly
Storage conditions	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5°C and +45°C. Mix well before use.
Density	~1.07 kg/l (+25°C)
pH-Value	5 – 8
Total chloride ion content	Nil (BS EN 934-2)

TECHNICAL INFORMATION

Concreting guidance

The standard rules of good concreting practice for production and placing must be observed when using Sika® Plastiment® PZ 392 in concrete. Refer to relevant standards. Fresh concrete must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Use Sika® Antisol® products as a curing agent or apply wet hessian.

APPLICATION INFORMATION

Recommended dosage

Trials should be conducted to determine the optimum addition rates of Sika® Plastiment® PZ 392, depending on mix design proposed and mix performance requirements. As a general guide, a dosage range of 200 ml to 600 ml per 100 kg of total binder is recommended as a starting point. Depending on the desired properties, a dosage of up to 800 ml per 100 kg of total binder shall be used.

Compatibility

Sika® Plastiment® PZ 392 is suitable for mixes containing all types of cement and supplementary cementitious materials such as: Microsilica (Silica Fume), Fly Ash (PFA), GGBS (Ground Granulated Blast Furnace Slag) and the following Sika products:

- Sikament®
- SikaPump®
- Sika® FerroGard®
- SikaFume®
- SikaFiber®
- Sika® Aer
- Sika® Stabilizer
- SikaControl®

We recommend to perform trial mixes to establish the required performance when combining Sika® Plastiment® PZ 392 with the above products or other admixtures. Please consult our Sika Technical Department for further assistance.

Dispensing

Sika® Plastiment® PZ 392 is added to the gauging water or simultaneously poured with it into the concrete mixer at the batching plant. Do not add Sika® Plastiment® PZ 392 directly to the dry mix. The addition of the remaining gauging water (to fine tune concrete consistency) may only be started after two-thirds of the wet mixing time to avoid surplus water in the concrete.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Sika® Plastiment® PZ 392 should not be pre-mixed with other admixtures. If other admixtures are to be used in concrete containing Sika® Plastiment® PZ 392, they must be dispensed separately.
- **Sika® Plastiment® PZ 392 is not compatible with admixtures containing polycarboxylic ether polymer such as those from the Sika® ViscoCrete® and SikaPlast® product ranges.**
- When using Sika® Plastiment® PZ 392 a suitable concrete mix must be designed for the local material sources and trial mixes performed to verify suitability.

- With high workability mixes take special care that all formwork is properly installed and secured.
- When accidental overdosing occurs the set retarding effect and workability increases. Additional air may also be entrained. During this period the concrete must be kept moist in order to prevent premature drying out. If properly cured, the ultimate strength of the concrete will not be adversely affected.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188

Email: info@bh.sika.com

Sika Kuwait Cons. Mat. & Paints Co WLL

Tel: +965 22 282 296

Email: sika.kuwait@kw.sika.com

Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC

Sika International Chemicals LLC

Tel: +971 4 439 8200

Email: info@ae.sika.com

Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for

Manufacturing LLC

Riyadh / Jeddah / Dammam / Rabigh

Tel: +966 9200 22167

Email: info@sa.sika.com

Web: gcc.sika.com

Sika LLC - Oman

Sika MB LLC

Tel. +968 22 826 500

Email: info@om.sika.com

Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
Sika MB LLC
Sika International Chemicals LLC
Sika Gulf B.S.C. (c)
ISO 9001, 14001 – SGS
Sika Saudi Arabia Limited
ISO 9001, 14001 – TÜV
Sika MB Construction Chemicals LLC
Sika Construction Chemicals for Manufacturing LLC
ISO 9001 – LMS
Sika MB LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



SikaPlastimentPZ392-en-AE-(01-2025)-1-1.pdf

Product Data Sheet

Sika® Plastiment® PZ 392

January 2025, Version 01.01

02130300000002133