

PRODUCT DATA SHEET

SikaMur[®]-100 Blockfix BH

CEMENT BASED PREMIXED BLOCK ADHESIVE

DESCRIPTION

SikaMur[®]-100 Blockfix BH is a cementitious, pre-bagged, one component mortar that requires only addition of water at site. Contains cement, graded sand and additives to improve workability, adhesion and water retention.
Suitable for use in hot and tropical climatic conditions.

USES

As masonry mortar for regular / hollow / autoclaved aerated concrete (AAC) blocks and bricks.

FEATURES

- Good adhesion to various type of blocks
- Good water retention
- Extended open time
- Excellent workability

PRODUCT INFORMATION

Composition	Portland cement and selected graded aggregates.
Packaging	25 kg and 40 kg bag
Appearance and colour	White powder (25 kg bag) Grey powder (40 kg bag)
Shelf life	12 months from production date
Storage conditions	Store in a dry area in original packaging and at temperatures between 5 °C to 35 °C. Protect from direct sunlight, heat and moisture.
Maximum grain size	~0.8 mm

TECHNICAL INFORMATION

Compressive strength	w/p = 0.15	≥ 10 N/mm ² (28 d)	(ASTM C 109)
Tensile adhesion strength	w/p = 0.15	≥ 0.5 N/mm ² (28 d)	(ASTM D 4541)

APPLICATION INFORMATION

Fresh mortar density	~1.6 kg/l (+23 °C)
Yield	~18.0 - 18.2 L (fresh mortar) per 25 kg bag ~28.8 - 29.0 L (fresh mortar) per 40 kg bag

Layer thickness	Min. 3 mm Max. 10 mm
Ambient air temperature	+5 °C min. / +40 °C max.
Mixing ratio	3.75 - 4.1 L water per 25 kg bag 6.0 - 6.5 L water per 40 kg bag
Substrate temperature	+5 °C min. / +40 °C max.
Pot Life	~4.5 h (+23 °C)

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Not suitable as tile adhesive / grout

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Blocks and bricks surface should be clean, sound and free from oil, grease, cement laitance and all loosely adhering particles. Absorbent surfaces should be saturated thoroughly with clean water.

MIXING

Add water according to the desired consistency into a clean mixing vessel before slowly adding the SikaMur®-100 Blockfix BH powder. SikaMur®-100 Blockfix BH is best mixed in a forced action mixer, for 2 to 3 minutes or until the mix is free of lumps. Slow speed drill (maximum 500 rpm) can be also used for mixing. Normal tumble type concrete mixers are not suitable. Do not add extra water or other ingredients. Mix only full bags for best results. Note: In hot weather application, use chilled water to extend the open time of the mixed materials.

APPLICATION

Apply the SikaMur®-100 Blockfix BH by trowel. Place the block on mortar ensuring good contact. Check the level and continue with next block. Tool mortar joints when the surface is thumb print hard. Protect newly applied mortar from sun and wind. After setting of SikaMur®-100 Blockfix BH, curing with water will help to gain better strength.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC
Sika International Chemicals LLC
Tel: +971 4 439 8200
Email: info@ae.sika.com
Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC
Riyadh / Jeddah / Dammam / Rabigh
Tel: +966 12 692 7079
Email: info@sa.sika.com
Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC
(part of Sika)
Tel: +968 22 826 500
Email: info@om.sika.com
Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
-Sika UAE LLC
-Sika International Chemicals LLC
-Sika Gulf B.S.C. (c)
ISO 9001, 14001 – SGS
-Sika Saudi Arabia Limited
ISO 9001, 14001 – TÜV
-Sika MB Construction Chemicals LLC
-Sika Construction Chemicals for Manufacturing LLC
-Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

SikaMur®-100 Blockfix BH
October 2024, Version 02.01
021850101000000023

