

PRODUCT DATA SHEET

SikaWall®-1030 Alpha Dry Base Coat

(formerly Senergy® Alpha Dry Base Coat)

DRY-MIX POLYMER BASE COAT



DESCRIPTION

SikaWall®-1030 Alpha Dry Base Coat is a dry-mix polymer base coat containing portland cement and requiring only water for mixing. Part of SikaWall® / Sikatherm® Exterior Insulation and Finish System (EIFS).

Suitable for use in hot and tropical climatic conditions.

USES

- For use with the SikaWall® / Sikatherm® Exterior Insulation and Finish System (EIFS) to be applied as a base coat over insulation board.
- For use with wall systems to embed SikaWall® Corner Beads and SikaWall® Flexguard Reinforcing Mesh range.
- To apply insulation plugs over fastener heads, when required.

FEATURES

- Easy to use, just add water to mix
- Reduces the chance for efflorescence
- Trowels easily
- Easy application, increases job-site productivity
- Fast mesh embedment
- Easy installation of corner beads
- Safe for use, non-toxic
- Easy to clean

CERTIFICATES AND TEST REPORTS

- Passed as a component of system testing in accordance with **NFPA 268** and **NFPA 285**
- Individual product testing in accordance with **ASTM E84**, Classification: Class A

PRODUCT INFORMATION

Composition	Portland cement with special fillers, sand, polymers and additives
Packaging	25 kg bag
Appearance and colour	Grey powder
Shelf life	12 months from date of production
Storage conditions	Store in original unopened packaging in a cool and dry condition between +5 °C and +30 °C. Protect from direct sunlight, heat and moisture.
Density	~1.7 kg/l (mixed, at +25 °C)

TECHNICAL INFORMATION

Tensile adhesion strength	≥ 0.5 N/mm ²	(EN 1542)
---------------------------	-------------------------	-----------

APPLICATION INFORMATION

Mixing ratio	5.6 L per 25 kg bag	
Consumption	Approximate coverage rates of base coat:	
	Type of insulation board	Coverage per 25 kg bag for mesh embedment (1 st coat)
	Expanded Polystyrene (EPS)	▪ ~13 m ² with embedded SikaWall-9004 Flexguard Mesh
	Mineral wool (Rockwool)	▪ ~8 m ² with embedded SikaWall-9012 Intermediate Mesh + SikaWall-9004 Flexguard Mesh (double mesh system)
		▪ ~11.5 m ² with embedded SikaWall-9004 Flexguard Mesh + SikaWall-9012 Intermediate Mesh + SikaWall-9004 Flexguard Mesh (double mesh system)
Type of insulation board	Coverage per 25 kg bag for final layer (2 nd coat)	
Expanded Polystyrene (EPS) and Mineral wool (Rockwool)	▪ ~24 m ²	
Note: Flat trowel application. Application rates will depend on the quality of application, substrate board flatness, texture and density. These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level, wastage or any other variations. Apply product to a test area to calculate the exact consumption for the specific substrate conditions and proposed application equipment.		
Yield	~18 L / 25 kg bag	
Layer thickness	Non-reinforced	Max. 2 mm per layer
	Single mesh reinforced	Max. 3 mm per layer
	Double mesh reinforced	Max. 5 mm per layer
Ambient air temperature	+5 °C min. / +40 °C max.	
Substrate temperature	+5 °C min. / +40 °C max.	
Pot Life	+25 °C	~8 hours
	+35 °C	~5 hours

SYSTEM INFORMATION

System structure	<table> <tr> <td>Air / Vapour barrier (optional)</td><td>Sikagard® AWB 661 range</td></tr> <tr> <td>Insulation adhesive</td><td>SikaWall®-1010 Alpha Dry Adhesive</td></tr> <tr> <td>Insulation board</td><td>EPS / Mineral wool / Sikatherm® range</td></tr> <tr> <td>Mechanical Fasteners</td><td>Sikatherm®-900 insulation fasteners range</td></tr> <tr> <td>Corner Beads</td><td>SikaWall®-9000 corner bead range</td></tr> <tr> <td>Base Coat</td><td>SikaWall®-1030 Alpha Dry Base Coat</td></tr> <tr> <td>Reinforcing Mesh</td><td>SikaWall®-9000 Flexguard Mesh range</td></tr> <tr> <td>Primer</td><td>SikaWall®-15 Tinted Primer AE</td></tr> <tr> <td>Textured Finish</td><td>SikaWall®-6000 finish range</td></tr> </table>	Air / Vapour barrier (optional)	Sikagard® AWB 661 range	Insulation adhesive	SikaWall®-1010 Alpha Dry Adhesive	Insulation board	EPS / Mineral wool / Sikatherm® range	Mechanical Fasteners	Sikatherm®-900 insulation fasteners range	Corner Beads	SikaWall®-9000 corner bead range	Base Coat	SikaWall®-1030 Alpha Dry Base Coat	Reinforcing Mesh	SikaWall®-9000 Flexguard Mesh range	Primer	SikaWall®-15 Tinted Primer AE	Textured Finish	SikaWall®-6000 finish range
Air / Vapour barrier (optional)	Sikagard® AWB 661 range																		
Insulation adhesive	SikaWall®-1010 Alpha Dry Adhesive																		
Insulation board	EPS / Mineral wool / Sikatherm® range																		
Mechanical Fasteners	Sikatherm®-900 insulation fasteners range																		
Corner Beads	SikaWall®-9000 corner bead range																		
Base Coat	SikaWall®-1030 Alpha Dry Base Coat																		
Reinforcing Mesh	SikaWall®-9000 Flexguard Mesh range																		
Primer	SikaWall®-15 Tinted Primer AE																		
Textured Finish	SikaWall®-6000 finish range																		

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTATION

General Method Statement: **SikaWall® / Sikatherm® External Insulation and Finish System (EIFS)**

IMPORTANT CONSIDERATIONS

- Do not apply in ambient temperatures below 4 °C. Provide supplementary heat during installation and drying period at least 24 hours after installation and until dry when temperatures less than 4 °C prevail.
- Do not apply to frozen surfaces.
- Avoid application in direct sunlight and/or strong wind / draughts.
- If the substrate surface is having major undulations, consumption of base coat can be increased significantly. Respect advised max. layer thickness.
- In high temperature application, use the chilled water for mixing, to keep the material temperature below +30 °C.
- Never add water or dry powder to reconstitute a SikaWall®-1030 Alpha Dry Base Coat mix which has already begun to set.
- Make a test area (mock-up) prior to carrying out any work.
- Consult the Sika Technical Services Department for specific recommendations concerning other potentially challenging applications.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

MIXING

- Place contents of each bag in a suitable container which is clean and free of foreign substances.
- Do not use a container which has contained or been cleaned with a petroleum-based product.
- Fill the container with advised amount of clean, potable water.
- Add SikaWall®-1030 Alpha Dry Base Coat in small increments, mixing after each addition.
- Mix the contents of the SikaWall®-1030 Alpha Dry Base Coat unit with a low-speed drill and paddle mixer until thoroughly blended.
- Additional SikaWall®-1030 Alpha Dry Base Coat or small amount of water may be added to adjust workability.
- Let it stand for 5 minutes, then remix and retemper before use.
- Additives are not permitted.
- Close container when not in use.

APPLICATION

Apply the base coat in 2 layers. First (1st) layer of SikaWall®-1030 Alpha Dry Base Coat shall be applied so as to achieve SikaWall® Reinforcing Mesh embedment with no SikaWall® Reinforcing Mesh colour visible. Allow for initial set (touch dry). Lightly abrade dried first layer with sandpaper, without damaging the mesh. Remove the dust and apply second (2nd) layer of SikaWall®-1030 Alpha Dry Base Coat. Allow to dry approx. 8 to 10 hours, depending on the ambient temperature, before the application of SikaWall®-15 Tinted Primer AE and SikaWall®-6000 range of finish coats.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water and soap immediately after use. Hardened / cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

Sika UAE LLC

Sika UAE LLC (Branch)
Sika International Chemicals LLC
Tel: +971 4 439 8200
Email: info@ae.sika.com
Web: gcc.sika.com

Sika Saudi Arabia Limited

Riyadh / Jeddah / Dammam / Rabigh
Tel: +966 9200 22167
Email: info@sa.sika.com
Web: gcc.sika.com

Sika MB LLC

Oman
Tel: +968 22 826 500
Email: info@om.sika.com
Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS:
- Sika UAE LLC
- Sika International Chemicals LLC
- Sika Gulf B.S.C. (c)
ISO 9001, 14001 – SGS:
- Sika Saudi Arabia Limited
ISO 9001, 14001 – TÜV:
- Sika UAE LLC (Branch)
ISO 9001 – SGS:
- Sika MB LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

SikaWall®-1030 Alpha Dry Base Coat

April 2026, Version 03.02

021830101000242409