

PRODUCT DATA SHEET

Sika® Reactivation Primer

ONE-COMPONENT PRIMER FOR THE REACTIVATION OF EXISTING SIKAROOF® MTC AND SIKALASTIC® WATERPROOFING SYSTEMS

DESCRIPTION

Sika® Reactivation Primer is an one-component polyurethane based primer for the reactivation of SikaRoof® MTC, Sikalastic® roofing systems and Sika-floor® balcony waterproofing systems. Suitable for use in hot and tropical climatic conditions.

USES

Primer for use when recoating existing:

- SikaRoof® MTC
- Sikalastic® roofing systems
- Sikafloor® balcony waterproofing systems.

CHARACTERISTICS / ADVANTAGES

- One-component - easy and ready to use
- Enhances adhesion to existing Sikalastic® and Sika-floor® systems
- Allows further coats to be safely applied when the standard re-coating window has been exceeded
- Suitable for use over a wide range of existing polyurethane roofing membranes (subject to satisfactory adhesion testing)

PRODUCT INFORMATION

Composition	Solvent borne polyurethane
Packaging	5 L (~5.15 kg) metal container
Appearance / Colour	Low viscosity liquid, clear
Shelf life	12 months from date of production
Storage conditions	The product must be stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between 0 °C and +25 °C. Higher storage temperatures may reduce shelf life of product. Reference shall also be made to the storage recommendations within the safety data sheet.
Density	~1.03 kg/l (23 °C) (EN ISO 2811-1)

APPLICATION INFORMATION

Consumption	~0.10 kg/m ² (Apply in 1 coat)	
Ambient Air Temperature	+5 °C min. / +30 °C max.	
Relative Air Humidity	85 % r.h. max.	
Dew Point	Beware of condensation. The substrate and uncured coating must be ≥ 3 °C above dew point.	
Substrate Temperature	+5 °C min. / +30 °C max.	
Pot Life	Once opened, the product should be used promptly. Storage of partial containers may result in performance being affected.	
Waiting Time / Overcoating	Temperature	Waiting time
	20 °C	3 – 4 h
	5 °C	5 – 6 h
Sika® Reactivation Primer can be overcoated once cured and tack free. Maximum recoat period within 48 hours of application of the primer. Note: Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.		

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The surfaces must be clean, dry, free of stripping agents and free of oil, grease, silanes, salts, silicone, siloxanes and other chemicals which could cause poor adhesion.

SUBSTRATE PREPARATION

All surfaces to be coated should be thoroughly cleaned by conventional means.

Pre-treat with Sika® Biowash on areas subject to organic growth.

If in doubt apply a test area first.

For detailed information regarding substrate quality/preparation and primer chart please refer to Method Statement.

APPLICATION

Prepare Sika® Reactivation Primer by stirring thoroughly.

Sika® Reactivation Primer can be applied by short-piled roller or brush.

Allow Sika® Reactivation Primer to dry sufficiently (see table waiting time/overcoating) before overcoating.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Thinner C immediately after use. Hardened and/or cured material can only be removed mechanically.

IMPORTANT CONSIDERATIONS

- Do not apply in wet weather or to wet surfaces.
- Take care to ensure an even coverage and avoid ponding in voids and depressions.
- Do not apply close to the air intake vent of a running air conditioning unit.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our

current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF
Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF
UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA SAUDI ARABIA
Riyadh / Jeddah / Damman
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

Product Data Sheet
Sika® Reactivation Primer
July 2016, Version 01.01
02091595100000008

SikaReactivationPrimer-en-AE-(07-2016)-1-1.pdf

