

PRODUCT DATA SHEET

SikaWrap®-300 C

Woven unidirectional carbon fibre fabric, designed for structural strengthening applications as part of the Sika® strengthening system

DESCRIPTION

SikaWrap®-300 C is a unidirectional woven carbon fibre fabric with mid-range strengths, designed for installation using the dry or wet application process. Suitable for use in hot and tropical climatic conditions.

USES

SikaWrap®-300 C may only be used by experienced professionals.

Structural strengthening of reinforced concrete, masonry, brickwork and timber elements or structures, to increase flexural and shear loading capacity for:

- Improved seismic performance of masonry walls
- Replacing missing steel reinforcement
- Increasing the strength and ductility of columns
- Increasing the loading capacity of structural elements
- Enabling changes in use / alterations and refurbishment
- Correcting structural design and / or construction defects
- Increasing resistance to seismic movement
- Improving service life and durability
- Structural upgrading to comply with current standards

CHARACTERISTICS / ADVANTAGES

- Multifunctional fabric for use in many different strengthening applications
- Flexible and accommodating of different surface planes and geometry (beams, columns, chimneys, piles, walls, soffits, silos etc.)
- Low density for minimal additional weight
- Extremely cost effective in comparison to traditional strengthening techniques

APPROVALS / CERTIFICATES

- Poland: Technical Approval ITB AT-15-5604/2011: Zestaw wyrobów Sika CarboDur do wzmacniania i napraw konstrukcji betonowych.
- Poland: Technical Approval IBDiM Nr AT/2008-03-0336/1, Płaskowniki. pręty, kształtki i maty kompozytowe do wzmacniania betonu o nazwie handlowej: Zestaw materiałów Sika CarboDur® do wzmacniania konstrukcji obiektów mostowych.
- USA: ACI 440.2R-08, Guide for the Design and construction of Externally Bonded FRP Systems for strengthening concrete structures, July 2008.
- UK: Concrete Society Technical Report No. 55, Design guidance for strengthening concrete structures using fibre composite material, 2012.

PRODUCT INFORMATION

Construction	Fibre orientation Warp Weft	0° (unidirectional) Black carbon fibres 99 % White thermoplastic heat-set fibres 1 %
Fibre type	Selected mid-range strength carbon fibres	
Packaging	Fabric length per roll ≥ 100 m	Fabric width 500 mm

Shelf life	24 months from date of production		
Storage conditions	Store in undamaged, original sealed packaging, in dry conditions at temperatures between +5 °C and +35 °C. Protect from direct sunlight.		
Dry fibre density	1.82 g/cm ³		
Dry fibre thickness	0.167 mm (based on fibre content)		
Mass per area	304 g/m ² ± 10 g/m ² (carbon fibres only)		
Dry fibre tensile strength	4 000 N/mm ²		(ISO 10618)
Dry fibre modulus of elasticity in tension	230 000 N/mm ²		(ISO 10618)
Dry fibre elongation at break	1.7 %		(ISO 10618)

TECHNICAL INFORMATION

Design nominal thickness	0.167 mm		
Design nominal cross section	167 mm ² per m width		
Laminate tensile strength	Average	Characteristic	(EN 2561*)
	3 500 N/mm ²	3 200 N/mm ²	(ASTM D 3039*)
Laminate modulus of elasticity in tension	Average	Characteristic	(EN 2561*)
	225 kN/mm ²	220 kN/mm ²	
	Average	Characteristic	(ASTM D 3039*)
	220 kN/mm ²	210 kN/mm ²	
* modification: sample with 50 mm Values in the longitudinal direction of the fibres Single layer, minimum 27 samples per test series			
Laminate elongation at break in tension	1.56 %		(EN 2561)
	1.59 %		(ASTM D 3039)
Tensile resistance	Average	Characteristic	(EN 2561)
	585 N/mm	534 N/mm	(ASTM D 3039)
Tensile stiffness	Average	Characteristic	(EN 2561)
	37.6 MN/m	36.7 MN/m	
	37.6 kN/m per ‰ elongation	36.7 kN/m per ‰ elongation	
	Average	Characteristic	(ASTM D 3039)
	36.7 MN/m	35.1 MN/m	
	36.7 kN/m per ‰ elongation	35.1 kN/m per ‰ elongation	

SYSTEM INFORMATION

System structure	<p>The system build-up and configuration as described must be fully complied with and may not be changed.</p> <table border="0"> <tr> <td>Concrete substrate adhesive primer</td> <td>Sikadur®-330</td> </tr> <tr> <td>Impregnating / laminating resin</td> <td>Sikadur®-330 or Sikadur®-300</td> </tr> <tr> <td>Structural strengthening fabric</td> <td>SikaWrap®-300 C</td> </tr> </table> <p>For detailed information on Sikadur®-330 or Sikadur®-300, together with the resin and fabric application details, please refer to the Sikadur®-330 or Sikadur®-300 Product Data Sheet and the relevant Method Statement.</p>			Concrete substrate adhesive primer	Sikadur®-330	Impregnating / laminating resin	Sikadur®-330 or Sikadur®-300	Structural strengthening fabric	SikaWrap®-300 C
Concrete substrate adhesive primer	Sikadur®-330								
Impregnating / laminating resin	Sikadur®-330 or Sikadur®-300								
Structural strengthening fabric	SikaWrap®-300 C								

APPLICATION INFORMATION

Consumption

Dry application with Sikadur®-330

First layer including primer layer	1.0 - 1.5 kg/m ²
Following layers	0.8 kg/m ²

Wet application with Sikadur®-300

Primer layer	0.4 - 0.6 kg/m ²
Fabric layers	0.6 kg/m ²

Note: Consumption is for standard application only. Rough or uneven substrate surfaces, loss and wastage may lead to a higher consumption.

Please refer to the relevant Method Statement for further information.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

Please refer to the Method Statement of SikaWrap® manual dry application, SikaWrap® manual wet application or SikaWrap® machine wet application for further information, guidelines and limitations.

IMPORTANT CONSIDERATIONS

- SikaWrap®-300 C shall only be applied by trained and experienced professionals.
- A specialist structural engineer must be consulted for any structural strengthening design calculation.
- SikaWrap®-300 C fabric is coated to ensure maximum bond and durability with the Sikadur® adhesives / impregnating / laminating resins. To maintain and ensure full system compatibility, do not interchange different system components.
- SikaWrap®-300 C can be over coated with a cementitious overlay or other coatings for aesthetic and / or protective purposes. The over coating system selection is dependent on the exposure and the project specific requirements. For additional UV light protection in exposed areas use e.g. Sikagard®-550 W Elastic (G).

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Minimal substrate tensile strength: 1.0 N/mm² or as specified in the strengthening design.

Please also refer to the relevant Method Statement or further information.

SUBSTRATE PREPARATION

Concrete must be cleaned and prepared to achieve a laitance and contaminant free, open textured surface. Please also refer to the relevant Method Statement for further information.

APPLICATION METHOD / TOOLS

The fabric can be cut with special scissors or a Stanley knife (razor knife / box-cutter knife). Never fold the fabric.

SikaWrap®-300 C is applied using the dry or wet application process.

Please refer to the relevant Method Statement for details on the impregnating / laminating procedure

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Kuwait
Tel: +973 177 38188
info@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

Sika Saudi Arabia

Riyadh / Jeddah / Dammam
Tel. +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001, 14001, 45001 –
Lloyd's Register
Sika S.A.C. LLC,
Sika International Chemicals LLC,
ISO 9001, 14001, 45001 – SGS
Sika Gulf S.S.C. O.
ISO 9001, 14001 – SGS;
Sika Saudi Arabia Limited

All products are supplied under
a management system certified
to conform to the requirements
of the quality, environmental
and occupational health &
safety standards ISO 9001, ISO
14001 and ISO 45001.



SikaWrap-300C-en-AE-(06-2023)-1-3.pdf

Product Data Sheet

SikaWrap®-300 C

June 2023, Version 01.03
020206020010000011