

PRODUCT DATA SHEET

Sikalastic®-851

LIQUID APPLIED POLYURETHANE/ POLYUREA HYBRID MEMBRANE

DESCRIPTION

Sikalastic®-851 is a two part, elastic, 100 % solids, very fast curing and coloured Polyurethane/ Polyurea-Hybrid liquid applied membrane with moderate chemical resistance.

Suitable for use in hot and tropical climatic conditions.

USES

Sikalastic®-851 may only be used by experienced professionals.

On Concrete:

- Waterproofing on concrete bridge decks, membrane underneath hot rolled asphalt, certified in accordance to BBA/HAPAS
- Waterproofing on concrete bridge decks, membrane underneath mastic asphalt, tested in accordance to ETAG 033
- Waterproofing for submersed structures
- Waterproofing for cut and cover structures
- Waterproofing on walkways and balconies
- Waterproofing on floors and car park decks
- Water retaining structures in power plants
- Tank, bund and pit lining in fresh water areas of sewage and waste water treatment plants

On Steel:

- Truck bed lining

CHARACTERISTICS / ADVANTAGES

- Very fast reactivity and curing time
- Almost immediate return-to-service time
- Applicable in temperatures from -10 °C to +50 °C
- Performs in constant dry temperatures from -30 °C to +100 °C
- Excellent crack bridging properties
- Moderate chemical resistance
- Good abrasion resistance
- Not UV resistant

SUSTAINABILITY

Conformity with LEED v2009 IEQc 4.2: Low-Emitting Materials - Paints and Coatings

APPROVALS / CERTIFICATES

- Coating for concrete protection according the requirements of EN 1504-2/2004, DoP 02 07 0 20 5001 0 000003, certified by FPC Notified Body and provided with CE-Marking
- KIWA Polymer Institut GmbH, report No. P9016-1-E, 2014, Testing of static and dynamic crack bridging ability in accordance with DIN EN 1062-7, as well as bond strength after freeze-thaw-cycling with de-icing salt immersion and after thundershower cycling in accordance with DIN EN 13687-1 and -2, in combination with Sikafloor®-161
- KIWA Polymer Institute GmbH, report No. P7934, 2014, Testing of the root resistance in accordance with DIN 4062
- Prüfinstitut Hoch, test report No. 140941, reation to fire classification in accordance with DIN EN 13501-1
- Dr. Kemski, determination of radon diffusion coefficient and radon diffusion length in accordance with DIN ISO 11665-10
- KIWA Polymer Institute GmbH, test report P-10064-1, test on accordance with German Guideline "Liquid applied waterproofing kits for buildings" (PG-FLK)

PRODUCT INFORMATION

Composition	Poyurethane/ Polyurea Hybrid		
Packaging	Part A	211 kg drums ~189 L (Isocyanate)	
	Part B	202 kg drums ~189 L (Polyol/ -amine)	
Appearance / Colour	Part A	Clear	
	Part B	Grey	
	Grey, approximately RAL 7004		
Shelf life	12 month from date of production		
Storage conditions	The packaging must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5 °C and +30 °C. Protected from direct sunlight.		
Density	Part A	~1.08 kg/l	
	Part B	~1.04 kg/l	
	Density values determined at +20 °C		
Solid content	~99 %		
Viscosity	Temperature	Part A	Part B
	+20 °C	~2300 mPas	~2300 mPas

TECHNICAL INFORMATION

Shore A Hardness	~85			(DIN 53505)
Mechanical Resistance	~13 mg	H17 / 1000 g / 1000 cy	(ISO 5470-1)	
	~480 mg	H22 / 1000 g / 1000 cy		
Tensile Strength	~11 N/mm ²			(DIN 53504)
Elongation at Break	~350 %			(DIN 53504)
Crack Bridging Ability	Class A5	Static	(DIN EN 1062-7)	
	Class B4.2	Dynamic	(DIN EN 1062-7)	
Chemical Resistance	Sikalastic®-851 is resistant to de-icing salts, bitumen, alkalis, fresh- and ground water and various chemicals. Contact Sika Technical Department for specific information.			

APPLICATION INFORMATION

Mixing Ratio	Part A : Part B = 1 : 1 (volume)		
Consumption	~1.05 kg/m ² per mm thickness		
Layer Thickness	~2 mm		
Product Temperature	Comp. A (ISO)	+70 °C min. / +80 °C max.	
	Comp. B	+70 °C min. / +80 °C max.	
Ambient Air Temperature	+1 °C min. / +40 °C max.		
Relative Air Humidity	85 % max.		
Substrate Temperature	+1 °C min. / +50 °C max.		
	Min. 3 °C above dew point, beware of condensation		
Curing Time	24 h at +20 °C		
Gel time	~11 s at +20 °C		
Waiting Time / Overcoating	1 – 2 min at +20 °C		

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².

The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.

Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.

Weak concrete must be removed and surface defects such as blow holes and voids must be fully exposed.

Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor[®], Sikadur[®], Sika[®] Monotop[®], SikaRep[®] and Sikagard[®] range of materials.

All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum.

SUBSTRATE PREPARATION

The surface must be sound, of sufficient strength, clean, dry and free of dirt, oil, grease and other contamination.

All substrate must be primed or mechanically cleaned. Grinding may be necessary to level the surface. Suitable substrates are, for example Concrete, bituminous felts.

For detailed information regarding substrate preparation and primer chart please refer to Method Statement.

Substrate Pre-Treatment Substrate Primer

Cementitious substrates	Sika [®] Concrete Primer or Sikafloor [®] -161 lightly broadcast with quartz sand, 0.3 – 0.8 mm, for example Sikadur [®] -507
Permanently submerged area	Sikafloor [®] -161 lightly broadcast with quartz sand, 0.3 – 0.8 mm, for example Sikadur [®] -507

For the consumption rates and waiting time / overcoating please refer to the PDS of the appropriate primer. Other substrates must be tested for their compatibility. If in doubt, apply a test area first.

APPLICATION

Dose and mix with a suitable air driven or electrical plural component heated spray equipment. Both components must be heated up to approximately 80 °C. The accuracy of mixing and dosage must be controlled regularly with the equipment. Thoroughly stir part B (Amine) using a drum stirrer until a homogenous colour is obtained.

CLEANING OF EQUIPMENT

Clean all tools with Thinner C immediately after use. The application equipment has to be cleaned and filled with Mesamoll. Hardened and/or cured material can only be removed mechanically.

IMPORTANT CONSIDERATIONS

This product may only be used by experienced professionals.

For spray application the use of protective health and safety equipment is mandatory.

Do not apply Sikalastic[®]-851 on substrates with rising moisture.

On substrates likely to exhibit outgassing, apply during falling ambient and substrate temperatures. If applied during rising temperatures "pin holing" may occur from rising air.

Product shall be used in conjunction with a safe system of work. Ensure an adequate assessment of all site risks has been conducted prior to work commencing.

Do not use Sikalastic[®]-851 for indoor applications.

Sikalastic[®]-851 is not UV light resistant and changes colour under UV exposure. However, the performance and technical properties are not affected

providing the exposure is maximum 4 weeks. It is therefore advisable to overcoat Sikalastic[®]-851 with UV protective top coat as early as possible.

Please note: Always apply a test area first

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied
under a management
system certified to conform
to the requirements of the
quality, environmental and
occupational health &
safety standards ISO 9001,
ISO 14001 and OHSAS
18001.

Product Data Sheet

Sikalastic®-851

February 2018, Version 02.02

020702050010000003

Sikalastic-851-en-AE-(02-2018)-2-2.pdf