

BUILDING TRUST

PRODUCT DATA SHEET

SikaControl®-3122 WT

(formerly MLife WP 3122)

Unique waterproofing admixture combining crystalline and hydrophobic pore-blocking ingredients

DESCRIPTION

SikaControl®-3122 WT is a waterproofing liquid admixture having both integral crystalline capillary and hydrophobic pore-blocking functions. It is designed for use in above- and below-grade applications. SikaControl®-3122 WT consists of various active, proprietary chemicals. These active chemicals react with the by-products of cement hydration to cause a reaction, which generates an insoluble crystalline deposit throughout the pores and capillary tracts of the concrete. Thus, the concrete with SikaControl®-3122 WT reduces water permeability. This product also has a self-healing property in the presence of moisture and can help with crack healing.

Suitable to use in hot and tropical climatic conditions.

USES

SikaControl®-3122 WT can be used in all structural concrete that is constantly or intermittently in contact with water such as sea walls, tunnels, basements, structural and pre-cast concrete. SikaControl®-3122 WT can also be used as crystalline waterproofing admixture for cement mortars and plasters. SikaControl®-3122 WT can be used to enhance the waterproofing properties of structures such as:

- Building basement and foundations
- Sewage and water treatment plants
- Dams, canals, tunnels, harbours
- Tunnel and subway systems
- Water reservoirs
- Concrete pipes
- Parking structures
- Pre-cast, cast-in-place and shotcrete applications
- Swimming pools
- Retaining walls and sea defense walls

FEATURES

- Liquid product facilitates accurate measurement and recording of addition through existing concrete batch plant dispensing system
- Reduces concrete permeability
- Allows concrete to breathe
- Non-toxic
- Becomes an integral part of the concrete
- Reduces penetration of water and other liquids under pressure
- Can help to seal hairline cracks
- Protects against sewage and industrial wastes
- Added to the concrete at time of batching and therefore, is not subject to climatic restraints

CERTIFICATES AND TEST REPORTS

SikaControl®-3122 WT is categorized as PRAH within ACI 212.3R-10 "Report on Chemical Admixtures for concrete" (Permeability reducing admixtures)

Product Data Sheet

SikaControl®-3122 WTNovember 2024, Version 02.01
021403000000002046

TECHNICAL INFORMATION

Concreting guidance	Points to remember when producing waterproof concrete:
	 Ensure water / cement ratio is less than 0.5
	 Addition of superplasticiser from the Sikament[®], SikaPlast[®] or Sika[®] Vis-
	coCrete® range is advised to achieve minimum water/cement ratio.
	 Good concrete practice as per ACI standards regarding mixing, placing
	and curing.
	 Use Sika® Antisol® products as a curing agent or apply wet hessian.
Effect on setting	SikaControl®-3122 WT admixture has minor to no effect on concrete setting time within the recommended dosage range. However, it is recommended to test this in case any additives or blended cementitious combin-
	ations are used.
PRODUCT INFORMATION	
Composition	Variuos active chemicals
Packaging	Drums or 1,000 L flowbins
Shelf life	6 months from date of production if stored properly
Storage conditions	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5°C and +50°C.
Appearance and colour	Clear to yellow liquid
Density	~1.06 kg/l (+25 °C)
Total chloride ion content	Nil (EN 934)
APPLICATION INFORMATI	
APPLICATION INFORMATI	1–2.5 % by weight of binder.
APPLICATION INFORMATI	ION
APPLICATION INFORMATI	1–2.5 % by weight of binder. Dosage may vary depending on the mix design, raw materials, climatic con-
APPLICATION INFORMATI	1–2.5 % by weight of binder. Dosage may vary depending on the mix design, raw materials, climatic conditions and concrete requirements. To ready mix concrete, a typical dosage of 6–7 kg/m³ of concrete is recommended. However, the optimum dosage to meet project requirements
APPLICATION INFORMATI	1–2.5 % by weight of binder. Dosage may vary depending on the mix design, raw materials, climatic conditions and concrete requirements. To ready mix concrete, a typical dosage of 6–7 kg/m³ of concrete is recom-
APPLICATION INFORMATI Recommended dosage	1–2.5 % by weight of binder. Dosage may vary depending on the mix design, raw materials, climatic conditions and concrete requirements. To ready mix concrete, a typical dosage of 6–7 kg/m³ of concrete is recommended. However, the optimum dosage to meet project requirements must be determined through trial mixes. SikaControl®-3122 WT should be added within the recommended dosage.
APPLICATION INFORMATI Recommended dosage	1–2.5 % by weight of binder. Dosage may vary depending on the mix design, raw materials, climatic conditions and concrete requirements. To ready mix concrete, a typical dosage of 6–7 kg/m³ of concrete is recommended. However, the optimum dosage to meet project requirements must be determined through trial mixes. SikaControl®-3122 WT should be added within the recommended dosage. It may be batched in either a central or truck mixer.
APPLICATION INFORMATI Recommended dosage	1–2.5 % by weight of binder. Dosage may vary depending on the mix design, raw materials, climatic conditions and concrete requirements. To ready mix concrete, a typical dosage of 6–7 kg/m³ of concrete is recommended. However, the optimum dosage to meet project requirements must be determined through trial mixes. SikaControl®-3122 WT should be added within the recommended dosage. It may be batched in either a central or truck mixer. Follow the procedures outlined in ASTM C94 / C94M, Standard Specifica-
APPLICATION INFORMATI Recommended dosage	1–2.5 % by weight of binder. Dosage may vary depending on the mix design, raw materials, climatic conditions and concrete requirements. To ready mix concrete, a typical dosage of 6–7 kg/m³ of concrete is recommended. However, the optimum dosage to meet project requirements must be determined through trial mixes. SikaControl®-3122 WT should be added within the recommended dosage. It may be batched in either a central or truck mixer. Follow the procedures outlined in ASTM C94 / C94M, Standard Specification for Ready-Mixed Concrete, for general batching and mixing instruc-
APPLICATION INFORMATI Recommended dosage	1–2.5 % by weight of binder. Dosage may vary depending on the mix design, raw materials, climatic conditions and concrete requirements. To ready mix concrete, a typical dosage of 6–7 kg/m³ of concrete is recommended. However, the optimum dosage to meet project requirements must be determined through trial mixes. SikaControl®-3122 WT should be added within the recommended dosage. It may be batched in either a central or truck mixer. Follow the procedures outlined in ASTM C94 / C94M, Standard Specification for Ready-Mixed Concrete, for general batching and mixing instructions for concrete if adding to a truck mixer.
APPLICATION INFORMATI Recommended dosage	1–2.5 % by weight of binder. Dosage may vary depending on the mix design, raw materials, climatic conditions and concrete requirements. To ready mix concrete, a typical dosage of 6–7 kg/m³ of concrete is recommended. However, the optimum dosage to meet project requirements must be determined through trial mixes. SikaControl®-3122 WT should be added within the recommended dosage. It may be batched in either a central or truck mixer. Follow the procedures outlined in ASTM C94 / C94M, Standard Specification for Ready-Mixed Concrete, for general batching and mixing instructions for concrete if adding to a truck mixer. Provide at least 5 minutes of mixing after the addition of SikaControl®-
APPLICATION INFORMATI Recommended dosage Dispensing	1–2.5 % by weight of binder. Dosage may vary depending on the mix design, raw materials, climatic conditions and concrete requirements. To ready mix concrete, a typical dosage of 6–7 kg/m³ of concrete is recommended. However, the optimum dosage to meet project requirements must be determined through trial mixes. SikaControl®-3122 WT should be added within the recommended dosage. It may be batched in either a central or truck mixer. Follow the procedures outlined in ASTM C94 / C94M, Standard Specification for Ready-Mixed Concrete, for general batching and mixing instructions for concrete if adding to a truck mixer. Provide at least 5 minutes of mixing after the addition of SikaControl®-3122 WT admixture to ensure thorough and uniform distribution of the admixture in the concrete mixture.
APPLICATION INFORMATI Recommended dosage Dispensing	1–2.5 % by weight of binder. Dosage may vary depending on the mix design, raw materials, climatic conditions and concrete requirements. To ready mix concrete, a typical dosage of 6–7 kg/m³ of concrete is recommended. However, the optimum dosage to meet project requirements must be determined through trial mixes. SikaControl®-3122 WT should be added within the recommended dosage. It may be batched in either a central or truck mixer. Follow the procedures outlined in ASTM C94 / C94M, Standard Specification for Ready-Mixed Concrete, for general batching and mixing instructions for concrete if adding to a truck mixer. Provide at least 5 minutes of mixing after the addition of SikaControl®-3122 WT admixture to ensure thorough and uniform distribution of the admixture in the concrete mixture. SikaControl®-3122 WT is suitable for mixes containing all types of cement and supplementary cementitious materials such as Microsilica (Silica Fume), Fly Ash (PFA), GGBS (Ground Granulated Blast Furnace Slag) and the following Sika products:
APPLICATION INFORMATI Recommended dosage Dispensing Compatibility	1–2.5 % by weight of binder. Dosage may vary depending on the mix design, raw materials, climatic conditions and concrete requirements. To ready mix concrete, a typical dosage of 6–7 kg/m³ of concrete is recommended. However, the optimum dosage to meet project requirements must be determined through trial mixes. SikaControl®-3122 WT should be added within the recommended dosage. It may be batched in either a central or truck mixer. Follow the procedures outlined in ASTM C94 / C94M, Standard Specification for Ready-Mixed Concrete, for general batching and mixing instructions for concrete if adding to a truck mixer. Provide at least 5 minutes of mixing after the addition of SikaControl®-3122 WT admixture to ensure thorough and uniform distribution of the admixture in the concrete mixture. SikaControl®-3122 WT is suitable for mixes containing all types of cement and supplementary cementitious materials such as Microsilica (Silica Fume), Fly Ash (PFA), GGBS (Ground Granulated Blast Furnace Slag) and the following Sika products: SikaPlast®, Sika® ViscoCrete®, Sikament®, Plastiment®, SikaPump®, Sika® FerroGard®, SikaFume®, SikaFiber®, Sika® Aer, Sika® Stabilizer, SikaCon-
APPLICATION INFORMATI Recommended dosage Dispensing	1–2.5 % by weight of binder. Dosage may vary depending on the mix design, raw materials, climatic conditions and concrete requirements. To ready mix concrete, a typical dosage of 6–7 kg/m³ of concrete is recommended. However, the optimum dosage to meet project requirements must be determined through trial mixes. SikaControl®-3122 WT should be added within the recommended dosage. It may be batched in either a central or truck mixer. Follow the procedures outlined in ASTM C94 / C94M, Standard Specification for Ready-Mixed Concrete, for general batching and mixing instructions for concrete if adding to a truck mixer. Provide at least 5 minutes of mixing after the addition of SikaControl®-3122 WT admixture to ensure thorough and uniform distribution of the admixture in the concrete mixture. SikaControl®-3122 WT is suitable for mixes containing all types of cement and supplementary cementitious materials such as Microsilica (Silica Fume), Fly Ash (PFA), GGBS (Ground Granulated Blast Furnace Slag) and the following Sika products: SikaPlast®, Sika® ViscoCrete®, Sikament®, Plastiment®, SikaPump®, Sika®





BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- SikaControl®-3122 WT will neither initiate nor promote corrosion of reinforcing steel embedded in concrete, prestressed concrete or concrete placed on galvanized steel floor and roof systems.
- Neither calcium chloride nor any calcium chloride based ingredients are used in the manufacture of SikaControl®-3122 WT. In all concrete application, SikaControl®-3122 WT will conform to the most stringent or minimum chloride ion limits currently suggested by construction industry standards and practices.
- SikaControl®-3122 WT has minor or no effect on workability of concrete. Prior site trials are advised to assess the effect and any increase or decrease in the workability can be adjusted by adjusting the admixture dosage or amount of water in use.
- It is strongly recommended that concrete should be properly cured particularly in hot, windy and dry climates.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC Sika International Chemicals LLC Tel: +971 4 439 8200 Email: info@ae.sika.com Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC Riyadh / Jeddah / Dammam / Rabigh Tel: +966 12 692 7079 Email: info@sa.sika.com Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC (part of Sika) Tel. +968 22 826 500 Email: info@om.sika.com Web: gcc.sika.com



ISO 9001, 14091, 65901 – 565:

- Sha LME LLC
- Sha Guif E.S.C. D
- Sha International Chemicals LLC
- Sha Guif E.S.C. D
- Sho South Associated
- Sha South Anabla Limited
- Sha South Anabla Limited
- Sho 9001, 14003 – TÜN:
- Sha MB Construction Chemicals LLC
- Sha Construction Chemicals
- Sha Construction Chemicals
- Sha Construction Chemicals
- Anaber Builders Solutions LLC
- Anaber Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



SikaControl-3122WT-en-AE-(11-2024)-2-1.pdf

