

PRODUCT DATA SHEET

SikaCeram[®]-434

(formerly MTile 434)

HIGH PERFORMANCE, ONE COMPONENT, LATEX POLYMER MODIFIED TILE ADHESIVE

DESCRIPTION

SikaCeram[®]-434 is a high performance, 1-component, latex polymer containing, water resistant, premixed adhesive.

Suitable for use in hot and tropical climatic conditions.

USES

- Suitable for laying ceramic tiles, porcelain and glass mosaics, brick tiles, clinker bricks, fully vitrified tiles non-moisture sensitive natural stone tiles and pavers.
- Suitable to be used in swimming pools, pool surroundings, wet rooms and cold storage depots.
- Suitable to be used on cement screeds, ground anhydrite and/or gypsum based floated screeds, precast concrete elements, aerated concrete, heated screeds, plasterboards, gypsum fiber boards, dry screeds, insulation boards, plaster slabs, plaster and on existing wall and floor tiles.

- Suitable for laying ceramic on the bonded water-proofing Sikalastic[®] WP 668.
- Suitable for laying ceramic tiles on the crack isolating fabric underlay SikaCeram[®] WP 680.

FEATURES

- For indoor and outdoor use
- For walls and floors
- Water resistant
- Non sag, no need for battens and spacers
- Flexible, compensates changes in temperature and elongations of the substrate
- Easy and quick application

CERTIFICATES AND TEST REPORTS

SikaCeram[®]-434 conforms to the requirements of ANSI A118.4 for latex portland cement mortar.

PRODUCT INFORMATION

| | |
|------------------------------|--|
| Composition | Consisting of portland cement, sand and specific additives. |
| Packaging | 20 kg and 25 kg bag |
| Shelf life | 12 months from date of production |
| Storage conditions | Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5°C and +35°C. Protect from direct sunlight, heat and moisture. |
| Appearance and colour | Grey or white powder |
| Density | ~1.81 kg/l (mixed, at 25°C) |

TECHNICAL INFORMATION

Service temperature -30°C min. / +80°C max.

SYSTEM INFORMATION

System structure In normal conditions on cement-based substrate, no primer is required. However, for very high absorbent substrates (e.g. drywalls) or non-absorbent substrates, please contact Sika Technical Service for recommendation.

APPLICATION INFORMATION

Consumption Powder consumption and coverage depends on the surface profile and roughness of the substrate, size and reverse profile of the tiles and the placing technique (simple placing "floating" or back to back "buttering-floating").
As a guide for solid bed application:
For 1 mm thickness over 1 m² area approximately 1.4 kg of powder is required.
This figure is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level, wastage or any other variations. Apply product to a test area to calculate the exact consumption for the specific substrate conditions and proposed application equipment. Above consumption indications refer to the installation of slightly profiled, non-vitrified or vitrified tiles on flat substrate e.g. render or cement screed. For small sized tiles (side ≤30 cm), use small squared notch size trowel (4 - 6 mm) and progressively increases for medium tiles (side ≤45 cm, trowel 6 - 8 mm) or large tiles (side ≤60 cm, trowel 8 - 10 mm).

Layer thickness Max. 10 mm
(locally up to 12 mm thickness possible, for small area leveling purpose)

Ambient air temperature +5°C min. / +40°C max.

Mixing ratio 5.4 to 5.6 L of water per 20 kg bag
6.75 to 7.0 L of water per 25 kg bag

Maturing time ~3 min (Slake time)

Pot Life ~1 h (at +23°C)

Open Time ~30 min (at +23°C)

| | | |
|--------------------------------------|----------------------|---------|
| Applied product ready for use | Tiles can be grouted | ~24 h |
| | Foot traffic | ~24 h |
| | Able to bear weight | ~7 days |

Values determined in laboratory conditions: +23°C ± 2°C, R.H. 50 % ± 5 %. Higher temperatures will reduce the indicated waiting times, lower temperatures will increase the indicated waiting time.

BASIS OF PRODUCT DATA

- All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
- Internal Reference - Version: MBS_CC-UAE/Tile_434_06_15/v4/07_16/v5/06_18/v6/09_19

FURTHER DOCUMENTATION

- General Method Statement (GMS)

IMPORTANT CONSIDERATIONS

- Protect from adverse weather conditions, such as extremely high or low temperatures, rain, direct exposure to sun, wind, etc. for at least 24 hours from application.
- Avoid application in direct sunlight and/or strong wind / draughts.
- Make a test area prior to carrying out any work with natural stones.
- White version of tile adhesive is recommended for translucent natural stone tiles and glass mosaic.

- Substrates made of precast concrete elements and/or in-situ concrete must be sufficiently cured as per common industry practice.
- The open time is reduced in case of absorbent substrates (recommendation: priming with SikaCeram® P 302).
- Never add water or dry powder to reconstitute a SikaCeram®-434 mix which has already begun to set.
- When laying tiles outdoors use SikaCeram®-434 in the combined method (buttering-floating).
- After laying mosaic tiles it is required to remove the adhesive from the joints down to a uniform depth to ensure proper, stain-free grouting afterwards. This also applies to front-sided paper-faced mosaic.
- When laying mosaic in swimming pools use only front sided paper-faced or front-sided foil-faced mosaic.
- Glass tiles with a reaction resin coating on the reverse side may be laid with SikaCeram®-434 only if the coating is alkali resistant.
- For natural stones or artificial stones subject to staining and/or deformation please use suitable tile adhesive. Please consult Sika Technical Service for recommendation.
- For facade tiles installation and fixing, follow the recommendations stated in BS 5385-1:2018 and/or DIN 18 515-1 "Outwall claddings" standards.

SikaCeram®-434 shall not be applied on the following cases:

- On metal surfaces and wood
- On old outdoor ceramic tiles
- For stone wares and porcelain large tiles (side > 60 cm)

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

EQUIPMENT

Select the most appropriate equipment required for the project:

Substrate preparation equipment:

- Grinding equipment
- Abrading equipment
- Power washing equipment
- Sandblasting equipment

Mixing equipment:

Low speed electric single or double paddle mixer (300–400 rpm) with a spiral mixing paddle.

Application equipment:

Notched trowel, various sizes

SUBSTRATE QUALITY

Minimum age of the substrate:

- SikaLevel® range – 3 days
- Cement screed - 28 days

Note: The screed drying time is subject to the screed thickness and site conditions. For applications before 28 days, contact Sika Technical Service Department. Newly applied cement screeds must not have a residual moisture content over 4%, anhydrite and/or gypsum-based screeds not more than 0.5% (measured with a CM meter).

SUBSTRATE PREPARATION

- Cementitious substrates must be sufficiently cured and dried.
- All substrates must be structurally sound, able to support the weight of the new tiling and provide a firm and securely fixed background.
- The substrate must be perfectly flat, tight and free from easily removable parts, non-deformable and correctly aged.
- Substrates must be clean, dry, free of any loose or friable particles, contaminants such as dust, dirt, oil, wax polish, grease, cement laitance or efflorescence.
- Use adequate mechanical preparation techniques to remove from the substrate, all traces of any materials that could reduce the product's adhesion to the substrate.
- The substrate must be plumb and flush in accordance with BS 5385. Plaster substrates must be approved by the plaster manufacturer for fixing ceramic tiles and must be suitable for the intended area of use.
- Smooth surfaces must be roughened lightly to improve adhesion.
- To confirm adequate surface preparation and adhesion, carry out a small trial before full application.
- For larger and thicker areas of substrate re-profiling, use suitable mortars from the Sika MonoTop® or SikaEmaco® range. Level concrete floors with SikaScreed® or Sikafloor® Level range.
- For any repairs of the substrate materials of SikaEmaco®, SikaRep® or Sika MonoTop® range should be used, applied at least 24 hours before laying the ceramic tiles.
- Identify cracks in the substrate and seal appropriately with Sikadur® epoxy resins.
- For applications in hot climates / environments, or on absorbent substrates, thoroughly pre-dampen (saturate) the substrate before product application. Avoid any ponding / standing water on the substrate. Surface must not be damp to touch.
- For tiling in constantly damp or wet rooms, a suitable Sika® waterproofing product / system must be applied to the substrate before tiling.
- Prime very absorbent cement-based substrates and aerated concrete with SikaCeram® P 302, diluted 1:1 with water, anhydrite and/or gypsum based floated screeds as well as gypsum-based substrates inside of buildings with undiluted SikaCeram® P 302. Allow the primer to dry.

MIXING

- Mix a bag with the necessary, above mentioned, amount of water, using an electric blender with a suitable mixing spiral at low speed, in a clean bucket, to obtain a smooth paste free of lumps.
- Use a blender at 500 rpm maximum; do not mix at faster rate because of mechanical strength decay of the cured product.
- Allow a maturing time (slake time) of approx. 3 minutes for SikaCeram®-434 in the mixing container, then remix briefly prior to application.
- Always start with minimum recommended quantity of water (water/powder ratio), only if required, gradually add water to desired consistency. Do not exceed the maximum allowed limit of water per bag weight.
- The obtained mix results should be very creamy, easily spreadable and thixotropic.
- Do not mix more material than can be used within 60 minutes.

APPLICATION

SikaCeram®-434 is applied using notched trowel. The amount of product should be enough to ensure complete wetting of the tiles rear. Tiling has to be carried out on fresh glue, exerting an adequate pressure to ensure contact with the adhesive, and thus the perfect bonding. In case a surface film is formed on the adhesive, it is necessary to wipe the trowel on the adhesive layer previously applied. Avoid wetting already applied adhesive with water, as it may negatively affect its properties.

Note: For tiles > 900 cm² (30 x 30 cm), the double spreading ("buttering") technique is always recommended.

Adhesive application:

- Apply a thin scratch coat to the substrate with the smooth edge of the trowel.
- Comb mortar onto the fresh scratch coat with a notched trowel.
- Apply sufficient adhesive to the prepared fixing surfaces with the notched trowel to the required bed thickness, in one direction.
- Place the tiles in the adhesive bed with a twist and slide motion and adjust to correct position.
- Adjust the tiles if required.
- Clean off surplus adhesive from tile face and between tile joints before the adhesive has dried.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188

Email: info@bh.sika.com

Sika Kuwait Cons. Mat. & Paints Co WLL

Tel: +965 22 282 296

Email: sika.kuwait@kw.sika.com

Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC

Sika International Chemicals LLC

Tel: +971 4 439 8200

Email: info@ae.sika.com

Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC

Riyadh / Jeddah / Dammam / Rabigh

Tel: +966 12 692 7079

Email: info@sa.sika.com

Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC (part of Sika)

Tel. +968 22 826 500

Email: info@om.sika.com

Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
-Sika UAE LLC
-Sika International Chemicals LLC
-Sika Gulf B.S.C. (c)
ISO 9001, 14001 – SGS
-Sika Saudi Arabia Limited
ISO 9001, 14001 – TÜV
-Sika MB Construction Chemicals LLC
-Sika Construction Chemicals for Manufacturing LLC
-Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

SikaCeram®-434

September 2024, Version 03.01

02171000000002036