

## PRODUCT DATA SHEET

# Sika® Plastocrete® N AE

## Waterproofing admixture for Concrete

### DESCRIPTION

Sika® Plastocrete® N AE is a concrete admixture in liquid form that acts as both a highly efficient plasticizer and as a waterproofing agent. Suitable for use in hot and tropical climatic conditions.

### USES

Sika® Plastocrete® N AE is recommended for use in structural and mass concrete particularly for water-retaining structures wherever waterproof concrete is required such as:

- Reservoirs and dams
- Sewage treatment plants
- Canals
- Culverts
- Tunnels
- Swimming pools
- Concrete water tanks

### FEATURES

Sika® Plastocrete® N AE provides the following properties:

- Improved workability without increased water content
- Allows easier compaction leading to denser concrete and superior finish
- Increased strength and durability
- Reduced shrinkage
- Improved water-tightness
- Chloride free

### CERTIFICATES AND TEST REPORTS

Sika® Plastocrete® N AE follows the requirements of ASTM C494; Type A and EN 934-2

### PRODUCT INFORMATION

<b>Composition</b>	Modified lignosulphonate
<b>Packaging</b>	5 and 20 kg pail 200 L drum, 1000 L flowbin Bulk supply in tanker trucks possible on request
<b>Appearance and colour</b>	Brown liquid
<b>Shelf life</b>	12 months from date of production if stored properly
<b>Storage conditions</b>	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5 °C and +45 °C. Protect from direct sunlight and frost.
<b>Density</b>	~1.09 kg/l (+25 °C)
<b>Total chloride ion content</b>	Nil (EN 934-2)

## TECHNICAL INFORMATION

---

### Concreting guidance

The standard rules of good concreting practice for production and placing must be observed when using Sika® Plastocrete® N AE in concrete. Refer to relevant standards.

Fresh concrete must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Use Sika® Antisol® products as a curing agent or apply wet hessian.

---

## APPLICATION INFORMATION

---

### Recommended dosage

0.5 % by weight of binder.

Other dosages by weight of binder can be used depending on the mix design, raw materials, climatic conditions and concrete requirements.

Trial mixes must be performed to establish the exact dosage rate required.

---

### Compatibility

Sika® Plastocrete® N AE may be combined with all types of Portland cement (OPC and SRC), concretes containing pozzolanic materials such as GGBS, PFA, micro-silica and the following Sika ranges and products: Sikament®, Sika® Plastiment®, SikaPump®, Sika® FerroGard®-901, SikaFume®, SikaFiber®, Sika® Aer, Sika® Stabilizer, Sika®-1 WT, Sika® WT-10.

We recommend to perform trial mixes to establish the required performance when combining Sika® Plastocrete® N AE with the above products or other admixtures. Please consult our Sika Technical Department.

---

### Dispensing

Sika® Plastocrete® N AE is added to the gauging water or simultaneously poured with it into the concrete mixer at the batching plant.

Do not add Sika® Plastocrete® N AE directly to the dry mix.

For optimum utilization we recommend thorough mixing at a minimum wet mixing time of 60 seconds.

The addition of the remaining gauging water (to fine tune concrete consistency) may only be started after two-thirds of the wet mixing time to avoid surplus water in the concrete.

---

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATIONS

Before pouring, suitability tests on the fresh concrete must be carried out.

Take special care that formwork is properly installed and secured.

If frozen and/or if precipitation has occurred, it may only be used after thawing slowly at room temperature and intensive mixing.

When using Sika® Plastocrete® N AE, a suitable concrete mix must be designed for the local material sources and should be trialed.

When accidental overdosing occurs the set retarding effect and workability increases. Additional air may also be entrained.

During this period the concrete must be kept moist in order to prevent premature drying out.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

# LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Gulf B.S.C. (c)

Tel: +973 177 38188  
Email: info@bh.sika.com  
Sika Kuwait Cons. Mat. & Paints Co WLL  
Tel: +965 22 282 296  
Email: sika.kuwait@kw.sika.com  
Web: gcc.sika.com

### Sika UAE LLC

Sika MB Construction Chemicals LLC  
Sika International Chemicals LLC  
Tel: +971 4 439 8200  
Email: info@ae.sika.com  
Web: gcc.sika.com

### Sika Saudi Arabia Limited

Sika Construction Chemicals for  
Manufacturing LLC  
Riyadh / Jeddah / Dammam / Rabigh  
Tel: +966 9200 22167  
Email: info@sa.sika.com  
Web: gcc.sika.com

### Sika LLC - Oman

Sika MB LLC  
Tel. +968 22 826 500  
Email: info@om.sika.com  
Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS  
Sika MB LLC  
Sika International Chemicals LLC  
Sika Gulf B.S.C. (c)  
ISO 9001, 14001 – SGS  
Sika Saudi Arabia Limited  
ISO 9001, 14001 – TÜV  
Sika MB Construction Chemicals LLC  
Sika Construction Chemicals  
for Manufacturing LLC  
ISO 9001 – LMS  
Sika MB LLC

All products are supplied under  
a management system certified  
to conform to the requirements  
of the quality, environmental  
and occupational health &  
safety standards ISO 9001, ISO  
14001 and ISO 45001.



### Product Data Sheet

Sika® Plastocrete® N AE  
December 2024, Version 02.01  
021303011000000756

