

# PRODUCT DATA SHEET

## Sarnafil® S 327-15 L

POLYMERIC MEMBRANE FOR MECHANICALLY FASTENED ROOF WATERPROOFING



### DESCRIPTION

Sarnafil® S 327-15 L (thickness 1.5 mm) is a polyester reinforced, multi-layer, synthetic roof waterproofing sheet based on premium-quality polyvinyl chloride (PVC) containing ultraviolet light stabilizers according to EN 13956.

Sarnafil® S 327-15 L is a hot air weldable roof membrane formulated for direct exposure. Suitable for use in hot and tropical climatic conditions.

### USES

Waterproofing membrane for:

- Mechanically fastened roofing systems

### CHARACTERISTICS / ADVANTAGES

- Proven performance over decades
- Resistant to permanent UV irradiation
- Resistant to permanent wind exposure
- Resistant to all common environmental influences
- Hot air welding without use of open flames
- High water vapour permeability
- Recyclable

### SUSTAINABILITY

- Conformity with LEED v4 MRc 2 (Option 1): Building Product Disclosure and Optimization – Environmental Product Declarations
- Conformity with LEED v4 MRc 3 (Option 2): Building Product Disclosure and Optimization - Sourcing of Raw Materials
- Conformity with LEED v4 MRc 4 (Option 2): Building Product Disclosure and Optimization - Material Ingredients
- Conformity with LEED v2009 MRc 4 (Option 2): Recycled Content

### APPROVALS / CERTIFICATES

Sarnafil® S 327-15 L is designed and manufactured to meet most international recognised standards.

- Polymeric sheets for roof waterproofing according to EN 13956, certified by notified body 1213-CPD-4920 and provided with the CE-mark.
- Reaction to fire according to EN 13501-1. Class E.
- External fire performance tested according to ENV 1187 and classified according to EN 13501-5: BROOF (t1).

## PRODUCT INFORMATION

|                            |   |                               |
|----------------------------|---|-------------------------------|
| <b>Packaging</b>           | Sarnafil® S 327-15 L standard rolls are wrapped individually in a blue PE-foil.   |                               |
|                            | Packing unit  | See price list                |
|                            | Roll length   | 20.00 m                       |
|                            | Roll width  | 2.00 m                        |
|                            | Roll weight   | 72.00 kg                      |
| <b>Appearance / Colour</b> | Surface   | Matt                          |
|                            | Colours   |                               |
|                            | Top surface   | Light grey (nearest RAL 7047) |
|                            | Bottom surface  | Dark grey                     |
|                            | Top surface of sheet in other special colours available on request, subject to minimum order quantities.  |                               |
| <b>Shelf life</b>          | 5 years from date of production in unopened, undamaged and original packaging.  |                               |
| <b>Storage conditions</b>  | Rolls must be stored between +5 °C and +30 °C in a horizontal position on pallet, protected from direct sunlight, rain and snow. Do not stack pallets of rolls or any other material during transport or storage. |                               |
| <b>Product Declaration</b> | EN 13956  |                               |
| <b>Visible Defects</b>     | Pass  | (EN 1850-2)                   |
| <b>Length</b>              | 20 m (- 0 % / + 5 %)  | (EN 1848-2)                   |
| <b>Width</b>               | 2 m (- 0.5 % / + 1 %)   | (EN 1848-2)                   |
| <b>Effective Thickness</b> | 1.5 mm (- 5 % / + 10 %)   | (EN 1849-2)                   |
| <b>Straightness</b>        | ≤ 30 mm   | (EN 1848-2)                   |
| <b>Flatness</b>            | ≤ 10 mm   | (EN 1848-2)                   |
| <b>Mass per unit area</b>  | 1.8 kg/m <sup>2</sup> (- 5 % / + 10 %)  | (EN 1849-2)                   |

## TECHNICAL INFORMATION

|   |                                 |                |              |
|---|---------------------------------|----------------|--------------|
| <b>Resistance to Impact</b>                                   | Hard substrate                  | ≥ 600 mm       | (EN 12691)   |
|   | Soft substrate                  | ≥ 900 mm       |              |
| <b>Hail Resistance</b>  | Rigid substrate                 | ≥ 22 m/s       | (EN 13583)   |
|   | Flexible substrate              | ≥ 30 m/s       |              |
| <b>Resistance to Static Load</b>                              | Soft substrate                  | ≥ 20 kg        | (EN 12730)   |
|   | Rigid substrate                 | ≥ 20 kg        |              |
| <b>Tensile Strength</b>                                       | Longitudinal (md) <sup>1)</sup> | ≥ 1100 N/50 mm | (EN 12311-2) |
|   | Transversal (cmd) <sup>2)</sup> | ≥ 1100 N/50 mm |              |
| 1) md = machine direction<br>2) cmd = cross machine direction |                                 |                |              |
| <b>Elongation</b>   | Longitudinal (md) <sup>1)</sup> | ≥ 12 %         | (EN 12311-2) |
|   | Transversal (cmd) <sup>2)</sup> | ≥ 12 %         |              |
| 1) md = machine direction<br>2) cmd = cross machine direction |                                 |                |              |
| <b>Dimensional Stability</b>                                  | Longitudinal (md) <sup>1)</sup> | ≤ 0.3 %        | (EN 1107-2)  |
|   | Transversal (cmd) <sup>2)</sup> | ≤ 0.2 %        |              |
| 1) md = machine direction<br>2) cmd = cross machine direction |                                 |                |              |

|  |                                 |   |                           |
|--|---------------------------------|---|---------------------------|
| <b>Tear Strength</b>                               | Longitudinal (md) <sup>1)</sup> | ≥ 200 N   | (EN 12310-2)              |
|  | Transversal (cmd) <sup>2)</sup> | ≥ 200 N   |                           |
|  |                                 | 1) md = machine direction<br>2) cmd = cross machine direction |                           |
| <b>Joint Peel Resistance</b>                       | No failure of the joint         |   | (EN 12316-2)              |
| <b>Joint Shear Resistance</b>                      | ≥ 800 N/50 mm                   |   | (EN 12317-2)              |
| <b>Foldability at Low Temperature</b>              | ≤ -25 °C                        |   | (EN 495-5)                |
| <b>External Fire Performance</b>                   | BROOF(t1) < 20°                 |   | (EN 1187)<br>(EN 13501-5) |
| <b>Reaction to Fire</b>                            | Class E                         | (EN ISO 11925-2, classification to EN 13501-1)                |                           |
| <b>Effect of Liquid Chemicals, Including Water</b> | On request                      |   | (EN 1847)                 |
| <b>Resistance to UV Exposure</b>                   | Pass (> 5000 h / grade 0)       |   | (EN 1297)                 |
| <b>Water Vapour Transmission</b>                   | μ = 15 000                      |   | (EN 1931)                 |
| <b>Watertightness</b>                              | Pass                            |   | (EN 1928)                 |

## SYSTEMS

|                         |   |
|-------------------------|---|
| <b>System Structure</b> | Wide range of accessories is available example prefabricated parts, roof drains, scuppers, walkway pads and decor profiles.<br>The following accessories shall be used: <ul style="list-style-type: none"> <li>▪ Sarnafil® G 410-15 Sheet for detailing</li> <li>▪ Sarnafil® Metal Sheet PVC</li> <li>▪ Sarnabar® / Sarnafast®</li> <li>▪ S-Welding Cord PVC</li> <li>▪ Sarnacol® 2170 (contact adhesive)</li> <li>▪ Sarna Seam Cleaner</li> <li>▪ Sarna Cleaner</li> </ul> |
| <b>Compatibility</b>    | Not compatible with direct contact to other plastics, example EPS, XPS, PUR, PIR or PF. Not resistant to tar, bitumen, oil and solvent containing materials.  |

## APPLICATION INFORMATION

|                                |                           |
|--------------------------------|---------------------------|
| <b>Ambient Air Temperature</b> | -20 °C min. / +60 °C max. |
| <b>Substrate Temperature</b>   | -30 °C min. / +60 °C max. |

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

The substrate surface must be uniform, smooth and free of any sharp protrusions or burrs, etc. Sarnafil® S 327-15 L must be separated from any incompatible substrates by an effective separation layer to prevent accelerated ageing. Prevent from direct contact with bitumen, tar, fat, oil, solvent containing material and direct contact to other plastic materials, example expanded polystyrene (EPS), extruded polystyrene (XPS), polyurethane (PUR), polyisocyanurate (PIR) or phenolic foam (PF) as this could adversely affect the product properties. The supporting layer must be compatible to the membrane, solvent resistant, clean, dry and free of grease and dust. Metal sheets must be degreased with Sarna Cleaner before adhesive is applied.

### APPLICATION

Installation works to be carried out only by Sika instructed contractors for roofing. Installation of some ancillary products, example contact adhesives / cleaners is limited to temperatures above +5 °C. Please observe information given by Product Data Sheets.

### APPLICATION METHOD / TOOLS

**Installation procedure:**  
According to the valid installation instructions for Sarnafil® S 327-15 L-types system for mechanically fastened roofing systems.

**Fixing Method, linear fastening (Sarnabar®):**

Unroll the Sarnafil® S 327-15 L membrane, overlap by 80 mm, weld immediately and fix to the substructure by means of Sarnabar®. The preferred type of fastening and the distance will be advised by Sika. The spacing of the fasteners is in accordance with the project specific calculation. The perimeter piece ends must be secured with the Sarnabar® Load Distribution Plate. For protection fasten a piece of Sarnafil® S 327-15 L under bar end and plate. Leave a 10 mm clearance between bar ends. Do not fasten in hole nearest bar end. Cover the bar ends with a piece of Sarnafil® S 327-15 L and weld. After installation the Sarnabar® must immediately be made watertight with a Sarnafil® S 327-15 L cover strip. At upstands and at all penetrations, the Sarnafil® S 327-15 L membrane must be secured with a Sarnabar®. The 4 mm diameter S-Welding Cord protects the Sarnafil® S 327-15 L roof covering against tearing and peeling off by wind uplift.

**Fixing Method, spot fastening (Sarnafast®):**

Sarnafil® S 327-15 L must always be installed at right angles to the deck direction. Sarnafil® S 327-15 L is fixed by means of the Sarnafast® fasteners and barbed washers/tubes along the marked line, 35 mm from the edge of the membrane. Sarnafil® S 327-15 L is overlapped by 120 mm. The spacing of the fasteners is in accordance with the project specific calculations. At upstands and at all penetrations, the Sarnafil® S 327-15 L membrane must be secured with a Sarnabar®. The 4 mm diameter S-Welding Cord protects the Sarnafil® S 327-15 L roof covering against tearing and peeling off by wind uplift.

**Welding Method:**

Overlap seams are welded by electric hot air welding equipment, such as manual hot air welding machines and pressure rollers or automatic hot air welding machines with controlled hot air temperature.

**Recommended type of equipment:**

Leister Triac for manual welding and Sarnamatic® 681 for automatic welding.

Welding parameters including temperature, machine speed, air flow, pressure and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic situation prior to welding. The effective width of welded overlaps by hot air must be minimum 20 mm.

The seams must be mechanically tested with screw driver to ensure the integrity / completion of the weld. Any imperfections must be rectified by hot air welding.

## IMPORTANT CONSIDERATIONS

**Geographical / Climate**

Permanent ambient temperature during use is limited to +50 °C.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

Fresh air ventilation must be ensured, when working (welding) in closed rooms.

**REGULATION (EC) NO 1907/2006 - REACH**

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w)

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait  
Tel: +973 177 38188  
sika.gulf@bh.sika.com  
gcc.sika.com

### SIKA SOUTHERN GULF

UAE / Oman / SIC  
Tel: +971 4 439 8200  
info@ae.sika.com  
gcc.sika.com

### SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman  
Tel: +966 11 217 6532  
info@sa.sika.com  
gcc.sika.com



ISO 9001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd,  
Sika Qatar LLC  
ISO 14001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd  
OHSAS: Sika UAE LLC,  
Sika Gulf B.S.C. (c)

All products are supplied  
under a management  
system certified to conform  
to the requirements of the  
quality, environmental and  
occupational health &  
safety standards ISO 9001,  
ISO 14001 and OHSAS  
18001.

### Product Data Sheet

Sarnafil® S 327-15 L

October 2017, Version 01.01

020905012000151001

SarnafilS327-15L-en-AE-(10-2017)-1-1.pdf

