

# PRODUCT DATA SHEET

## SikaFix<sup>®</sup>-210

### TOUGH POLYURETHANE RESIN FOR INJECTION SEALING AND GROUND STABILIZATION IN TUNNELLING AND MINING

#### DESCRIPTION

SikaFix<sup>®</sup>-210 is a fast-reacting polyurethane based resin with short gel times and high final strength. Suitable for use in hot and tropical climatic conditions.

#### USES

SikaFix<sup>®</sup>-210 may only be used by experienced professionals. SikaFix<sup>®</sup>-210 is used for permanent and durable injection sealing and ground stabilization of the headings in tunnel construction and mining. SikaFix<sup>®</sup>-210 is also used for stabilization of other loose rock faces, voids and unstable surfaces. It is suitable for injection in dry, damp and wet conditions, including sealing around water-bearing zones in rock, masonry dams and tunnel walls etc. SikaFix<sup>®</sup>-210 can be accelerated with SikaFix<sup>®</sup> AC-21 for waterstopping applications during construction works that is for unexpected water inrush.

#### CHARACTERISTICS / ADVANTAGES

- High final strength
- Foaming on contact with water (approximately 3 times volume increase)
- Very fast curing
- Modular system with SikaFix AC-21
- Easy application due to volume ratio 1 : 1
- High penetration ability
- Low initial viscosity
- CFC- and halogen-free
- Total solid\*

\*According to testing method of German Institute "Deutsche Bauchemie e.V."

#### APPROVALS / CERTIFICATES

German KTW drinking water certificate

#### PRODUCT INFORMATION

<b>Composition</b>	2-component Polyurethane resin, solvent and CFC-free	
<b>Packaging</b>	Part A	20.20 kg (~20 L)
	Part B	24.80 kg (~20 L)
<b>Colour</b>	Part A	Slightly yellow
	Part B	Black brown
<b>Shelf life</b>	12 months shelf life from date of production if stored properly in undamaged, unopened, original sealed packaging.	
<b>Storage conditions</b>	Dry storage at temperatures from +5 °C up to +35 °C. Protect from direct sunlight and humidity.	

<b>Density</b>	At 23 °C		(ISO 2811)
	<b>Part A</b> ~1.01 kg/l	<b>Part B</b> ~1.23 kg/l	
<b>Flash Point</b>	<b>Part A</b> > 140 °C	<b>Part B</b> > 250 °C	(DIN 53213)
	At 23 °C		(ISO 3219)
<b>Viscosity</b>	<b>Part A</b> ~300 mPa·s	<b>Part B</b> ~260 mPa·s	

## TECHNICAL INFORMATION

<b>Shore A Hardness</b>	~80 (3 d)	(EN 868)
<b>Compressive Strength</b>	~80 N/mm <sup>2</sup>	(ISO 604)
<b>Tensile Strength in Flexure</b>	~70 N/mm <sup>2</sup> (3 d / 23 °C)	(ISO 178)

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	1 : 1 parts by volume (refer to Application Instructions)	
<b>Ambient Air Temperature</b>	+5 °C min. / +35 °C max.	
<b>Substrate Temperature</b>	+5 °C min. / +35 °C max.	
<b>Pot Life</b>	~45 s (23 °C)	(PM 10081-11)

## APPLICATION INSTRUCTIONS

### MIXING

- SikaFix®-210 is supplied in containers pre-batched according to the required mixing ratio of 1 : 1 parts by volume
- Both components are mixed together on injection through a 2 C-injection pump, drawing each component directly from the original containers. The static mixer must be suitable to ensure that the mixture of comp. A and B forms a stable emulsion.
- Use injection ports, lances or packers with a sufficiently large diameter and flow.

### APPLICATION METHOD / TOOLS

2 component injection pumps suitable for PU-Injection. For detailed information, please refer to the corresponding method statement.

### CLEANING OF EQUIPMENT

Clean all tools and application equipment according to the Product Data Sheet for the Sika® Injection Cleaning System.

Alternatively Sika® Colma Cleaner can be used to remove any polyurethane residue immediately after use. Do not leave Sika® Colma Cleaner in the injection pump. Hardened / cured material can only be removed mechanically.

### IMPORTANT CONSIDERATIONS

Only for application by trained and experienced professionals.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait  
Tel: +973 177 38188  
sika.gulf@bh.sika.com  
gcc.sika.com

### SIKA SOUTHERN GULF

UAE / Oman / SIC  
Tel: +971 4 439 8200  
info@ae.sika.com  
gcc.sika.com

### SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman  
Tel: +966 11 217 6532  
info@sa.sika.com  
gcc.sika.com



ISO 9001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd,  
Sika Qatar LLC  
ISO 14001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd  
OHSAS: Sika UAE LLC,  
Sika Gulf B.S.C. (c)

All products are supplied  
under a management  
system certified to conform  
to the requirements of the  
quality, environmental and  
occupational health &  
safety standards ISO 9001,  
ISO 14001 and OHSAS  
18001.

### Product Data Sheet

SikaFix®-210

November 2016, Version 01.01  
020707010020000009

SikaFix-210-en-AE-(11-2016)-1-1.pdf

