

# PRODUCT DATA SHEET

## Sika® Bonding Primer

### TWO-COMPONENT WATERBASED EPOXY PRIMER

#### DESCRIPTION

Sika® Bonding Primer is a two-component, water-based epoxy primer to consolidate substrates and enhance the adhesion of SikaRoof MTC®, Sikalastic®, Sikafloor® and Sikagard® products. Suitable for use in hot and tropical climatic conditions.

#### USES

Versatile primer for use with:

- SikaRoof® MTC
- Sikalastic® roofing systems
- Sikafloor® balcony waterproofing systems
- Sikagard® hygiene coatings
- Suitable for use on concrete, masonry, tiles, insulation foams, bituminous surfaces, plaster, cementitious renders, screeds and mortars.

#### CHARACTERISTICS / ADVANTAGES

- Fast curing - overcoat possible after 1 - 2 hours
- Long pot life - up to 12 hours
- Low odour - water-based product
- Consolidates dusty or friable surfaces
- Uniforms the absorbency of the substrate
- Enhances adhesion to a broad range of substrates
- Easy application by brush or roller

#### PRODUCT INFORMATION

<b>Composition</b>	Epoxy, waterborne and polyamine curative	
<b>Packaging</b>	1.0 L (~1.03 kg) unit	0.8 L component A 0.2 L component B
	5.0 L (~5.16 kg) unit	4 L component A 1 L component B
	15.0 L (~15.54 kg) unit	12 L component A 3 L component B
<b>Appearance / Colour</b>	Milky green liquid resin	
<b>Shelf life</b>	24 months from date of production	
<b>Storage conditions</b>	<p>The product must be stored properly in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +25 °C.</p> <p>Higher storage temperatures may reduce shelf life of product. Reference shall also be made to the storage recommendations within the safety data sheet.</p>	

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	Component A : Component B = 4 : 1 (by volume)																								
<b>Consumption</b>	Apply in one to two coats, with a consumption of 0.10 kg/m <sup>2</sup> approximately per coat depending upon surface roughness and absorption. <b>Note:</b> For metal substrates apply 1 x Sikalastic® Metal Primer (0.20 kg/m <sup>2</sup> approximately) instead of Sika® Bonding Primer (please refer to Sikalastic® Metal Primer Product Data Sheet for further information). These figures are theoretical and do not include for any additional material required due to surface porosity, surface profile, variations in level and wastage.																								
<b>Ambient Air Temperature</b>	+5 °C min. / +40 °C max.																								
<b>Relative Air Humidity</b>	80 % r.h. max.																								
<b>Dew Point</b>	Beware of condensation. The substrate and uncured coating must be ≥ 3 °C above dew point.																								
<b>Substrate Temperature</b>	+5 °C min. / +40 °C max.																								
<b>Substrate Moisture Content</b>	Visible damp free (maximum 18 % wood moisture equivalent) ≤ 6 % pbw moisture content Test method: Sika®-Tramex meter ≤ 4 % CM - measurement or Oven-dry-method No rising moisture according to ASTM (Polyethylene-sheet)																								
<b>Waiting Time / Overcoating</b>	<p>Before applying any recommended SikaRoof® MTC, Sikalastic® and Sika-floor® products on Sika® Bonding Primer, allow:</p> <table border="1"> <thead> <tr> <th>Substrate temperature</th> <th>Minimum waiting time</th> <th>Maximum waiting time</th> </tr> </thead> <tbody> <tr> <td>+10 °C</td> <td>~4 h</td> <td>7 d</td> </tr> <tr> <td>+20 °C</td> <td>~2.5 – 3.5 h</td> <td>7 d</td> </tr> <tr> <td>+30 °C</td> <td>~1 h</td> <td>7 d</td> </tr> </tbody> </table> <p>Before applying Sikagard® products on Sika® Bonding Primer allow:</p> <table border="1"> <thead> <tr> <th>Substrate temperature</th> <th>Minimum waiting time</th> <th>Maximum waiting time</th> </tr> </thead> <tbody> <tr> <td>+10 °C</td> <td>~24 h</td> <td>7 d</td> </tr> <tr> <td>+20 °C</td> <td>~8 h</td> <td>7 d</td> </tr> <tr> <td>+30 °C</td> <td>~6 h</td> <td>7 d</td> </tr> </tbody> </table> <p><b>Note:</b> Apply an additional coat if more than 24 hours pass before coating. Times are approximate and will be affected by changing ambient conditions particularly temperature and relative humidity.</p>	Substrate temperature	Minimum waiting time	Maximum waiting time	+10 °C	~4 h	7 d	+20 °C	~2.5 – 3.5 h	7 d	+30 °C	~1 h	7 d	Substrate temperature	Minimum waiting time	Maximum waiting time	+10 °C	~24 h	7 d	+20 °C	~8 h	7 d	+30 °C	~6 h	7 d
Substrate temperature	Minimum waiting time	Maximum waiting time																							
+10 °C	~4 h	7 d																							
+20 °C	~2.5 – 3.5 h	7 d																							
+30 °C	~1 h	7 d																							
Substrate temperature	Minimum waiting time	Maximum waiting time																							
+10 °C	~24 h	7 d																							
+20 °C	~8 h	7 d																							
+30 °C	~6 h	7 d																							

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY

The surface must be sound, of sufficient strength, clean, dry and free of dirt, oil, grease and other contamination. The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm<sup>2</sup>) with a minimum pull off strength of 1.5 N/mm<sup>2</sup>.

### SUBSTRATE PREPARATION

All surfaces to be coated should be thoroughly cleaned by conventional means.  
Inspect the substrate.  
Spalling, flaking or damaged areas should be repaired using compatible materials to match surroundings or replaced as necessary.  
If in doubt apply a test area first.  
Tiles have to be prepared mechanically, glazing has to be removed.  
Grinding may be necessary to level the surface.  
For detailed information regarding substrate quality / preparation and primer chart please refer to Method Statement.

## APPLICATION

Prepare Sika® Bonding Primer by adding component B into component A container, mix with an electric drill until a homogeneous light green colour is achieved and the product is free of streaks. The 1 L packaging can be mixed by spatula or flat stick.

Sika® Bonding Primer can be applied by short-piled roller, brush or airless spray.

Allow primer to dry sufficiently (see table waiting time / overcoating) before overcoating.

## CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened and/or cured material can only be removed mechanically.

## IMPORTANT CONSIDERATIONS

- Do not apply Sika® Bonding Primer on substrates with rising moisture.
- Sika® Bonding Primer is not recommended for use as a direct primer for Sikagard® 307, Sikagard® 317 and Sikalastic®-641
- Always ensure good ventilation when using Sika® Bonding Primer in a confined space, to ensure drying and full curing.
- If the primer is damaged by rain, a chalky surface will result and the surface must be re-primed.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking (for further information please contact Sika Technical Department).
- If heating is required do not use gas, oil, paraffin or other fossil fuel heaters, these produce large quantities of both CO<sub>2</sub> and H<sub>2</sub>O water vapour, which may adversely affect the finish. For heating use only electric powered warm air blower systems.
- New concrete should be allowed to cure/hydrate for a minimum of 10 days, preferably 28 days.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait  
Tel: +973 177 38188  
sika.gulf@bh.sika.com  
gcc.sika.com

### SIKA SOUTHERN GULF

UAE / Oman / SIC  
Tel: +971 4 439 8200  
info@ae.sika.com  
gcc.sika.com

### SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman  
Tel: +966 11 217 6532  
info@sa.sika.com  
gcc.sika.com



ISO 9001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd,  
Sika Qatar LLC  
ISO 14001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd  
OHSAS: Sika UAE LLC,  
Sika Gulf B.S.C. (c)

All products are supplied  
under a management  
system certified to conform  
to the requirements of the  
quality, environmental and  
occupational health &  
safety standards ISO 9001,  
ISO 14001 and OHSAS  
18001.

SikaBondingPrimer-en-AE-(08-2017)-2-1.pdf

Product Data Sheet  
Sika® Bonding Primer  
August 2017, Version 02.01  
02091595100000009

