

PRODUCT DATA SHEET

Sikament® RB 3243

(formerly MRheobuild 3243)

WATER REDUCING SUPERPLASTICISING ADMIXTURE FOR THE PRODUCTION OF WORKABLE CONCRETE

DESCRIPTION

Sikament® RB 3243 is a liquid admixture for concrete based on sulphonated naphthalene. The product may be used to effect substantial water reductions or to produce workable concrete with normal setting times. Suitable for use in hot and tropical climatic conditions.

USES

- Production of workable ready-mix concrete.
- In complicated formwork or with congested reinforcement.

FEATURES

- Its plasticising action reduces or eliminates the need for compaction.
- Increased compressive, tensile and flexural strength can be achieved as a benefit of its water reducing properties.

CERTIFICATES AND TEST REPORTS

Sikament® RB 3243 follows the requirements of ASTM C494; Type A, F & F, And BS EN 934-2

PRODUCT INFORMATION

Composition	Sulphonated naphthalene
Packaging	210 L drum, 1000 L flowbin or bulk supply in tanker
Appearance and colour	Dark brown/black liquid
Shelf life	12 months from date of production when stored properly
Storage conditions	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5°C and +45°C. Protect from direct sunlight. Mix well before use.
Density	~1.18 kg/l (+25°C)
Total chloride ion content	Nil (BS EN 934-2)

TECHNICAL INFORMATION

Concreting guidance

The standard rules of good concreting practice for production and placing must be observed when using Sikament® RB 3243 in concrete. Refer to relevant standards. Fresh concrete must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Use Sika® Antisol® products as a curing agent or apply wet hessian.

APPLICATION INFORMATION

Recommended dosage	Sikament® RB 3243 is normally dispensed at a rate of 0.6 – 2.3 litres per 100 kg of binder. Other dosages may be used, depending on the mix design, raw materials, climatic conditions and concrete requirements. Trial mixes must be performed to establish the exact dosage rate required.
Compatibility	<p>Sikament® RB 3243 is suitable for mixes containing all types of cement and supplementary cementitious materials such as: Microsilica (Silica Fume), Fly Ash (PFA), GGBS (ground granulated blast furnace slag) and the following Sika products:</p> <ul style="list-style-type: none">▪ SikaPump®▪ Sika®FerroGard®▪ SikaFume®▪ SikaFiber®▪ Sika® Aer▪ Sika®Stabilizer▪ SikaControl® <p>We recommend to perform trial mixes to establish the required performance when combining Sikament® RB 3243 with the above products or other admixtures. Sikament® RB 3243 should not be premixed with any other admixtures. If other admixtures are to be used, those should be dispensed separately. Please consult our Sika Technical Department for further assistance.</p>
Dispensing	Sikament® RB 3243 is a ready-to-use admixture to be added to the concrete as a separate component. Optimal result is obtained if Sikament® RB 3243 is poured into the concrete mix right after the addition of the first 70 % of the mixing water, i.e. when all solids are wetted. Avoid adding the admixture to the dry aggregates. Alternatively, when using Sikament® RB 3243 to produce flowing concrete at site using ready mix trucks, it can be added to the concrete via the feed hopper at the rear of the truck. Mix before discharge for 5 minutes at 10 rpm to produce a fully homogenous mix.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Before pouring, suitability tests on the fresh concrete must be carried out. With high workability mixes take special care that all formwork is properly installed and secured. If frozen and/or if precipitation has occurred, it may only be used after thawing slowly at room temperature and intensive mixing. When using Sikament® RB 3243 a suitable concrete mix must be designed for the local material sources and trial mixes performed to verify suitability. When accidental overdosing occurs the set retarding effect and workability increases along with bleeding. Additional air may also be entrained. During this period the concrete must be kept moist in order to prevent premature drying out.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188

Email: info@bh.sika.com

Sika Kuwait Cons. Mat. & Paints Co WLL

Tel: +965 22 282 296

Email: sika.kuwait@kw.sika.com

Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC

Sika International Chemicals LLC

Tel: +971 4 439 8200

Email: info@ae.sika.com

Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for

Manufacturing LLC

Riyadh / Jeddah / Dammam / Rabigh

Tel: +966 9200 22167

Email: info@sa.sika.com

Web: gcc.sika.com

Sika LLC - Oman

Sika MB LLC

Tel. +968 22 826 500

Email: info@om.sika.com

Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
Sika MB LLC
Sika International Chemicals LLC
Sika Gulf B.S.C. (c)
ISO 9001, 14001 – SGS
Sika Saudi Arabia Limited
ISO 9001, 14001 – TÜV
Sika MB Construction Chemicals LLC
Sika Construction Chemicals for Manufacturing LLC
ISO 9001 – LMS
Sika MB LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

Sikament® RB 3243

December 2024, Version 01.01

02130200000002097