

**BUILDING TRUST** 

# PRODUCT DATA SHEET Sika<sup>®</sup> Sigunit<sup>®</sup>-5130 AFL

(formerly MRoc SA 430)

Liquid sprayed concrete accelerator for wet-mix spraying

# DESCRIPTION

Sika<sup>®</sup> Sigunit<sup>®</sup>-5130 AFL is an accelerator for the wetmix spraying process but can also be used in the drymix spraying process. It is a liquid additive whose dosage can be varied to the desired setting and hardening times.

Suitable for use in hot and tropical climatic conditions.

# USES

Sika<sup>®</sup> Sigunit<sup>®</sup>-5130 AFL is suitable for all applications where high early strength and very thick sprayed concrete layers are required.

- For temporary ground support in tunneling and mining
- Slope stabilization

# **PRODUCT INFORMATION**

# **FEATURES**

- Fast setting and higher early strength
- Rapid word progress
- Low viscosity
- Easy to mix into the concrete (even at low temperat-
- ures)

  Low consumption

Composition	Blend of special inorganic materials	
Packaging	Drum, 1,000 L flowbin or in bulk	
Appearance and colour	Clear to whitish liquid	
Shelf life	12 months from date of production if stored properly	
Storage conditions	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5 °C and +50 °C.	
Density	~1.36 kg/l (+25 °C)	
Viscosity	30–70 mPa.s (cps) (+20 °C)	
Total chloride ion content	Nil	(EN 480-10)

 Product Data Sheet

 Sika® Sigunit®-5130 AFL

 November 2024, Version 02.02

 021401011000000293

TECHNICAL INFORMATION		
Concrete mix design	When Sika <sup>®</sup> Sigunit <sup>®</sup> -5130 AFL is used for wet mix spraying, it is advised to have the w/c ratio < 0.45. When targeting extremely high early strength, it is preferable to have w/c ratio ≤ 0.40. The lower w/c ratios provide faster setting, higher early strength, better durability and lower accelerator dosage; moreover, it allow for thicker lay- ers to be applied overhead.	
APPLICATION INFORM	ATION	
Recommended dosage	3–8 % by weight of binder Dosages by weight of binder depend on the mix design, raw materials, cli- matic conditions and concrete requirements. Trial mixes must be performed to establish the exact dosage rate required.	
Dispensing	Sika <sup>®</sup> Sigunit <sup>®</sup> -5130 AFL is added at the nozzle. It is essential to have a constant and accurate dosage of accelerator into the concrete stream. To ensure quality sprayed concrete, follow the pump selection guidelines given below:	
	Works very well with: • Mono pumps (stator & rotor pumps) • Peristaltic pumps	
	<ul> <li>Should not be used with:</li> <li>Piston pumps</li> <li>All pumps with ball and seat valves</li> <li>Pressure tanks</li> <li>Gear pumps</li> <li>Do not use a filter on the suction hose as this causes obstructions. Preferably draw the material off the bottom of the drum/container.</li> </ul>	
Compatibility	Sika <sup>®</sup> Sigunit <sup>®</sup> SA 430 is compatible with the following Sika products: SikaPump <sup>®</sup> , Sika <sup>®</sup> ViscoCrete <sup>®</sup> , Sikament <sup>®</sup> , SikaFume <sup>®</sup> , SikaFiber <sup>®</sup> , SikaTard <sup>®</sup> We recommend to perform trial mixes to establish the required perform- ance when combining Sika <sup>®</sup> Sigunit <sup>®</sup> -5130 AFL with the above products or other admixtures. Please consult our Sika Technical Department.	

# **BASIS OF PRODUCT DATA**

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

# **IMPORTANT CONSIDERATIONS**

- Overdosing (> 8% by weight of binder) may result in decreased final strength.
- The effect of the accelerator depends on the content, age and type of cement as well as the shotcrete temperature. It is recommended to use only fresh cement. With some cements the setting characteristics can be slower. We recommend the use of Portland cements, which normally give faster setting than blended or sulphate resistant cement types.
- Sika<sup>®</sup> Sigunit<sup>®</sup>-5130 AFL also works well with composite cements types (blended cements, fly ash/slag). In all cases, it is strongly recommended to carry out preliminary tests to check setting and the 24 h strength of the cements planned for use in a project.
- The w/c ratio of the base shotcrete mix in the wet spraying process, and the quantity of gauging water in the dry spraying process are also parameters influencing the acceleration effect of Sika® Sigunit®-5130 AFL.

# ECOLOGY, HEALTH AND SAFETY

**BUILDING TRUST** 

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

 Product Data Sheet

 Sika® Sigunit®-5130 AFL

 November 2024, Version 02.02

 02140101100000293



# **APPLICATION INSTRUCTIONS**

#### SUBSTRATE PREPARATION

The substrate must be clean and free from loose particles and preferably damp.

#### CLEANING OF EQUIPMENT

After the use of Sika<sup>®</sup> Sigunit<sup>®</sup>-5130 AFL, the dosing pump and other parts of the system must be thoroughly cleaned with plenty of water. Failure to do so provokes blockages in the dosing system when next used.

# **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Sika Gulf B.S.C. (c)

Tel: +973 177 38188 Email: info@bh.sika.com Sika Kuwait Cons. Mat. & Paints Co WLL Tel: +965 22 282 296 Email: sika.kuwait@kw.sika.com Web: gcc.sika.com



#### Product Data Sheet Sika<sup>®</sup> Sigunit<sup>®</sup>-5130 AFL November 2024, Version 02.02 021401011000000293

## Sika UAE LLC

Sika MB Construction Chemicals LLC Sika International Chemicals LLC Tel: +971 4 439 8200 Email: info@ae.sika.com Web: gcc.sika.com



#### Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC Riyadh / Jeddah / Dammam / Rabigh Tel: +966 12 692 7079 Email: info@sa.sika.com Web: gcc.sika.com

#### Sika LLC - Oman

Master Builders Solutions LLC (part of Sika) Tel. +968 22 826 500 Email: info@om.sika.com Web: gcc.sika.com

SikaSigunit-5130AFL-en-AE-(11-2024)-2-2.pdf



### BUILDING TRUST