

PRODUCT DATA SHEET

Sikament® RB 561 M

(formerly MRheobuild 561M)

High range water-reducing and slump retaining concrete admixture

DESCRIPTION

Sikament® RB 561 M is a highly effective dual action liquid superplasticiser that imparts excellent slump retention for prolonged periods.

Suitable for use in hot and tropical climatic conditions.

USES

Sikament® RB 561 M can be used as a superplasticizer for the production of free flowing concrete for:

- Slabs
- Foundations
- Walls
- Columns
- Piers
- Piles
- Slender components with dense reinforcement

FEATURES

Sikament® RB 561 M provides the following properties:

As a Superplasticiser:

- Workability is greatly improved
- Concrete is placed easily
- Especially suitable for slender components with densely packed reinforcement
- Concrete requires less vibrating
- Improved cohesion of the concrete mix significantly reduces the risk of segregation and allows greater time for placement

As a Water Reducer:

- Very good water reduction capability
- Final strength improvement

CERTIFICATES AND TEST REPORTS

Sikament® RB 561 M follows the requirements of ASTM C494; Type G and EN 934-2

TECHNICAL INFORMATION

Concreting guidance The standard rules of good concreting practice for production and placing must be observed when using Sikament® RB 561 M in concrete. Refer to relevant standards. Fresh concrete must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Use Sika® Antisol® products as a curing agent or apply wet hessian.

Product Data Sheet
Sikament® RB 561 M
November 2024, Version 02.01
021302011000004073

PRODUCT INFORMATION

Composition	Sulphonated napthalene	
Packaging	1000 L flowbin or bulk supply in tanker	
Shelf life	12 months from date of production if stored properly	
Storage conditions	Store in undamaged, unopened, original sealed packaging in dry condit at temperatures between +5°C and +50°C. Mix well before using.	tions
Appearance and colour	Dark brown liquid	
Density	~1.22 kg/l (+25°C)	
Total chloride ion content	Nil (EN 9	34-2)

APPLICATION INFORMATION

Recommended dosage	0.8 - 2.0 % by weight of binder Other dosages by weight of binder can be used depending on the mix design, raw materials, climatic conditions and concrete requirements. Trial mixes must be performed to establish the exact dosage rate required.
Dispensing	Sikament® RB 561 M is a ready-to-use admixture to be added to the concrete as a separate component. Optimal result is obtained if Sikament® RB 561 M is poured into the concrete mix right after the addition of the first 80% of the mixing water, i.e. when all solids are wetted. Avoid adding the admixture to the dry aggregates.
Compatibility	Sikament® RB 561 M is suitable for mixes containing all types of cement and supplementary cementitious materials such as: Microsilica (Silica Fume), Fly Ash (PFA), GGBS (Ground Granulated Blast Furnace Slag) and the following Sika® products: SikaPump®, Sika®FerroGard®, SikaFume®, SikaFiber®, Sika® Aer, Sika® Stabilizer, SikaControl®. We recommend to perform trial mixes to establish the required performance when combining Sikament® RB 561 M with the above products or other admixtures. Please consult our Sika Technical Department.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Before pouring, suitability tests on the fresh concrete must be carried out. With high workability mixes take special care that all formwork is properly installed and secured.

If frozen and/or if precipitation has occurred, it may only be used after thawing slowly at room temperature and intensive mixing. When using Sikament® RB 561 M a suitable concrete mix must be designed for the local material sources and trial mixes performed to verify suitability.

When accidental overdosing occurs, the set retarding effect and workability increases. Additional air may also be entrained. During this period the concrete must be kept moist in order to prevent premature drying out.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

Product Data Sheet Sikament® RB 561 M November 2024, Version 02.01 021302011000004073



LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

SGS

ISO 9601, 16021, 95901 – 965:

*Shis LUE LUC
- Shis Inference Shis Commendational Chemicals LUC
- Shis Cort Shis Co.
ISO 9601, 16001 – 956:

*Shis Soulf Anabla United
ISO 9601, 16001 – TÜV:
- Shis Count Anabla Limited
ISO 9601, 16001 – TÜV:
- Shis MC Construction Chemicals LUC
- Shis Construction Chemicals LUC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Sika UAE LLC

Sika MB Construction Chemicals LLC Sika International Chemicals LLC Tel: +971 4 439 8200 Email: info@ae.sika.com Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC Riyadh / Jeddah / Dammam / Rabigh Tel: +966 12 692 7079 Email: info@sa.sika.com Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC (part of Sika) Tel. +968 22 826 500 Email: info@om.sika.com Web: gcc.sika.com

SikamentRB561M-en-AE-(11-2024)-2-1.pdf

