

PRODUCT DATA SHEET

Sikagard[®]-1812

(formerly MProtect 1812)

AMINE-CURED, PITCH FREE EPOXY

DESCRIPTION

Sikagard[®]-1812 is a two component, solvent free, highly chemical resistant, pitch free epoxy coating. Suitable for use in hot and tropical climatic conditions.

USES

Sikagard[®]-1812 is used to provide a heavy duty protective, waterresistant and flexible coating. Widely used in the sewerage and waste water industry as well as other aggressive immersion conditions on cementitious and metal substrates. Uses include the lining of tanks, pipes and ducting, coating of concrete, asbestos cement, pipes and nonferrous metals.

Sikagard[®]-1812 is particularly suitable for use in sewerage work applications and in offshore or marine environments.

Sikagard[®]-1812 may only be used by experienced professionals.

FEATURES

- Excellent overall chemical resistance
- Excellent abrasion resistance and flexibility
- VOC compliant to EN norms
- High build coating
- Easy application: brush, roller, spray
- Economical
- Seamless finish
- Eco-friendly coating
- Excellent corrosion protection
- Available in two colours to differentiate system build-up
- Smooth and glossy finish

PRODUCT INFORMATION

Packaging	Supplied in 27 kg (18 L) units
Shelf life	12 months from date of production
Storage conditions	Store in a dry area in original sealed packaging at temperatures between +5°C and +30°C. Protect from direct sunlight, heat and moisture.
Colour	Available in the following standard colours: Black, Concrete Grey, Light Grey and White
Appearance	Thixotropic resin
Density	~1.5 kg/l (mixed, at 23°C) (ASTM D1475)
Solid content by volume	~100 %
Volatile organic compound (VOC) content	~20 g/l

TECHNICAL INFORMATION

Abrasion resistance	< 50 mg (CS17 wheel / 1000g / 1000 cycle) (7d)	(ASTM D4060)						
Tensile strength	~23 N/mm ² (7d)	(ASTM D638)						
Tensile adhesion strength	~3 N/mm ² (or concrete failure) (7d) Dry Heat Aging Test: ≥ 1.5 N/mm ² (at 160°C continuous for 30 days, ~300 µm DFT)	(ASTM D4541)						
Temperature resistance	<table border="1"> <thead> <tr> <th>Exposure ¹</th> <th>Maximum Temperature</th> </tr> </thead> <tbody> <tr> <td>Dry heat</td> <td>+160°C ²</td> </tr> <tr> <td>Water Immersion</td> <td>+60°C</td> </tr> </tbody> </table>	Exposure ¹	Maximum Temperature	Dry heat	+160°C ²	Water Immersion	+60°C	
Exposure ¹	Maximum Temperature							
Dry heat	+160°C ²							
Water Immersion	+60°C							
	¹ No simultaneous chemical and mechanical exposure ² A loss of gloss and discolouration may be observed above +90°C.							
Water penetration under pressure	Nil	(BS EN 12390, Part 8: 2000)						
Chemical resistance	Resistant to many chemicals. Contact Sika Technical Department for further information.							

APPLICATION INFORMATION

Consumption

Exposure Conditions:

Moderate	Total DFT	200-300 µm
Primer	Sikagard® P 659	150-300 g/m ²
Skim Coat	Sikadur® ADH 2200	As required
Top Coat	Sikagard®-1812	180-255 g/m ²

Severe	Total DFT	325-500 µm
Primer	Sikagard® P 659	150-300 g/m ²
Skim Coat	Sikadur® ADH 2200	As required
Body Coat	Sikagard®-1812	180-255 g/m ²
Top Coat	Sikagard®-1812	180-255 g/m ²

Immersion	Total DFT	450-650 µm
Primer	Sikagard® P 659	150-300 g/m ²
Skim Coat	Sikadur® ADH 2200	As required
Body Coat 1	Sikagard®-1812	180-240 g/m ²
Body Coat 2	Sikagard®-1812	180-240 g/m ²
Top Coat	Sikagard®-1812	180-255 g/m ²

Abrasive	Total DFT	900-1200 µm
Primer	Sikagard® P 659	150-300 g/m ²
Skim Coat	Sikadur® ADH 2200	As required
Body Coat 1	Sikagard®-1812	250-312 g/m ²
Body Coat 2	Sikagard®-1812	250-312 g/m ²
Body Coat 3	Sikagard®-1812	250-312 g/m ²
Body Coat 4	Sikagard®-1812	250-312 g/m ²
Top Coat	Sikagard®-1812	180-250 g/m ²

Note: These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.

Pot Life	25°C ~70 min	40°C ~45 min	(ASTM D2471)
Tack free time	25°C ~4 h	40°C ~1 h and 40 min	(ASTM C679)

BASIS OF PRODUCT DATA

- All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
- Internal Reference - Version: MBS_CC-UAE/Pr_1812_11_09/v6/02_21

IMPORTANT CONSIDERATIONS

- Immersion temperature resistance is dependant upon exposure. Please consult Sika Technical Service for specific information.
- Do not use in immersed areas where water temperature is over +60°C.
- Epoxies lose gloss, discolour and will chalk in direct sunlight exposure.
- No additions or omissions are required and on no account should attempts be made to split packs.
- Unsuitable in situations where foodstuff or potable water will be in contact with the coating.
- Ventilation: When used as a tank lining or in enclosed areas, air circulation must be used during and after application, until the applied product is fully cured. In addition to ensuring proper ventilation, appropriate respirators must be used by all application personnel. Treat splashes to eyes and skin immediately. If accidentally ingested, seek immediate medical attention. Keep away from children and animals. Reseal containers after use.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

Surfaces must be clean and dry. Use suitable methods to remove dirt, dust, oil and all other forms of contamination that could interfere with the adhesion of the coating.

Concrete

Concrete should be sound and sufficiently dry to accept Sikagard®-1812. Mechanically surface profiling is the method of surface preparation. Mechanically profile the surface to CSP3 as described by the International Concrete Repair Institute. Voids and pinholes must be repaired.

APPLICATION

Sikagard®-1812 may be applied by airless spray, brush or roller. Please refer to our latest Method Statement for detailed application instructions.

CLEANING OF EQUIPMENT

Use a suitable thinner (Xylene / MEK / Acetone) in case of spillage, absorb and dispose of in accordance with local applicable regulations.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188

Email: info@bh.sika.com

Sika Kuwait Cons. Mat. & Paints Co WLL

Tel: +965 22 282 296

Email: sika.kuwait@kw.sika.com

Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC

Sika International Chemicals LLC

Tel: +971 4 439 8200

Email: info@ae.sika.com

Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for

Manufacturing LLC

Riyadh / Jeddah / Dammam / Rabigh

Tel: +966 12 692 7079

Email: info@sa.sika.com

Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC

(part of Sika)

Tel. +968 22 826 500

Email: info@om.sika.com

Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
 - Sika UAE LLC
 - Sika International Chemicals LLC
 - Sika Gulf B.S.C. (c)
 - Sika MB Construction Chemicals LLC
 - Sika Saudi Arabia Limited
 - Sika MB Construction Chemicals for Manufacturing LLC
 - Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Sikagard-1812-en-AE-(09-2024)-2-1.pdf

Product Data Sheet

Sikagard®-1812

September 2024, Version 02.01

02030300000002040