

PRODUCT DATA SHEET

Sikafloor® P 651

(formerly MTop P 651)

THREE COMPONENT TOTAL SOLIDS HIGH-BUILD EPOXY SURFACE SEALER AND PRIMER

DESCRIPTION

Sikafloor® P 651 is a high grade, high-build, three component epoxy primer and surface sealer. Sikafloor® P 651 is used as a sealer or scratch coat with, and without, the addition of guartz sand.

USES

Sikafloor® P 651 is suitable for priming and sealing of concrete surfaces.

Sikafloor® P 651 may be mixed with sand to the desired consistency to repair patches or form covings. In either case the mixed mortar must be applied to a surface previously coated with Sikafloor® P 651 resin and whilst still tacky.

FEATURES

- High build
- Total solids
- Easy application
- Medium viscosity
- Seals very porous substrate
- Short waiting times, faster drying
- Good intercoat adhesion
- Excellent bond strength

PRODUCT INFORMATION

Composition	Three component epoxy resin with selected fillers	
Packaging	25.4 kg units (Part A+B+C)	
Shelf life	12 months from date of production	
Storage conditions	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5°C and +30°C. Protect from direct sunlight, heat and moisture. In tropical climates the product must be stored in an air-conditioned environment.	
Appearance and colour	Off-white liquid	
Density	~1.55 kg/l (mixed, at 25°C)	
Solid content by mass	$^{\sim}100~\%$ Note: Total solid epoxy composition acc. to the test method Deutsche Bauchemie e.V. (German Association for construction chemicals)	

Product Data Sheet

Sikafloor® P 651 September 2024, Version 02.01 020811000000002055

TECHNICAL INFORMATION

Flexural-strength	≥ 40 N/mm² (at 25°C)	(ASTM C580)
Tensile strength	≥ 15 N/mm² (at 25°C)	(ASTM C307)
Tensile adhesion strength	≥ 1.5 N/mm² (or failure in concrete)	(ASTM D4541)
Skid / slip resistance	~85	(BS 7976, Part 2)
Service temperature	Dry heat permanent exposure up to +60°C.	

APPLICATION INFORMATION

Consumption	From 0.30 - 0.35 kg/m ² depending on surface texture and porosity. These figures are theoretical and do not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.		
Ambient air temperature	+10°C min. / +40°C max.		
Relative air humidity	80 % r.h. max.		
Dew point	Beware of condensation! The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish. Note: Low temperatures and high humidity conditions increase the probability of blooming.		
Substrate moisture content	< 5 % pbw moisture content Test method: Sika®-Tramex	nt. c meter, CM-measurement or Oven-dry-methording to ASTM D4236 (Polyethylene-sheet).	
Substrate moisture content Pot Life	< 5 % pbw moisture conten Test method: Sika®-Tramex od. No rising moisture acco	meter, CM-measurement or Oven-dry-meth-	
	< 5 % pbw moisture content Test method: Sika®-Tramex	meter, CM-measurement or Oven-dry-methording to ASTM D4236 (Polyethylene-sheet).	
	< 5 % pbw moisture content Test method: Sika®-Tramex od. No rising moisture accontemperature:	meter, CM-measurement or Oven-dry-methording to ASTM D4236 (Polyethylene-sheet). Time:	
	< 5 % pbw moisture content Test method: Sika®-Tramex od. No rising moisture accontent Temperature: +25°C +40°C Full cure: ~7 days at +25°C	region of the contract of the	
Pot Life Curing time	< 5 % pbw moisture content Test method: Sika®-Tramex od. No rising moisture accontent Temperature: +25°C +40°C Full cure: ~7 days at +25°C Curing times are approximate	region of the contract of the	
Pot Life	< 5 % pbw moisture content Test method: Sika®-Tramex od. No rising moisture accontent Temperature: +25°C +40°C Full cure: ~7 days at +25°C	meter, CM-measurement or Oven-dry-methording to ASTM D4236 (Polyethylene-sheet). Time: ~40 min. ~20 min. and will be affected by changing ambient conditions	

BASIS OF PRODUCT DATA

- All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
- Internal Reference Version: MBS_CC-UAE/ Top_P651_07_15/v1/09_19

FURTHER DOCUMENTATION

- System Method Statement
- Substrate quality & Preparation: Please refer to Sika Method Statement: "EVALUATION AND PREPARA-TION OF SURFACES FOR FLOORING SYSTEMS".

IMPORTANT CONSIDERATIONS

 Do not apply Sikafloor® P 651 on substrates with rising moisture.

- Freshly applied Sikafloor® P 651 should be protected from damp, condensation and water for at least 24 hours.
- Practical trials should be carried out for mortar mixes to assess suitable aggregate grain size distribution.
- For external applications, apply on a falling temperature. If applied during rising temperatures "pin holing" may occur from rising air.

Construction joints require pre-treatment. Treat as follows:

- Static Cracks: prefill and level with Sikadur® or Sikafloor® suitable epoxy resin based mortars.
- Dynamic cracks: to be assessed and if necessary apply a stripe coat of elastomeric material or design as a movement joint.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.



ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

- The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².
- The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.
- Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.
- Weak concrete must be removed and surface defects such as blow holes and voids must be fully exposed.
- Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor®, Sikadur® or SikaEmaco® range of materials.
- All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum.

MIXING

Mix the base (Part A) and reactor (Part B) of Sikafloor® P 651 together, for a minimum of one minute, until it is streak free and then add the PTC powder (Part C) and mix for additional 2 minutes until a uniform even mix is achieved. Do not overmix.

APPLICATION

Apply the mixed Sikafloor® P 651 to the substrate, using a medium pile roller at suitable rate, depending on the absorption of the substrate. The surface of the primer must be glossy. Dry / matt areas must be reprimed.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with suitable thinner (Xylene / MEK / Acetone), immediately after use. Hardened and/or cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC Sika International Chemicals LLC Tel: +971 4 439 8200 Email: info@ae.sika.com Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC Riyadh / Jeddah / Dammam / Rabigh Tel: +966 12 692 7079 Email: info@sa.sika.com Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC (part of Sika) Tel. +968 22 826 500 Email: info@om.sika.com Web: gcc.sika.com



ISO 9001, 16091, 45901 – 565;

- Sha LUE LUC
- Sha Guit E.S.C. D

Sha Fatematismal Chemicals LLC
- Sha Guit E.S.C. D

Sho 9001, 14002 – 565;

- Sha Soudi Anaba Limited

ISO 9001, 14003 – TÜV;

- Sha Mic Construction Chemicals LLC
- Sha Construction Chemicals

For Manufacturing LLC
- Allaser Balakers Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



SikafloorP651-en-AE-(09-2024)-2-1.pdf

