

PRODUCT DATA SHEET

Sarnafil® S 327-12 L

POLYMERIC MEMBRANE FOR MECHANICALLY FASTENED ROOF WATERPROOFING



DESCRIPTION

Sarnafil® S 327-12 L (thickness 1.2 mm) is a polyester reinforced, multi-layer, synthetic roof waterproofing sheet based on premium-quality polyvinyl chloride (PVC) containing ultraviolet light stabilizers according to EN 13956.

Sarnafil® S 327-12 L is a hot air weldable roof membrane, formulated for direct exposure. Suitable for use in hot and tropical climatic conditions.

USES

Waterproofing membrane for:

Mechanically fastened roofing systems

CHARACTERISTICS / ADVANTAGES

- Proven performance over decades
- Resistant to permanent UV irradiation
- Resistant to permanent wind exposure
- Resistant to all common environmental influences
- Hot air welding without use of open flames
- High water vapour permeability
- Recyclable

SUSTAINABILITY

- Conformity with LEED v4 MRc 2 (Option 1): Building Product Disclosure and Optimization – Environmental Product Declarations
- Conformity with LEED v4 MRc 3 (Option 2): Building Product Disclosure and Optimization - Sourcing of Raw Materials
- Conformity with LEED v4 MRc 4 (Option 2): Building Product Disclosure and Optimization - Material Ingredients
- Conformity with LEED v2009 MRc 4 (Option 2): Recycled Content

APPROVALS / CERTIFICATES

Sarnafil® S 327-12 L is designed and manufactured to meet most international recognised standards.

- Polymeric sheets for roof waterproofing according to EN 13956 certified by notified body 1213-CPD-4920 and provided with the CE-mark.
- Reaction to fire according to EN 13501-1. Class E.
- External fire performance tested according to ENV 1187 and classified according to EN 13501-5: BROOF(t1).

PRODUCT INFORMATION

Packaging	Sarnafil® S 327-12 L sta foil.	ndard rolls are wrapped individ	dually in a blue PE-	
	Packing unit	See price list	See price list	
	Roll length	20.00 m		
	Roll width	2.00 m		
	Roll weight 60.00 kg			
Appearance / Colour	Surface Matt			
	Colours			
	Top surface Light grey (nea		est RAL 7047)	
	Bottom surface Dark grey			
Shelf life	5 years from date of propackaging.	5 years from date of production in unopened, undamaged and original packaging.		
Storage conditions	pallet, protected from o	Rolls must be stored between +5 °C and +30 °C in a horizontal position on pallet, protected from direct sunlight, rain and snow. Do not stack pallets of rolls or any other material during transport or storage.		
Product Declaration	EN 13956	EN 13956		
Visible Defects	Pass		(EN 1850-2)	
Length	20 m (-0 % / +5 %)	20 m (-0 % / +5 %)		
Width	2 m (-0.5 % / +1 %)	2 m (-0.5 % / +1 %)		
Effective Thickness	1.2 mm (-5 % / +10 %)	1.2 mm (-5 % / +10 %)		
Straightness	≤ 30 mm	≤ 30 mm		
Flatness	≤ 10 mm		(EN 1848-2)	
Mass per unit area	1.5 kg/m² (-5 % / +10 %)	(EN 1849-2)	
TECHNICAL INFORMATION	ON			
Resistance to Impact	Hard substrate	≥ 600 mm	(EN 12691)	
	Soft substrate	≥ 900 mm	_	
Hail Resistance	Rigid substrate	≥ 17 m/s	(EN 13583)	
	Flexible substrate	≥ 25 m/s	-	
Resistance to Static Load	Soft substrate	≥ 20 kg	(EN 12730)	
	Rigid substrate	≥ 20 kg	_	
Tensile Strength	Longitudinal (md) ¹⁾	≥ 1000 N/50 mm	(EN 12311-2)	
	Transversal (cmd) ²⁾	≥ 1000 N/50 mm	_	
	 md = machine direction cmd = cross machine direction 			
Elongation	Longitudinal (md) ¹⁾	≥ 12 %	(EN 12311-2)	
	Transversal (cmd) ²⁾	≥ 12 %	_	
	1) md = machine direction2) cmd = cross machine direction			
Dimensional Stability	Longitudinal (md) ¹⁾	≤ 0.3 %	(EN 1107-2)	
	Transversal (cmd) ²⁾	≤ 0.2 %	_	
	1) md = machine direction			





Tear Strength	Longitudinal (md) ¹⁾ Transversal (cmd) ²⁾	≥ 200 N ≥ 200 N	(EN 12310-2)
	1) md = machine direction 2) cmd = cross machine direction		
Joint Peel Resistance	No failure of the joint		(EN 12316-2)
Joint Shear Resistance	≥ 800 N/50 mm	(EN 12317-2)	
Foldability at Low Temperature	≤ -25 °C	(EN 495-5)	
External Fire Performance	Broof(t1) < 20°		(EN 1187) (EN 13501-5)
Reaction to Fire	Class E	(EN ISO 11925-2, classification to EN 13501-1)	
Effect of Liquid Chemicals, Including Water	On request		(EN 1847)
Resistance to UV Exposure	Pass (> 5000 h / grade 0)		(EN 1297)
Water Vapour Transmission	μ = 15 000		(EN 1931)
Watertightness	Pass		(EN 1928)
SYSTEMS			

System Structure	Wide range of accessories is available example prefabricated parts, roof drains, scuppers, walkway pads and decor profiles. The following accessories shall be used: Sarnafil® G 410-15 Sheet for detailing Sarnafil® Metal Sheet PVC Sarnabar® / Sarnafast® S-Welding Cord PVC			
				 Sarnacol® 2170 (contact adhesive) Sarna Seam Cleaner
				■ Sarna Cleaner
				Compatibility

APPLICATION INFORMATION

Ambient Air Temperature	-20 °C min. / +60 °C max.
Substrate Temperature	-30 °C min. / +60 °C max.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate surface must be uniform, smooth and free of any sharp protrusions or burrs, etc.

Sarnafil® S 327-12 L must be separated from any incompatible substrates by an effective separation layer to prevent accelerated ageing. Prevent from direct contact with bitumen, tar, fat, oil, solvent containing material and direct contact to other plastic materials, example expanded polystyrene (EPS), extruded polystyrene (XPS), polyurethane (PUR), polyisocyanurate (PIR) or phenolic foam (PF) as this could adversely affect the product properties.

The supporting layer must be compatible to the membrane, solvent resistant, clean, dry and free of grease and dust. Metal sheets must be degreased with Sarna Cleaner before adhesive is applied.

APPLICATION

Installation works to be carried out only by Sika instructed contractors for roofing.

Installation of some ancillary products, example contact adhesives / cleaners is limited to temperatures

tact adhesives / cleaners is limited to temperatures above +5 °C. Please observe information given by Product Data Sheets.

APPLICATION METHOD / TOOLS

Installation procedure:

According to the valid installation instructions for Sarnafil® S 327-12 L-types system for mechanically fastened roofing systems.





Fixing Method, linear fasting (Sarnabar®):

Unroll the Sarnafil® S 327-12 L membrane, overlap by 80 mm, weld immediately and fix to the substructure by means of Sarnabar®. The preferred type of fastening and the distance will be advised by Sika. The spacing of the fasteners is in accordance with the project specific calculations. The perimeter piece ends must be secured with the Sarnabar® Load Distribution Plate. For protection fasten a piece of Sarnafil® S 327-12 L under bar end and plate. Leave a 10 mm clearance between bar ends. Do not fasten in hole nearest bar end. Cover the bar ends with a piece of Sarnafil® S 327-12 L and weld. After installation the Sarnabar® must immediately be made watertight with a Sarnafil® S 327-12 L cover strip. At upstands and at all penetrations, the Sarnafil® S 327-12 L membrane must be secured with a Sarnabar®. The 4 mm diameter S-Welding Cord protects the Sarnafil® S 327-12 L roof covering against tearing and peeling off by wind uplift.

Fixing Method, spot fasting (Sarnafast®):

Sarnafil® S 327-12 L must always be installed at right angles to the deck direction. Sarnafil® S 327-12 L is fixed by means of the Sarnafast® fasteners and barbed washers/tubes along the marked line, 35 mm from the edge of the membrane. Sarnafil® S 327-12 L is overlapped by 120 mm. The spacing of the fasteners is in accordance with the project specific calculations. At upstands and at all penetrations, the Sarnafil® S 327-12 L membrane must be secured with a Sarnabar®. The 4 mm diameter S-Welding Cord protects the Sarnafil® S 327-12 L roof covering against tearing and peeling off by wind uplift.

Welding Method:

Overlap seams are welded by electric hot air welding equipment, such as manual hot air welding machines and pressure rollers or automatic hot air welding machines with controlled hot air temperature.

Recommended type of equipment:

Leister Triac for manual welding and Sarnamatic® 681 for automatic welding.

Welding parameters including temperature, machine speed, air flow, pressure and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic situation prior to welding. The effective width of welded overlaps by hot air must be minimum 20 mm.

The seams must be mechanically tested with screw driver to ensure the integrity / completion of the weld. Any imperfections must be rectified by hot air welding.

IMPORTANT CONSIDERATIONS

Geographical / ClimateC.

Permanent ambient temperature during use is limited to +50 °C.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

Fresh air ventilation must be ensured, when working (welding) in closed rooms.

REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w)



LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait Tel: +973 177 38188 sika.gulf@bh.sika.com gcc.sika.com



ISO 9001: Sika UAE LLC, Sika Gulf B.S.C. (c), Sika Saudi Arabia Co. Ltd, Sika Qatar LLC ISO 14001: Sika UAE LLC, Sika Gulf B.S.C. (c), Sika Saudi Arabia Co. Ltd OHSAS: Sika UAE LLC, Sika Gulf B.S.C. (c)

Product Data Sheet Sarnafil® S 327-12 L October 2017, Version 01.01 020905012000121001

SIKA SOUTHERN GULF

UAE / Oman / SIC Tel: +971 4 439 8200 info@ae.sika.com gcc.sika.com

under a management system certified to conform to the requirements of the quality, environmental and

SIKA SAUDI ARABIA

Rivadh / Jeddah / Dammam Tel: +966 11 217 6532 info@sa.sika.com gcc.sika.com

BUILDING TRUST

SarnafilS327-12L-en-AE-(10-2017)-1-1.pdf

