

PRODUCT DATA SHEET

Sika® Separol®-202

(formerly MFinish 202)

Oil based, anti-corrosive shutter release agent

DESCRIPTION

Chemical release mould and shutter faces prior to casting concrete in order to achieve a clean release. After removal of the formwork, the resultant concrete has a smooth, hard, uniform finish, with reduced incidence of blow holes. Low viscosity hydrocarbon carrier blended with a chemically active release agent. Suitable for use in hot and tropical climatic conditions.

USES

- Steel shuttering
- Plywood shutters
- High density plastic shutters

FEATURES

- Sika® Separol®-202 exhibits a smooth, hard, and uniform finish.
- Sika® Separol®-202 has no negative effect on the properties of concrete.
- It will not impair the adhesion of subsequent surface treatments when applied at the recommended coverage rates.
- Allows clean, easy striking
- Extends the life of formwork
- Improved finish for fair faced concrete
- Reduces concrete contamination
- Economical to use

PRODUCT INFORMATION

Composition	Blend of oil based products
Packaging	210 L drums
Shelf life	12 months from date of production if stored properly
Storage conditions	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5°C and +50°C. Mix well before using.
Appearance and colour	Clear to brown liquid
Density	~0.83 kg/l (+25 °C)
Total chloride ion content	Nil (EN 934-2)

APPLICATION INFORMATION

Consumption	The coverage rate for Sika® Separol®-202 is between 30 to 70 m ² /L when spray applied depending on the smoothness, type and porosity of the formwork used.
-------------	--

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Excess application will tend to run down on vertical surfaces and pond at the bottom. Remove excess material using a dry cloth or sponge. Over application may lead to staining of the hardened concrete. After application to surfaces protect them from rain for at least 2 - 3 hours.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

APPLICATION

Apply before the first casting and thereafter re-apply immediately after stripping and cleaning the mould. Shutter surfaces must be clean and free from moisture, dirt and laitance.

Lightweight horticultural sprayers are ideal as Sika® Separol®-202 is finely atomised to give a uniform coating. Excessive application should be avoided.

Alternatively, application may be made by a fine haired brush, only a very thin coating should be made and any excess removed.

If after the first application, the Sika® Separol®-202 is completely absorbed into new timber or plywood, a further application should be made before filling the moulds or formwork.

CLEANING OF EQUIPMENT

Sika® Separol®-202 may usually be left in spray guns or sprayers without detriment, but with certain types, there may be some softening of rubber seals with prolonged contact.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188

Email: info@bh.sika.com

Sika Kuwait Cons. Mat. & Paints Co WLL

Tel: +965 22 282 296

Email: sika.kuwait@kw.sika.com

Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC

Sika International Chemicals LLC

Tel: +971 4 439 8200

Email: info@ae.sika.com

Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for

Manufacturing LLC

Riyadh / Jeddah / Dammam / Rabigh

Tel: +966 12 692 7079

Email: info@sa.sika.com

Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC

(part of Sika)

Tel. +968 22 826 500

Email: info@om.sika.com

Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
- Sika UAE LLC
- Sika International Chemicals LLC
- Sika Gulf B.S.C. (c)
- Sika MB Construction Chemicals LLC
- Sika Saudi Arabia Limited
- Sika MB Construction Chemicals for Manufacturing LLC
- Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

Sika® Separol®-202

November 2024, Version 02.01

02140500000002124