

## PRODUCT DATA SHEET

# Sikafloor® Marine-579

## Self-levelling decorative resin

## TYPICAL PRODUCT DATA (FURTHER VALUES SEE SAFETY DATA SHEET)

Properties	Sikafloor® Marine-579 (A)	Sikafloor® Marine-579 (B)
<b>Chemical base</b>	Polyurethane	Isocyanate
<b>Color (CQP001-1)</b>	Colored	Transparent
	mixed Brown colors available (see color design chart)	
<b>Density</b>	1.5 kg/l	1.2 kg/l
	mixed 1.4 kg/l	
<b>Solid content</b>	100 %	
<b>Mixing ratio</b>	by weight	79 : 21
<b>Application temperature</b>	substrate / climate	10 – 30 °C <sup>A, B</sup>
<b>Working time</b>	10 °C	30 minutes
	20 °C	21 minutes
	30 °C	18 minutes
<b>Shore D hardness (CQP023-1 / ISO 48-4)</b>	50	
<b>Tensile strength (DIN 53504)</b>	20 MPa	
<b>Elongation at break (DIN 53504)</b>	100 %	
<b>Shelf life</b>	9 months <sup>C</sup>	12 months <sup>C</sup>

CQP = Corporate Quality Procedure <sup>A)</sup> Substrates must be 3 °C above the dew point<sup>B)</sup> max. 80 % r.h.<sup>C)</sup> stored in sealed container in up-right position in a dry place between 5 and 30 °C, protected from direct sunlight**DESCRIPTION**

Sikafloor® Marine-579 is a 2-component, polyurethane, tough elastic, low VOC self-smoothing marine flooring resin. It is part of the Sikafloor® Marine decorative resin systems.

**PRODUCT BENEFITS**

- Good application characteristics
- Very low VOC emission
- Good mechanical resistance
- Solvent-free (ISO 16001-6)
- tough elastic

**AREAS OF APPLICATION**

Sikafloor® Marine-579 can be used interior and exterior as wearing layer compound in ship and boat construction. For interior tough floor solution and exterior as a layer compound in the Sikafloor® Marine Deco Teak solutions.

This product is suitable for experienced professional users only. Tests with actual substrates and conditions have to be performed ensuring adhesion and material compatibility.

## CURE MECHANISM

The curing of Sikafloor® Marine-579 takes place by a chemical reaction of the two components.

Higher temperatures speed up and lower temperatures slow down the curing process.

## CHEMICAL RESISTANCE

For advice contact the Technical Department of Sika Industry.

## METHOD OF APPLICATION

### Surface preparation

For steel decks, an anti-corrosion protection layer applied and intact as designed by the shipyard is a pre-requisite.

The surface need to be clean, free of dirt, dust, grease, oil and loose particles before application of the SikaCor® ZP Primer. The adhesion between the anti-corrosion protection layer and SikaCor® ZP Primer must be verified.

Aluminum deck needs to be clean, free of dirt, dust, grease, oil and loose particles. The aluminum substrate must be sanded with 40 – 80 grit and dust free vacuum cleaned before application of SikaCor® ZP Primer (Tiecoat).

In the case of cementitious substrates, it must be ensured that the laitance layer is completely removed. This is usually achieved by grinding. All dust, loose and friable material must be completely removed by vacuum before the next application.

Repairs to the substrate, filling of cracks, holes/voids or surface levelling must be carried out first. Repair areas must be cured before applying primers.

Ensure the substrate moisture content is equal or less than 4 % (Calcium carbide method (CM-method). Apply Sikafloor®-150/-151 as a primer to obtain a closed pore free surface.

Backing substrate for prefab installations must be clean, dry and free of all contaminants such as dirt, oil, grease and loose friable material.

2-C polyurethane substrates need usually to be sanded with 40 – 80 grit sanding paper up to diamond disc. In case the substrate is not clean, it is required to clean it before the sanding process to ensure no debris is sanded into the surface. All dust, loose and friable material must be completely removed from the surface by vacuum cleaning before next application.

For more information and other substrates refer to the Sika Pre-Treatment Chart for Sikafloor® Marine Applications.

The application area must be protected against dirt, sun light, water and draught.

### Mixing process

Prior to mixing all components, stir part A using the electric mixing equipment.

Add part B to part A and mix continuously for 2 minutes until a uniformly mix has been obtained. To ensure thorough mixing pour materials into a clean container and mix again for at least 1 minute to achieve a smooth consistent mix.

## PRODUCT DATA SHEET

Sikafloor® Marine-579  
Version 05.01 (02 - 2026), en\_AE  
012119015794001000

## Sika UAE LLC

P.O.Box 126212  
Dubai  
United Arab Emirates  
Tel: +971 4 439 8200 Fax: +971 4 439  
3606  
info@ae.sika.com  
gcc.sika.com

Excessive mixing must be avoided to minimize air entrainment.

For areas with cambers or slopes (1 – 3 %) SikaLiquid Thickener or Sika® Extender T may be added to adapt the consistency of the product.

Remark: By adapt the consistency, the de-airing properties may be affected.

### Application

Sikafloor® Marine-579 is poured and spread evenly by means of a suitable trowel or pin leveller. A spike roller may be used to improve levelling and de-airing.

For liquid application on cambers and slopes multiple applications steps might be needed. A seamless finish can be achieved when a "wet" edge is maintained during application.

### Curing

Indications regarding curing details see table below.

Temper- ature	walk- and overcoatable	Full loading
10 °C	24 hours	7 days
20 °C	18 hours	7 days
30 °C	12 hours	7 days

### Removal

Uncured Sikafloor® Marine-579 can be removed from tools and equipment with Sika® Colma Cleaner or another suitable solvent. Once cured, the material can only be removed mechanically.

Hands and exposed skin shall be washed immediately using hand wipes such as Sika® Cleaner-350H or a suitable industrial hand cleaner and water.

Do not use solvents on skin.

### STORAGE CONDITIONS

Both components of Sikafloor® Marine-579 have to be kept between 5 °C and 30 °C in a dry place. Do not expose it to direct sunlight. After opening of the packaging, the contents need to be protected against moisture.

Minimum temperature during transportation is 5 °C.

## FURTHER INFORMATION

The information herein is offered for general guidance only. Advice on specific applications is available on request from the Technical Department of Sika Industry.

Copies of the following publications are available on request:

- Safety Data Sheet
- Sika Pre-Treatment Chart for Sikafloor® Marine Applications

## PACKAGING INFORMATION

Sikafloor® Marine-579 (A)

Pail	15.8 kg
------	---------

Sikafloor® Marine-579 (B)

Pail	4.2 kg
------	--------

## BASIS OF PRODUCT DATA

All technical data stated in this document are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## HEALTH AND SAFETY INFORMATION

For information and advice regarding transportation, handling, storage and disposal of chemical products, users shall refer to the actual Safety Data Sheets containing physical, ecological, toxicological and other safety-related data.

## DISCLAIMER

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

