

PRODUCT DATA SHEET

Sika® ViscoCrete® RM-115 SA

HIGH RANGE WATER-REDUCING ADMIXTURE FOR CONCRETE

DESCRIPTION

Sika® ViscoCrete® RM-115 SA is a polycarboxylate based superplasticizer developed particularly for use in ready mixed concrete to give extended slump retention and high strength development of high specification grade concrete mixes. Sika® ViscoCrete® RM-115 SA is suitable for use in concrete mixes incorporating pozzolanic materials such as GGBS, PFA and micro-silica. Suitable for use in hot and tropical climatic conditions.

USES

Sika® ViscoCrete® RM-115 SA is mainly used for the following applications:

- Production of site mixed and ready-mix concrete during hot weather production of concrete with extended transportation or placing times
- Concrete requiring workability retention
- Concrete with low water binder ratio
- Concrete placing in congested steel reinforcement
- Production of high flowable and self-compacting concrete (SCC)
- Slim elements requiring a high standard of surface finish
- High performance durable concrete

PRODUCT INFORMATION

Composition	Aqueous solution of modified polycarboxylates co-polymers
Packaging	210 L drum, 1000 L flowbin or bulk supply in tanker
Appearance and colour	Brown colored liquid
Shelf life	12 months from date of production if stored properly
Storage conditions	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5 °C and +45 °C. Protect from direct sunlight. Mix well before use.
Density	~1.08 kg/l (+25 °C)

FEATURES

Sika® ViscoCrete® RM-115 SA acts by surface absorption on the cement particles producing steric hindrance and electrostatic repulsion between cement particles which results in higher dispersion, flow and retention. Sika® ViscoCrete® RM-115 SA provides the following beneficial properties:

- Powerful plasticising action Production of workable concrete at low water binder ratio
- Improved shrinkage and creep characteristics
- Excellent flowability resulting in minimal placing and compacting efforts
- Slower rate of carbonation ingress
- Cost effective, structurally economical concrete
- Higher ultimate strengths allows greater flexibility for engineers to design durable concrete
- Reduced surface defects so improving aesthetic appearance
- Durable concrete, doesn't contain chlorides or other steel corrosion promoting ingredients

CERTIFICATES AND TEST REPORTS

Sika® ViscoCrete® RM-115 SA follows the requirements of ASTM C494; Type F and EN 934-2

pH-Value	4–6	
Total chloride ion content	Nil	(EN 934-2)

TECHNICAL INFORMATION

Concreting guidance	The standard rules of good concreting practice for production and placing must be observed when using Sika® ViscoCrete® RM-115 SA in concrete. Refer to relevant standards. Fresh concrete must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Use Sika® Antisol® products as a curing agent or apply wet hessian.
----------------------------	---

APPLICATION INFORMATION

Recommended dosage	0.5 L to 2.0 L per 100 kg of total binder. Higher dosages by weight of binder can be used depending on the mix design, raw materials, climatic conditions and concrete requirements. Trial mixes must be performed to establish the exact dosage as per the project requirements.
Compatibility	<p>Sika® ViscoCrete® RM-115 SA is suitable for mixes containing all types of cement and supplementary cementitious materials such as: Microsilica (Silica Fume), Fly Ash (PFA), GGBS (Ground Granulated Blast Furnace Slag) and the following Sika products:</p> <ul style="list-style-type: none"> ▪ SikaPump® ▪ Sika® FerroGard® ▪ SikaFume® ▪ SikaFiber® ▪ Sika® Aer ▪ Sika® Stabilizer ▪ SikaControl® <p>Sika® ViscoCrete® RM-115 SA can be used with air-entraining admixtures, provided they meet ASTM, AASHTO CRG specifications. We recommend to perform trial mixes to establish the required performance when combining Sika® ViscoCrete® RM-115 SA with the above products or other admixtures. Please consult our Sika Technical Department for further assistance.</p>
Dispensing	Sika® ViscoCrete® RM-115 SA is added to the gauging water or simultaneously poured with it into the concrete mixer at the batching plant. Do not add Sika® ViscoCrete® RM-115 SA directly to the dry mix. For optimum utilization of its high water reduction property, we recommend thorough mixing at a minimal wet mixing time of 60 seconds. The addition of the remaining gauging water (to fine tune concrete consistency) may only be started after two-thirds of the wet mixing time to avoid surplus water in the concrete.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS OF USE

When using Sika® ViscoCrete® RM-115 SA a mix design must be selected for the local material sources used and trial mixes performed to verify suitability. If frozen and/or if precipitation has occurred, it may only be used after thawing slowly at room temperature and intensive mixing. Sika® ViscoCrete® RM-115 SA should not be added to dry cement. Before pouring, suitability tests on the fresh concrete must be carried out.

Due to the extended workability take special care that formwork is properly installed and secured. In case the setting time of concrete is extended, if cured properly, other properties may not be affected and higher ultimate strength is visualized. **Sika® ViscoCrete® products are not compatible with admixtures based on sulfonated naphthalene or melamine.** When accidental overdosage occurs bleeding and segregation of the concrete and retardation of initial set will be observed.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188

Email: info@bh.sika.com

Sika Kuwait Cons. Mat. & Paints Co WLL

Tel: +965 22 282 296

Email: sika.kuwait@kw.sika.com

Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC

Sika International Chemicals LLC

Tel: +971 4 439 8200

Email: info@ae.sika.com

Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for

Manufacturing LLC

Riyadh / Jeddah / Dammam / Rabigh

Tel: +966 9200 22167

Email: info@sa.sika.com

Web: gcc.sika.com

Sika LLC - Oman

Sika MB LLC

Tel. +968 22 826 500

Email: info@om.sika.com

Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
Sika MB LLC
Sika International Chemicals LLC
Sika Gulf B.S.C. (c)
ISO 9001, 14001 – SGS
Sika Saudi Arabia Limited
ISO 9001, 14001 – TÜV
Sika MB Construction Chemicals LLC
Sika Construction Chemicals for Manufacturing LLC
ISO 9001 – LMS
Sika MB LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

Sika® ViscoCrete® RM-115 SA

June 2025, Version 01.01

021301011000243871