

## PRODUCT DATA SHEET

# SikaControl® SRA 50

(formerly MasterLife® SRA 50)

Expanding plasticising admixture for cementitious grout and concrete

## DESCRIPTION

SikaControl® SRA 50 is an expansion system which compensates for plastic shrinkage and settlement in cementitious grouts and concrete. Supplied in powder form, SikaControl® SRA 50 produces controlled expansion and maintains high water retention. It contains a water-reducing agent which increases the workability of the mix with a reduced water content. Full expansion is achieved before initial setting occurs resulting in a high degree of interfacial contact.

Suitable for use in hot and tropical climatic conditions.

## USES

- Ready-mixed or precast concrete structures
- Wet mix shotcrete
- Mortars and grouts

## FEATURES

- Improves the free flowing properties of the grout or concrete at low water/cement ratios.
- Increases the volume of the grout or concrete which in turn offsets shrinkage and settlement.

## PRODUCT INFORMATION

Composition	Blend of organic and inorganic chemicals	
Packaging	15 kg bag	
Shelf life	9 months from date of production if stored properly	
Storage conditions	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5°C and +50°C. Protect from moisture.	
Appearance and colour	Grey powder	
Density	~0.85 kg/l (+25 °C)	
Total chloride ion content	Nil	(EN 934)

## APPLICATION INFORMATION

Recommended dosage	0.5 % by weight of binder. Other dosages by weight of binder may be used depending on the mix design, raw materials, climatic conditions and concrete requirements. Trial mixes must be performed to establish the exact dosage rate required.
--------------------	--

## BASIS OF PRODUCT DATA

- All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
- Internal Reference - Version: MBS\_CC-UAE/Life\_SRA50\_01\_95/v3/11\_14

## IMPORTANT CONSIDERATIONS

- The expansion obtained by the use of SikaControl® SRA 50 reaches a maximum within 1–2.5 hours of mixing under average temperature conditions. After this period no settlement occurs and the grout retains its maximum expansion.
- May be used with ordinary Portland cement or rapid hardening Portland cement.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### MIXING

First add the water to the mixer and then the Portland cement, mix thoroughly until the cement has been completely dispersed. Then add the SikaControl® SRA 50 and sand (if any is being used), and continue mixing a further 2 minutes or until complete dispersion of the SikaControl® SRA 50 is achieved.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Sika Gulf B.S.C. (c)

Tel: +973 177 38188  
Email: info@bh.sika.com  
Sika Kuwait Cons. Mat. & Paints Co WLL  
Tel: +965 22 282 296  
Email: sika.kuwait@kw.sika.com  
Web: gcc.sika.com

#### Sika UAE LLC

Sika MB Construction Chemicals LLC  
Sika International Chemicals LLC  
Tel: +971 4 439 8200  
Email: info@ae.sika.com  
Web: gcc.sika.com

#### Sika Saudi Arabia Limited

Riyadh / Jeddah / Dammam / Rabigh  
Tel: +966 11 217 6532  
Email: info@sa.sika.com  
Web: gcc.sika.com

#### Sika LLC - Oman

Master Builders Solutions LLC  
(part of Sika)  
Tel. +968 22 826 500  
Email: info@om.sika.com  
Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS:  
- Sika UAE LLC  
- Sika International Chemicals LLC  
- Sika Gulf B.S.C. (c)  
- Sika Saudi Arabia Limited  
- Sika MB Construction Chemicals LLC  
- Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



#### Product Data Sheet

SikaControl® SRA 50

March 2024, Version 01.02

021403000000002014