

# PRODUCT DATA SHEET

# Sikafloor® P 650

(formerly MTop P 650)

# TWO COMPONENT TOTAL SOLIDS EPOXY SURFACE SEALER AND PRIMER

#### **DESCRIPTION**

Sikafloor® P 650 is a high grade, low-viscosity, two-component epoxy primer and surface sealer. Sikafloor® P 650 is used as a sealer or scratch coat, with or without, the addition of guartz sand.

#### **USES**

Sikafloor® P 650 is suitable for the sealing of concrete surfaces, as well as for the filling of fissures and joints. For improved subsequent coat adhesion, Sikafloor® P 650 can be lightly broadcasted with quartz sand, while still wet, to create additional mechanical key. Sikafloor® P 650 may be mixed with selected aggregate to the desired consistency, to create mortar for patch repairs or to form covings. The mixed mortar must be applied to a surface previously coated with Sikafloor® P 650 resin, whilst still tacky.

# **FEATURES**

- Easy application
- Low viscosity
- Seals porus substrate
- Multipurpose primer
- Good penetration
- Short waiting times, faster drying
- Good intercoat adhesion
- Excellent bond strength

# PRODUCT INFORMATION

Composition	Two component epoxy resin	
Packaging	15 kg units (A+B)	
Shelf life	12 months from date of production	
Storage conditions	The packaging must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5°C and +30°C.  Store under cover, out of direct sunlight and protect from temperature extremes. In tropical climates the product must be stored in an air-conditioned environment.	
Appearance and colour	Clear to pale yellow liquid	
Density	~1.09 kg/l (mixed, at 25°C)	
Solid content by mass	$^{\sim}100~\%$ Note: Total solid epoxy composition acc. to the test method Deutsche Bauchemie e.V. (German Association for construction chemicals)	

### **Product Data Sheet**

**Sikafloor® P 650** September 2024, Version 02.01 020811000000002054

#### TECHNICAL INFORMATION

Tensile adhesion strength	Greater than cohesive strength of typical good quality concrete substrate	
APPLICATION INFORMA	TION	
Consumption	Min. 0.15 kg/m <sup>2</sup> This figure is theoretical and does not allow for any additional material due to surface porosity, surface profile, variations in level or wastage etc.	
Ambient air temperature	+10°C min. / +40°C max.	
Relative air humidity	80 % r.h. max.	
Dew point	Beware of condensation!  The substrate and uncured floor must be at least 3°C above dew point to reduce the risk of condensation or blooming on the floor finish.  Note: Low temperatures and high humidity conditions increase the probability of blooming.	
Substrate temperature	+10°C min. / +40°C max.	
Substrate moisture content	< 5 % pbw moisture content.  Test method: Sika®-Tramex meter, CM-measurement or Oven-dry-method.  No rising moisture according to ASTM (Polyethylene-sheet).	
Pot Life	~20 minutes at 25°C	
Curing time	Full cure: 7 days at 20°C	
Tack free time	~20 min. at 25°C	
Waiting time to overcoating	Temperature +20°C +30°C	Witing time for overcoating 12 hours 6 hours

# **BASIS OF PRODUCT DATA**

- All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
- Internal Reference Version: MBS\_CC-UAE/
   Top P650 06 98/v2/07 15/v3/09 19

#### **FURTHER DOCUMENTATION**

- Method Statement Thin section epoxy repair
- Substrate quality & Preparation: Please refer to Sika Method Statement: "EVALUATION AND PREPARA-TION OF SURFACES FOR FLOORING SYSTEMS".

# **IMPORTANT CONSIDERATIONS**

- Do not apply Sikafloor® P 650 on substrates with rising moisture.
- Freshly applied Sikafloor® P 650 should be protected from damp, condensation and water for at least 24 hours.
- Practical trials should be carried out for mortar mixes to assess suitable aggregate grain size distribution.
- For external applications, apply on a falling temperature. If applied during rising temperatures "pin holing" may occur from rising air.

Construction joints require pre-treatment. Treat as follows:

- Static Cracks: prefill and level with Sikadur® or Sikafloor ® suitable epoxy resin based mortars.
- Dynamic cracks: to be assessed and if necessary apply a stripe coat of elastomeric material or design as a movement joint.
- The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking.

# **ECOLOGY, HEALTH AND SAFETY**

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.



#### SUBSTRATE QUALITY / PRE-TREATMENT

- The concrete substrate must be sound and of sufficient compressive strength (minimum 25 N/mm²) with a minimum pull off strength of 1.5 N/mm².
- The substrate must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc.
- Concrete substrates must be prepared mechanically using abrasive blast cleaning or scarifying equipment to remove cement laitance and achieve an open textured surface.
- Weak concrete must be removed and surface defects such as blow holes and voids must be fully exposed.
- Repairs to the substrate, filling of blowholes/voids and surface levelling must be carried out using appropriate products from the Sikafloor®, Sikadur® or SikaEmaco® range of materials.
- All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by brush or vacuum.

#### **MIXING**

Pour the reactor (Part B) component into the base (Part A) component then mix continiously until streak free, approx. for 3 minutes.

On porous surfaces a maximum of 0.5 L of a suitable thinner (Xylene / MEK / Acetone) per 15 kg unit of primer may be added to improve penetration.

#### **APPLICATION**

Make sure that a continuous, pore free coat covers the substrate. If necessary, apply two priming coats. Apply Sikafloor® P 650 by brush, roller, airless spray or squeegee at the required coverage depending from substrate porosity. Preferred application is by using a squeegee and then back rolling crosswise.

#### **CLEANING OF EQUIPMENT**

Clean all tools and application equipment with suitable thinner (Xylene / MEK / Acetone), immediately after use. Hardened and/or cured material can only be removed mechanically.

#### LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

#### **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

#### Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

#### Sika UAE LLC

Sika MB Construction Chemicals LLC Sika International Chemicals LLC Tel: +971 4 439 8200 Email: info@ae.sika.com Web: gcc.sika.com

#### Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC Riyadh / Jeddah / Dammam / Rabigh Tel: +966 12 692 7079 Email: info@sa.sika.com Web: gcc.sika.com

#### Sika LLC - Oman

Master Builders Solutions LLC (part of Sika) Tel. +968 22 826 500 Email: info@om.sika.com Web: gcc.sika.com



ISO 9001, 16091, 45901 – 565:

- Sha Nat LLC
- Sha Coult St.C.
- Sha Coult St.C.
- Sha Coult St.C.
- Sha Countrained LLC
- Sha Countrained LLC
- Sha Countrained LLC
- Sha St.C.
- Sha St.

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



SikafloorP650-en-AE-(09-2024)-2-1.pdf

