

BUILDING TRUST

PRODUCT DATA SHEET

Sika® Plastiment® PZ 40 BH

(formerly MPozzolith 40LD)

Water reducing admixture

DESCRIPTION

Sika® Plastiment® PZ 40 BH is a versatile and economical concrete plasticiser with a wide dosage range suitable for various applications.

Suitable for use in hot and tropical climatic conditions.

USES

Sika® Plastiment® PZ 40 BH is used wherever high quality structural concrete is required. Its plasticising effect is particularly useful where:

- Exposed surfaces are important
- Maximum performance is desired
- Placing conditions are difficult
- Pre-cast elements are produced

FEATURES

Sika® Plastiment® PZ 40 BH provides:

- Improved workability without increased water
- Reduced water without loss of workability
- Increased strengths
- Improved surface finish
- Unaffected setting times
- Reduced shrinkage and creep

CERTIFICATES AND TEST REPORTS

Sika® Plastiment® PZ 40 BH follows the requirements of ASTM C494; Type B & D and EN 934-2

TECHNICAL INFORMATION

Concreting guidance	The standard rules of good concreting practice for production and placing must be observed when using Sika® Plastiment® PZ 40 BH in concrete. Refer to relevant standards. Fresh concrete must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Use Sika® Antisol® products as a curing agent or apply wet hessian.
PRODUCT INFORMATION	
Composition	Modified lignosulphonates blend
Packaging	1000 L flowbin. Bulk supply in tanker trucks possible on request
Shelf life	12 months from date of production if stored properly
Storage conditions	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5 °C and +45 °C. Protect from direct sunlight and frost.
Appearance and colour	Brown liquid
Density	~1.18 kg/l (+25 °C)

Product Data Sheet Sika® Plastiment® PZ 40 BH November 2024, Version 03.01 021303011000004744 Total chloride ion content Nil (EN 934-2)

APPLICATION INFORMATION

Recommended dosage	0.2 - 1.0 % by weight of binder. Higher dosages by weight of binder can be used depending on the mix design, raw materials, climatic conditions and concrete requirements. Trial mixes must be performed to establish the exact dosage rate required.
Dispensing	Sika® Plastiment® PZ 40 BH is added to the gauging water or simultaneously poured with it into the concrete mixer at the batching plant. Do not add Sika® Plastiment® PZ 40 BH directly to the dry mix. For optimum utilization we recommend thorough mixing at a minimum wet mixing time of 60 seconds. The addition of the remaining gauging water (to fine tune concrete consistency) may only be started after two-thirds of the wet mixing time to avoid surplus water in the concrete.
Compatibility	Sika® Plastiment® PZ 40 BH may be combined with all types of Portland cement (OPC and SRC), concretes containing pozzolanic materials such as; GGBS, PFA, micro-silica and the following Sika products: SikaPump®, Sika® FerroGard®-901, SikaFume®, SikaFiber®, Sika® Aer, Sika® Stabilizer, Sika®-1 WT, Sika® WT-10 We recommend to perform trial mixes to establish the required performance when combining Sika® Plastiment® PZ 40 BH with the above products or other admixtures. Please consult our Sika Technical Department.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Before pouring suitability tests on the fresh concrete must be carried out. Take special care that formwork is properly installed and secured. If frozen and/or if precipitation has occurred, it may only be used after thawing slowly at room temperature and intensive mixing. When using Sika® Plastiment® PZ 40 BH a suitable concrete mix must be designed for the local material sources and should be trialed. When accidental overdosing occurs the set retarding effect and workability increases. Additional air may also be entrained. During this period the concrete must be kept moist in order to prevent premature drying out.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.



LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC Sika International Chemicals LLC Tel: +971 4 439 8200 Email: info@ae.sika.com Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC Riyadh / Jeddah / Dammam / Rabigh Tel: +966 12 692 7079 Email: info@sa.sika.com Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC (part of Sika) Tel. +968 22 826 500 Email: info@om.sika.com Web: gcc.sika.com



SO 5001, 16091, 45091 – 565: Sita (UKE LIC Sita formatismal Chemicals LIC Sita Guil #5.5. ® 50 5001, 16091 – 565: Sita Sosal Arabia Limited 50 5001, 16091 – TÜV: Sita Mic Construction Chemicals Sita Construction Chemicals For Manufacturing LIC Master Builders Solution LIC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



SikaPlastimentPZ40BH-en-AE-(11-2024)-3-1.pdf

