

PRODUCT DATA SHEET

Sikament[®] NN

High Range Water-Reducing Concrete Admixture

DESCRIPTION

Sikament[®] NN is a highly effective dual action liquid superplasticiser for the production of high slump concrete or as a substantial water reducing agent for promoting high early and ultimate strengths. Suitable for use in hot and tropical climatic conditions.

USES

Sikament[®] NN is used as a superplasticizer in the production of free flowing concrete, such as:

- Slabs and foundations
- Walls, columns and piers
- Slender components with dense reinforcement
- Textured surface finished

Sikament[®] NN is also used as a water-reducing agent for producing high early strength concrete, such as:

- Pre-cast concrete elements
- Pre-stressed concrete
- Bridges and cantilever structures
- Concrete where formwork must be removed quickly or early loading can be applied

FEATURES

Sikament[®] NN provides the following properties:

As a Superplasticiser:

- Workability is greatly improved
- Concrete is placed easily
- Especially suitable for slender components with densely packed reinforcement
- Concrete requires less vibrating
- Improved cohesion of the concrete mix significantly reduces the risk of segregation and allows greater time for placement

As a Water Reducer:

- Impressive water reduction capability
- Final strength improvement

CERTIFICATES AND TEST REPORTS

Sikament[®] NN follows the requirements of ASTM C494; Type F and EN 934-2

PRODUCT INFORMATION

Composition	Sulphonated naphthalene
Packaging	1000 L flowbin. Bulk supply in tanker trucks possible on request
Shelf life	12 months from date of production
Storage conditions	The product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5°C and +50°C. Mix well before using.
Appearance and colour	Brown liquid
Density	~1.21 kg/l (+25°C)
Total chloride ion content	Nil (EN 934-2)

TECHNICAL INFORMATION

Concreting guidance

The standard rules of good concreting practice for production and placing must be observed when using Sikament® NN in concrete. Refer to relevant standards.

Fresh concrete must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Use Sika® Antisol® products as a curing agent or apply wet hessian.

APPLICATION INFORMATION

Recommended dosage

0.6 – 3.0 % by weight of binder.
Higher dosages by weight of binder can be used depending on the mix design, raw materials, climatic conditions and concrete requirements.
Trial mixes must be performed to establish the exact dosage rate required.

Dispensing

Sikament® NN is added to the gauging water or simultaneously poured with it into the concrete mixer at the batching plant.
Do not add Sikament® NN directly to the dry mix.
For optimum utilization of its high water reduction property we recommend thorough mixing at a minimal wet mixing time of 60 seconds. The remaining gauging water (to fine tune concrete consistency) may only be started after two-thirds of the wet mixing time to avoid surplus water in the concrete.

Compatibility

Sikament® NN may be combined with all types of Portland cement (OPC and SRC), concretes containing pozzolanic materials such as; Microsilica (Silica Fume), Fly Ash (PFA), GGBS (Ground Granulated Blast Furnace Slag) and the following Sika products:

- SikaPump®
- Sika® FerroGard®
- SikaFume®
- SikaFiber®
- Sika® Aer
- Sika® Stabilizer
- SikaControl®

We recommend that trial mixes be performed to establish the required performance when combining Sikament® NN with the above products or other admixtures. Please consult our Sika Technical Department.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

- When accidental overdosing occurs the set retarding effect and workability increases. Additional air may also be entrained. During this period the concrete must be kept moist in order to prevent premature drying out.

IMPORTANT CONSIDERATIONS

- Before pouring suitability tests on the fresh concrete must be carried out.
- Due to the extended workability take special care that formwork is properly installed and secured.
- If frozen and/or if precipitation has occurred, it may only be used after thawing slowly at room temperature and intensive mixing.
- When using Sikament® NN a suitable concrete mix must be designed for the local material sources and should be trialed.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC
Sika International Chemicals LLC
Tel: +971 4 439 8200
Email: info@ae.sika.com
Web: gcc.sika.com

Sika Saudi Arabia Limited

Riyadh / Jeddah / Dammam / Rabigh
Tel: +966 11 217 6532
Email: info@sa.sika.com
Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC
(part of Sika)
Tel. +968 22 826 500
Email: info@om.sika.com
Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
- Sika UAE LLC
- Sika International Chemicals LLC
- Sika Gulf B.S.C. (c)
- Sika MB Construction Chemicals LLC
- Sika MB Construction Chemicals LLC
- Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

Sikament® NN

March 2024, Version 01.02
02130201100000072