

# PRODUCT DATA SHEET

# Sarnafil® S 327-18 L (CH\_CE)

# POLYMERIC MEMBRANE FOR MECHANICALLY FASTENED ROOF WATERPROOFING



# **DESCRIPTION**

Sarnafil® S 327-18 L (CH\_CE) (thickness 1.8 mm) is a polyester reinforced, multi-layer, synthetic roof water-proofing sheet based on premium-quality polyvinyl chloride (PVC) containing ultraviolet light stabilizers according to EN 13956.

Sarnafil® S 327-18 L (CH\_CE) is a hot air weldable roof membrane, formulated for direct exposure. Suitable for use in hot and tropical climatic conditions.

# **USES**

Waterproofing membrane for:

Mechanically fastened roofing systems

# **CHARACTERISTICS / ADVANTAGES**

- Proven performance over decades
- Resistant to permanent UV irradiation
- Resistant to permanent wind exposure
- Resistant against impact load and hail
- Resistant to all common environmental influences
- Hot air welding without use of open flames
- High water vapour permeability
- Recyclable

# **SUSTAINABILITY**

- Conformity with LEED v4 MRc 2 (Option 1): Building Product Disclosure and Optimization – Environmental Product Declarations
- Conformity with LEED v4 MRc 3 (Option 2): Building Product Disclosure and Optimization - Sourcing of Raw Materials
- Conformity with LEED v4 MRc 4 (Option 2): Building Product Disclosure and Optimization - Material Ingredients
- Conformity with LEED v2009 MRc 4 (Option 2): Recycled Content

# **APPROVALS / CERTIFICATES**

Sarnafil® S 327-18 L (CH\_CE) is designed and manufactured to meet most international recognised standards.

- Polymeric sheets for roof waterproofing according to EN 13956 certified by notified body 1213-CPD-4920 and provided with the CE-mark.
- Reaction to fire according to EN 13501-1. Class E.
- External fire performance tested according to ENV 1187 and classified according to EN 13501-5: BROOF(t1).

# **PRODUCT INFORMATION**

Packaging	Sarnafil® S 327-18 L (CF blue PE-foil.	I_CE) standard rolls are wrapp	oed individually in a	
	Packing unit	Coo price list		
	<u>_</u>	See price list 15.00 m		
	Roll length Roll width	2.00 m		
	Roll weight	66.00 kg		
	Weight			
Appearance / Colour	Surface	Matt		
	Colours			
	Top surface Light grey (near		rest RAL 7047)	
	Bottom surface Dark grey			
	Top surface of sheet in other colours available on request, subject to minimum order quantities.			
Shelf life	5 years from date of propackaging.	5 years from date of production in unopened, undamaged and original packaging.		
Storage conditions	pallet, protected from o	Rolls must be stored between +5 °C and +30 °C in a horizontal position on pallet, protected from direct sunlight, rain and snow. Do not stack pallets of rolls or any other material during transport or storage.		
Product Declaration	EN 13956			
Visible Defects	Pass		(EN 1850-2)	
Length	15 m (-0 % / +5 %)		(EN 1848-2)	
Width	2 m (-0.5 % / +1 %)		(EN 1848-2	
Effective Thickness	1.8 mm (-5 % / +10 %)		(EN 1849-2)	
Straightness	≤ 30 mm		(EN 1848-2)	
Flatness	≤ 10 mm		(EN 1848-2)	
Mass per unit area	2.2 kg/m² (-5 % / +10 %	)	(EN 1849-2)	
TECHNICAL INFORMATION	N			
Resistance to Impact	Hard substrate	≥ 900 mm	(EN 12691	
	Soft substrate	≥ 1250 mm		
			<del></del>	
Hail Resistance	Rigid substrate	≥ 32 m/s	(EN 13583)	
	Flexible substrate	≥ 37 m/s		
Posistance to Static Load	Coft substrata	> 20 kg	(EN 12720)	
Resistance to Static Load	Soft substrate	≥ 20 kg	(EN 12730)	
Resistance to Static Load	Soft substrate Rigid substrate	≥ 20 kg ≥ 20 kg	(EN 12730) 	
	Rigid substrate	≥ 20 kg		
	Rigid substrate  Longitudinal (md) <sup>1)</sup>	≥ 20 kg ≥ 1100 N/50 mm		
Tensile Strength	Rigid substrate  Longitudinal (md) <sup>1)</sup> Transversal (cmd) <sup>2)</sup> 1) md = machine direction 2) cmd = cross machine direction	≥ 20 kg ≥ 1100 N/50 mm ≥ 1100 N/50 mm	(EN 12311-2)	
	Rigid substrate  Longitudinal (md) <sup>1)</sup> Transversal (cmd) <sup>2)</sup> 1) md = machine direction 2) cmd = cross machine direction Longitudinal (md) <sup>1)</sup>	≥ 20 kg  ≥ 1100 N/50 mm ≥ 1100 N/50 mm  ≥ 12 %	(EN 12311-2)	
Tensile Strength	Rigid substrate  Longitudinal (md) <sup>1)</sup> Transversal (cmd) <sup>2)</sup> 1) md = machine direction 2) cmd = cross machine direction Longitudinal (md) <sup>1)</sup> Transversal (cmd) <sup>2)</sup> 1) md = machine direction	≥ 20 kg ≥ 1100 N/50 mm ≥ 1100 N/50 mm	(EN 12311-2	
Tensile Strength Elongation	Rigid substrate  Longitudinal (md) <sup>1)</sup> Transversal (cmd) <sup>2)</sup> 1) md = machine direction 2) cmd = cross machine direction  Longitudinal (md) <sup>1)</sup> Transversal (cmd) <sup>2)</sup> 1) md = machine direction 2) cmd = cross machine direction	≥ 20 kg  ≥ 1100 N/50 mm ≥ 1100 N/50 mm  ≥ 12 % ≥ 12 %	(EN 12311-2)	
Tensile Strength Elongation	Rigid substrate  Longitudinal (md) <sup>1)</sup> Transversal (cmd) <sup>2)</sup> 1) md = machine direction 2) cmd = cross machine direction Longitudinal (md) <sup>1)</sup> Transversal (cmd) <sup>2)</sup> 1) md = machine direction 2) cmd = cross machine direction Longitudinal (md) <sup>1)</sup>	≥ 20 kg  ≥ 1100 N/50 mm ≥ 1100 N/50 mm  ≥ 12 % ≥ 12 % ≤0.3 %	(EN 12311-2)	
Tensile Strength	Rigid substrate  Longitudinal (md) <sup>1)</sup> Transversal (cmd) <sup>2)</sup> 1) md = machine direction 2) cmd = cross machine direction  Longitudinal (md) <sup>1)</sup> Transversal (cmd) <sup>2)</sup> 1) md = machine direction 2) cmd = cross machine direction	≥ 20 kg  ≥ 1100 N/50 mm ≥ 1100 N/50 mm  ≥ 12 % ≥ 12 %	(EN 12730) (EN 12311-2) (EN 12311-2) (EN 1107-2)	

Product Data Sheet Sarnafil® S 327-18 L (CH\_CE) October 2017, Version 01.01 020905012000181001



Tear Strength	Longitudinal (md) <sup>1)</sup>	≥ 200 N	(EN 12310-2)
	Transversal (cmd) <sup>2)</sup>	≥ 200 N	
	<ol> <li>md = machine direction</li> <li>cmd = cross machine direction</li> </ol>		
Joint Peel Resistance	no failure of the joint		(EN 12316-2)
Joint Shear Resistance	≥ 800 N/50 mm		(EN 12317-2)
Foldability at Low Temperature	≤ -25 °C	(EN 495-5)	
External Fire Performance	Broof(t1) < 20°		(EN 1187) (EN 13501-5)
Reaction to Fire	Class E	(EN ISO 11925-	2, classification to EN 13501-1)
Effect of Liquid Chemicals, Including Water	On request		(EN 1847)
Resistance to UV Exposure	Pass (> 5000 h / grade 0)		(EN 1297)
Water Vapour Transmission	μ= 15 000		(EN 1931)
Watertightness	Pass		(EN 1928)
SYSTEMS	1 433		(214 1526)

System Structure	Wide range of accessories is available example prefabricated parts, roof				
	drains, scuppers, walkway pads and decor profiles. The following accessories shall be used: Sarnafil® G 410-15 Sheet for detailing Sarnafil® Metal Sheet PVC				
				Sarnabar <sup>®</sup> / Sarnafast <sup>®</sup>	
				<ul> <li>S-Welding Cord PVC</li> </ul>	
				<ul> <li>Sarnacol® 2170 (contact adhesive)</li> </ul>	
	■ Sarna Seam Cleaner				
	■ Sarna Cleaner				
	Compatibility	Not compatible with direct contact to other plastics, example EPS, XPS, PUR, PIR or PF. Not resistant to tar, bitumen, oil and solvent containing ma			
		terials.			

# APPLICATION INFORMATION

Ambient Air Temperature	-20 °C min. / +60 °C max.
Substrate Temperature	-30 °C min. / +60 °C max.

# APPLICATION INSTRUCTIONS

# **SUBSTRATE QUALITY**

The substrate surface must be uniform, smooth and free of any sharp protrusions or burrs, etc. Sarnafil® S 327-18 L (CH CE) must be separated from any incompatible substrates by an effective separation layer to prevent accelerated ageing. Prevent from direct contact with bitumen, tar, fat, oil, solvent containing material and direct contact to other plastic materials, example expanded polystyrene (EPS), extruded polystyrene (XPS), polyurethane (PUR), polyisocyanurate (PIR) or phenolic foam (PF) as this could adversely affect the product properties.

The supporting layer must be compatible to the membrane, solvent resistant, clean, dry and free of grease and dust. Metal sheets must be degreased with Sarna Cleaner before adhesive is applied.

# **APPLICATION**

Installation works to be carried out only by Sika instructed contractors for roofing. Installation of some ancillary products, example contact adhesives / cleaners is limited to temperatures above +5 °C. Please observe information given by Product Data Sheets.

# **APPLICATION METHOD / TOOLS**

# Installation procedure:

According to the valid installation instructions for Sarnafil® S 327-18 L (CH\_CE)-types system for mechanically fastened roofing systems.

**Product Data Sheet** Sarnafil® S 327-18 L (CH\_CE) October 2017, Version 01.01 020905012000181001



# Fixing Method, linear fasting (Sarnabar®):

Unroll the Sarnafil® S 327-18 L (CH CE) membrane, overlap by 80 mm, weld immediately and fix to the substructure by means of Sarnabar®. The preferred type of fastening will be advised by Sika. The spacing of the fasteners is in accordance with the project specific calculations. The perimeter piece ends must be secured with the Sarnabar® Load Distribution Plate. For protection fasten a piece of Sarnafil® S 327-18 L (CH CE) under bar end and plate. Leave a 10 mm clearance between bar ends. Do not fasten in hole nearest bar end. Cover the bar ends with a piece of Sarnafil® S 327-18 L (CH\_CE) and weld. After installation the Sarnabar® must immediately be made watertight with a Sarnafil® S 327-18 L (CH CE) cover strip. At upstands and at all penetrations, the Sarnafil® S 327-18 L (CH CE) membrane must be secured with a Sarnabar<sup>®</sup>. The 4 mm diameter S Welding Cord protects the Sarnafil® S 327-18 L (CH CE) roof covering against tearing and peeling off by wind uplift.

# Fixing Method, spot fasting (Sarnafast®):

Sarnafil® S 327-18 L (CH\_CE) must always be installed at right angles to the deck direction. Sarnafil® S 327-18 L (CH\_CE) is fixed by means of the Sarnafast® fasteners and barbed washers/tubes along the marked line, 35 mm from the edge of the membrane. Sarnafil® S 327-18 L (CH\_CE) is overlapped by 120 mm. The spacing of the fasteners is in accordance with the project specific calculations. At upstands and at all penetrations, the Sarnafil® S 327-18 L membrane must be secured with a Sarnabar®. The 4 mm diameter S-Welding Cord protects the Sarnafil® S 327-18 L roof covering against tearing and peeling off by wind uplift.

# **Welding Method:**

Overlap seams are welded by electric hot air welding equipment, such as manual hot air welding machines and pressure rollers or automatic hot air welding machines with controlled hot air temperature.

# Recommended type of equipment:

Leister Triac for manual welding Sarnamatic® 681 for automatic welding.

Welding parameters including temperature, machine speed, air flow, pressure and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic situation prior to welding. The effective width of welded overlaps by hot air must be minimum 20 mm.

The seams must be mechanically tested with screw driver to ensure the integrity / completion of the weld. Any imperfections must be rectified by hot air welding.

# IMPORTANT CONSIDERATIONS

#### **Geographical / Climate**

Permanent ambient temperature during use is limited to +50  $^{\circ}$ C.

# **BASIS OF PRODUCT DATA**

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

# LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses

# **ECOLOGY, HEALTH AND SAFETY**

Fresh air ventilation must be ensured, when working (welding) in closed rooms.

#### REGULATION (EC) NO 1907/2006 - REACH

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w)



# **LEGAL NOTES**

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

# SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait Tel: +973 177 38188 sika.gulf@bh.sika.com gcc.sika.com



ISO 9001: Sika UAE LLC, Sika Gulf B.S.C. (c), Sika Saudi Arabia Co. Ltd, Sika Quatr LLC Sika Gulf B.S.C. (c), Sika Saudi Arabia Co. Ltd OHSAS: Sika UAE LLC, Sika Gulf B.S.C. (c)

Product Data Sheet
Sarnafil® S 327-18 L (CH\_CE)
October 2017, Version 01.01

SIKA SOUTHERN GULF

UAE / Oman / SIC Tel: +971 4 439 8200 info@ae.sika.com gcc.sika.com

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS SIKA SAUDI ARABIA

Riyadh / Jeddah / Dammam Tel: +966 11 217 6532 info@sa.sika.com gcc.sika.com

SarnafilS327-18LCHCE-en-AE-(10-2017)-1-1.pdf



020905012000181001