

BUILDING TRUST

PRODUCT DATA SHEET SikaWall[®]-115 Render

CEMENTITIOUS READY MIX PLASTER

DESCRIPTION

SikaWall[®]-115 Render is a cementitious ready mix plaster, to carry out traditional plastering works in a clean and speedy manner, while keeping a homogeneous mix. Due to its high content in additives, it has a better shrinkage control as well as workability and curing. It can be applied by a suitable plastering machine or manually.

Suitable for use in hot and tropical climatic conditions.

USES

SikaWall[®]-115 Render is recommended for internal and external plastering, ceilings, concrete surfaces, bricks, regular blocks, concrete blocks, etc. and for general filling up.

PRODUCT INFORMATION

CHARACTERISTICS / ADVANTAGES

- Ready to use, mix with water only
- Good adhesion and good mechanical properties
- Good workability
- Durable
- Traditional manual application
- Suitable plaster-spraying machines application

Composition	Portland cement, selected sand, specific additives & fibers	
Packaging	40 kg bag	
Appearance / Colour	Grey powder	
Shelf life	12 months from the production date	
Storage conditions	Store in dry conditions in original sealed undamaged packaging at temper- atures between +5 °C and +35 °C. Protect from direct sunlight, heat and moisture.	
Density	~1.50 kg/l (bulk density-powder)	
Maximum grain size	~1.70 mm	

Tensile adhesion strength	System ¹ adhesion: ≥ 1.00 N/mm ² (28d)	(EN 1542)		
	¹ System: SikaWall®-115 Render with keycoat (primer) SikaWall®-105 Rush Coat			
APPLICATION INFORMATION				
Mixing ratio	w/p=0.16-0.18 6.4 L - 7.2 L of water per 40 kg bag			
Fresh mortar density	~1.35 kg/l			

 Layer thickness
 min. 10 mm, max. 20 mm (in one layer) For higher thicknesses, application in multiple layers is possible.

 Pot Life
 ~120 min (23 °C)

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets before using any products. For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

FURTHER INFORMATION

- General best practice of rendering applies.
- On all types of external surfaces, rendering must be started 15 cm above the ground level in order to prevent the upward migration of water/salts due to capillary action of render.
- On high absorbant, rough surfacess, rush coat (keycoat) e.g. SikaWall®-105 Rush Coat, should be applied prior to application of render.
- For best results, always apply mock-up area first, as per the substrate requirements.
- Mechanically fixed steel wire mash is recommended in all areas of substrate transition (e.g. blocks to concrete).

IMPORTANT CONSIDERATIONS

- Apply only on vertical areas, without mechanical impact.
- Not to be used as concrete repair material.
- Do not apply in submerged areas.
- For application of highly absorbant substrates, like AAC blocks, contact Sika's Technical Support.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

Remove all the dust, loose particles, cement laitance, oil and grease from the surface to be

plastered/rendered. Spray sufficient amount of clean potable water to neutralize the absorption of the substrate. Allow the free water to completely evaporate before the application of SikaWall®-115 Render. Fixing of all attachments such as pipe, electrical fittings, corner beads etc. should be carried out before the rendering works.

For rendering of concrete, bonding slurry (rush coatkeycoat) should be applied to achieve mechanical bond, prior to rendering (e.g. SikaMur[®], SikaWall[®], Sika MonoTop[®] range, or mixture of sand, cement and SikaLatex[®]). Proper curing of the keycoat should be done by applying potable water 3-4 times a day for at least 3 days.

In case of dissimilar substrates, fix a steel wire mesh across the joint to prevent the formation of cracks due to movement. For straight vertical joints of masonry substrate a "V" groove cut should be made in the rendering when it is in wet condition.

MIXING

Add water according to the desired consistency and recommended mixing ratio into a clean mixing vessel before slowly adding the SikaWall®-115 Render powder. SikaWall®-115 Render is best mixed in a forced action mixer, for 2 to 3 minutes or until the mix is free of lumps, not longer than 5 minutes. Slow speed drill (maximum 500 rpm) can also be used for mixing. Normal tumble type concrete mixers are not suitable. Do not mix more material than can be placed within the pot life.

Do not add extra water or other ingredients. Mix only full bags for the best result. When applied with plastering machine, the water is manually adjusted by the flow meter. Before application, apply test area first, to set up the spray equipment. Do not add excess water during application. Always follow recommended mixing ratio. Do not re-use hardened material.

Product Data Sheet SikaWall®-115 Render November 2020, Version 03.01 021820101000000031



BUILDING TRUST

APPLICATION

- The plaster is now ready for application by machine or manually with a plastering trowel. Apply the plaster on the prepared surface at a thickness between 10 and 20 mm in one layer.
- Finish the surface with a soft synthetic sponge and a steel float.
- Let the product set properly on the surface before any curing.
- If more thickness is required, the application should be done in 2 layers. First layer should be left rough. Cure the first layer. Apply the second layer at least 48 hrs after the first one.

CURING

- Protect the new surface applied from sunshine and wind.
- The new plaster has to be cured with water for at least three days by spraying 3 to 4 times daily.

CLEANING OF EQUIPMENT

Application and mixing tools should be cleaned with water while the material is still fresh. Hardened material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait Tel: +973 177 38188 sika.gulf@bh.sika.com gcc.sika.com



C, All products are supplie under a management td, system certified to com to the requirements of LC, quality, environmental occupational health & td safety standards ISO 90 ISO 14001 and OHSAS 18001.

SIKA SOUTHERN GULF

Tel: +971 4 439 8200

UAE / Oman / SIC

info@ae.sika.com

gcc.sika.com

Product Data Sheet SikaWall®-115 Render November 2020, Version 03.01

SIKA SAUDI ARABIA Riyadh / Jeddah / Dammam Tel: +966 11 217 6532 info@sa.sika.com gcc.sika.com

SikaWall-115Render-en-AE-(11-2020)-3-1.pdf



BUILDING TRUST