

PRODUCT DATA SHEET

Sarnafil® AT-18 FSH

1.8 mm thick polymeric FPO membrane for mechanically fastened and ballasted roof waterproofing

DESCRIPTION

Sarnafil® AT-18 FSH (thickness 1.8 mm) is a premium multi-layer synthetic roof waterproofing sheet based on elastomer modified flexible polyolefin (FPO) with internal Polyester reinforcement and glass non-woven inlay and a self-healing fleece backing according to EN 13956. The product is hot air weldable, UV-stabilised with extrenal fire performance. Can be applied in all climatic zones.

USES

Sarnafil® AT-18 FSH is used as a waterproofing membrane in the following roofing applications:

- Mechanically fastened roofing systems
- Ballasted roofing systems

FEATURES

- Highly flexible membrane allows for easy application
- High durability and long service life

- Self-healing properties prevent water ingress after mechanical damage
- Hot-air welding application avoids fire risk
- White coloured membranes reduce air conditioning costs by reducing heat transmission into the building
- Dimensionally stable membrane reduces wrinkling and increases ease of application
- Increased resistance to damage through wind uplift
- Increased resistance to root penetration

CERTIFICATES AND TEST REPORTS

- CE marking and declaration of performance based on EN 13956:2012 Flexible sheets for waterproofing — Plastic and rubber sheets for roof waterproofing — Definitions and characteristics
- Root resistance testing report (FLL), Weißenstephan-Triesdorf / Germany
- Leaching test report according DIN CEN/TC 16637-2

PRODUCT INFORMATION

Composition	Flexible polyolefins (FPO)	
Packaging	Standard rolls are wrapped individually in a PE-foil.	
	Roll width	2 m
	Roll length	10 m
	Roll weight	46 kg
Refer to the current price list for available packaging variations.		
Colour	Top layer colour	beige, window grey (~RAL 7040), traffic white (~RAL 9016)
	Bottom layer colour	dark grey
Shelf life	5 years from date of production.	

Storage conditions	The Product must be stored in original unopened and undamaged sealed packaging in dry conditions and temperatures between -5 °C and +40 °C. Store in a horizontal position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to the packaging.	
Product declaration	EN 13956 - Polymeric sheets for roof waterproofing	
Visible defects	Pass	(EN 1850-2)
Length	10 m (+0.5 m / -0 m)	(EN 1848-2)
Width	2 m (+0.02 m / -0.01 m)	(EN 1848-1)
Effective thickness	1.8 mm (+0.18 mm / -0.09 mm)	(EN 1849-2)
Straightness	≤ 30 mm	(EN 1848-2)
Flatness	≤ 10 mm	(EN 1848-2)
Mass per area	2.3 kg/m ² (+0.23 kg/m ² / -0.12 kg/m ²)	(EN 1849-2)
Appearance	matt	

TECHNICAL INFORMATION

Resistance to impact	Method A, Hard support	≥ 1000 mm	(EN 12691)
	Method B, Soft support	≥ 3000 mm	
Hail resistance	Hard support	≥ 33 m/s	(EN 13583)
	Soft support	≥ 40 m/s	
Resistance to static loading	Soft support	≥ 20 kg	(EN 12730)
	Hard support	≥ 20 kg	
Resistance to root penetration	Pass		(EN 13948)
Dimensional stability	Longitudinal (MD), aged 6 hours at +80 °C	≤ 0.2 %	(EN 1107-2)
	Transversal (CMD), aged 6 hours at +80 °C	≤ 0.1 %	
Resistance to tear	Longitudinal (MD)	≥ 300 N	(EN 12310-2)
	Transversal (CMD)	≥ 300 N	
Joint peel resistance	Failure mode C, no failure of the joint.		(EN 12316-2)
Joint shear resistance	≥ 400 N/50 mm		(EN 12317-2)
Foldability at low temperature	≤ -50 °C		(EN 495-5)
External fire performance	B _{Roof} T1, roof angle < 20°	Pass	(EN 13501-5)
	B _{Roof} T4, roof angle < 10°	Pass	
Reaction to fire	Class E		(EN 13501-1)
Chemical resistance	Resistant to specific chemicals. Contact Sika Technical Services for additional information.		(EN 1847)
Effect of liquid chemicals, including water	Resistant to many chemicals. Contact Sika Technical Services for additional information.		
Exposure to bitumen	Bitumen compatibility	Pass	(EN 1928; EN 1548)
Resistance to UV exposure	> 5000 hours UV exposure	Grade 0	(EN 1297)

Artificial ageing	Pass		(EN 1297)
Diffusion resistance to water vapour	Resistance factor, Method A, tested at +23 °C and 75 % r.h.	$\mu = 190\,000$	(EN 1931)
Watertightness	Method B: at 10 kPa	Pass	(EN 1928)
Maximum tensile force	Longitudinal (MD) Transversal (CMD)	$\geq 950\text{ N/50 mm}$ $\geq 900\text{ N/50 mm}$	(EN 12311-2)
Elongation at maximum tensile force	Longitudinal (MD) Transversal (CMD)	$\geq 15\%$ $\geq 15\%$	(EN 12311-2)

APPLICATION INFORMATION

Ambient air temperature	Maximum Minimum	+60 °C -20 °C
Substrate temperature	Maximum Minimum	+60 °C -25 °C

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTATION

- Application Manual Sarnafil® AT.

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w).

APPLICATION INSTRUCTIONS

EQUIPMENT

HOT-WELDING OVERLAP SEAMS

- Electric hot-air welding equipment such as hand-held, manual hot-air welding equipment and pressure rollers
- Automatic hot-air welding machines with controlled hot-air temperature capability of a minimum +600 °C

Recommended equipment:

Manual Leister Triac
Automatic Varimat

SUBSTRATE PREPARATION

The substrate surface must be smooth and uniform. The supporting layer must be compatible with the membrane, resistant to solvents and dry.

1. Remove any sharp protrusions or burrs from the substrate.
2. If contaminants such as grease or dust are present, clean the supporting layer.

APPLICATION

IMPORTANT

Strictly follow installation procedures

Strictly follow installation procedures as defined in Method Statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

IMPORTANT

Application by trained personnel

The application of this Product must only be carried out by an applicator that is trained or approved by Sika. The applicator must also be experienced in this type of application.

FIXING METHOD - GENERAL

The waterproofing membrane is installed by loose laying – without stretching the membrane or installing under tension – with mechanical fastening in the seam overlaps or independently of overlaps. Overlap seams are hot-air welded using specialised hot-air equipment.

FIXING METHOD - SPOT FASTENING (SARNAFAST®)

1. Install the Product at right angles to the deck direction. Unroll the waterproofing membrane, overlapping it by 120 mm.

2. Fix the waterproofing membrane using Sarnafast® fasteners, barbed washers and tubes along the marked line, 35 mm from the edge of the membrane. The spacing of the fasteners must be in accordance with the project specific Sika calculations.
3. At upstands and at all penetrations, secure the Product with a Sarnabar®.
4. Use the 4 mm diameter Sarnafil® T Welding Cord to protect the roof covering against tearing and peeling off by wind uplift.

FIXING METHOD - BALLASTED SYSTEM

1. Unroll the waterproofing membrane, overlapping it by 80 mm.
2. Immediately weld the overlap seams.
3. Cover with the appropriate roof material according to the roof design and the local wind loading conditions.
4. Mechanically fix around the roof perimeter with Sarnabar® including Sarnafil® T Welding Cord to keep the membrane in place.

HOT-WELDING OVERLAP SEAMS

Overlap seams must be welded by electric hot-welding equipment. Prior to welding, welding parameters including temperature, machine speed, air flow, pressure, and machine settings must be evaluated, adapted and checked on site according to the type of equipment and the climatic conditions. The effective width of overlaps welded by hot air must be a minimum of 20 mm.

TESTING OVERLAP SEAMS

1. Mechanically test seams with a rounded-edge screwdriver to ensure the integrity and completion of the weld.
2. Rectify any imperfections using hot-air welding.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC
Sika International Chemicals LLC
Tel: +971 4 439 8200
Email: info@ae.sika.com
Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC
Riyadh / Jeddah / Dammam / Rabigh
Tel: +966 9200 22167
Email: info@sa.sika.com
Web: gcc.sika.com

Sika LLC - Oman

Sika MB LLC
Tel. +968 22 826 500
Email: info@om.sika.com
Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
Sika MB LLC
Sika International Chemicals LLC
Sika Gulf B.S.C. (c)
ISO 9001, 14001 – SGS
Sika Saudi Arabia Limited
ISO 9001, 14001 – TÜV
Sika MB Construction Chemicals LLC
Sika Construction Chemicals for Manufacturing LLC
ISO 9001 – LMS
Sika MB LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

Sarnafil® AT-18 FSH

November 2025, Version 05.01
020910012120181001