

PRODUCT DATA SHEET

SikaBit® E 15-15 HDPE XL SA

PEEL AND STICK, SELF-ADHESIVE, BITUMINOUS SHEET WATERPROOFING
MEMBRANE FOR BELOW GROUND APPLICATIONS



DESCRIPTION

SikaBit® E 15-15 HDPE XL SA is a self-adhesive bituminous sheet waterproofing membrane. It's based on a SBS modified bitumen compound on a cross-laminated HDPE film, formulated for hot and tropical climate.

USES

SikaBit® E 15-15 HDPE XL SA is a cold and post-applied self-adhesive sheet waterproofing membrane. The system is applied on existing below ground concrete structures to provide damp-proofing and waterproofing:

- On horizontal slabs and protrusions
- On single and strip foundations or slabs
- On the outside of external walls

PRODUCT INFORMATION

Packaging	1.05 m x 15 m single roll
Appearance / Colour	Supplied as sheets in rolls, on one side a black HDPE carrier film and on the other the black bitumen compound adhesive protected with a peel-release film.
Shelf life	SikaBit® E 15-15 HDPE XL SA membrane rolls have a shelf-life of 12 months from date of production.
Storage conditions	Product must be stored in original unopened and undamaged sealed packaging in dry conditions and temperatures between +5 °C and +35 °C. Store in a vertical position. Do not stack pallets of the rolls on top of each other, or under pallets of any other materials during transport or storage. Always refer to packaging.
Thickness	1.50 mm (+/- 1%) (EN 1849-1)

CHARACTERISTICS / ADVANTAGES

- Cold-applied and self-adhesive (no heating or open flames required)
- Fully bonded sheets
- Resistant to aggressive mediums in natural ground water and soil
- Controlled layer thickness
- Easy, fast and secure application, without special equipment
- Split release liner for easy application

APPROVALS / CERTIFICATES

SikaBit® E 15-15 HDPE XL SA complies with EN 13969 "Bitumen damp proof sheets including bitumen base-ment tanking sheets".

TECHNICAL INFORMATION

Resistance to Static Puncture	~220 N	(ASTM E154)	
Tensile Strength	Film Longitudinal	≥42 N/mm ²	(ASTM D882)
	Film Transversal	≥42 N/mm ²	
Elongation	Film Longitudinal	≥450 %	(ASTM D882)
	Film Transversal	≥450 %	
Resistance to Tear	Film Longitudinal	~340 N/mm	(ASTM D1004)
	Film Transversal	~310 N/mm	
Joint Peel Resistance	~2.2 N/mm (adhesion to itself)	(ASTM D1000)	
Adhesion in Peel	~2.0 N/mm (adhesion to primed substrate)	(ASTM D1000)	
Resistance to Environmental Stress Cracking	<u>Crack Bridging Ability</u>	≥ 2 mm	(ASTM C836)
Water Vapour Transmission	≤0.1 g/m ² /24h	(ASTM E96)	
Resistance to Water Penetration	Resistance to hydrostatic pressure (7 bar)	No leakage	(EN 12390-8)
Water Absorption	Film	~0.1 % (24 h)	(ASTM D570)
Service Temperature	-15 °C to +50 °C		

APPLICATION INFORMATION

Ambient Air Temperature	+5 °C min. / +50 °C max.
Relative Air Humidity	<80 %
Dew Point	The substrate temperature must be at least 3 °C above the dew point to reduce the risk of condensation and so limited adhesion
Substrate Temperature	+5 °C min. / +50 °C max.
Substrate Moisture Content	Dry, ≤ 4 % moisture content, no rising moisture

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate must be uniform, firm, smooth and free of any sharp protrusion or burrs, clean, dry, free of grease, bitumen, oil, dust and loosely adhering particles.

SUBSTRATE PREPARATION

Unevenness and surface defects (such as blowholes, voids, honeycombing, cracks, protrusions, etc.) in the surface must be pretreated and filled prior to the application, in order to prevent any subsequent damage to the membrane sheets. For more detailed information please refer to the current Method Statement for the SikaBit® E 15-15 HDPE XL SA membrane system.

A suitable primer has to be used for an optimal bond between SikaBit® E 15-15 HDPE XL SA membrane sheets and the concrete substrate, for example:

- SikaBit® P-11 SA
- SikaBit® P-12 AE

APPLICATION METHOD / TOOLS

Installation procedure may vary slightly depending on site conditions.

Priming

Apply the appropriate primer SikaBit® P-11 SA or SikaBit® P-12 AE, at the correct consumption to the prepared dry surface by brush, roller or spray and allow to dry before next application stage. Refer to the individual Product Data Sheets.

Overlaps

Side: 60mm. End: 150 mm.

Application

Once the roll is aligned, peel back a portion of the silicone release film and press the membrane onto the substrate. When securely adhered, remove the remaining release film from the roll.

Use a suitable roller (eg. steel) to press the self-adhesive membrane onto the substrate including the laps. Use the roller to push out any air bubbles out to the edge of the membrane.

Detailing

All details such as internal and external corners, upstands, vent pipes, drains, support metalwork etc. must be cut and sealed effectively. Detailing must follow the recommended guidelines and good practice for self-adhered membranes.

Protection

The membrane must be protected from damage during any ongoing site activities for example with a suitable SikaBit Protection Sheet or geotextile.

IMPORTANT CONSIDERATIONS

- The sheets must be protected immediately after completion to prevent mechanical damage. In any case don't let the membrane unprotected for more than 7 days.
- SikaBit® E 15-15 HDPE XL SA sheets are only temporarily and not permanently UV and weather resistant.
- For any connection of SikaBit® E 15-15 HDPE XL SA with other Sika membrane systems please refer to relevant product documentation, check especially regarding their bitumen compatibility or contact Sika's Technical Department for advice.
- In case of submerged structures / projects or exposure to chemicals contact Sika Technical Department prior to application.
- SikaBit® E 15-15 HDPE XL SA is not designed for use on structures under vehicular traffic.
- Low temperatures reduce the adhesion of the materials, while high temperatures soften the materials and make them more adhesive.
- Small wrinkles on the membrane surface don't affect the integrity of the waterproofing system.
- Suspend laying by self-adhesion when the temperature falls below +5°C and/or facilitate laying with hot air appliances or with a flame at temperatures below +10°C and/or in particularly humid conditions.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

This product is an article as defined in article 3 of regulation (EC) No 1907/2006 (REACH). It contains no substances which are intended to be released from the article under normal or reasonably foreseeable conditions of use. A safety data sheet following article 31 of the same regulation is not needed to bring the product to the market, to transport or to use it. For safe use follow the instructions given in the product data sheet. Based on our current knowledge, this product does not contain SVHC (substances of very high concern) as listed in Annex XIV of the REACH regulation or on the candidate list published by the European Chemicals Agency in concentrations above 0,1 % (w/w)

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

Product Data Sheet

SikaBit® E 15-15 HDPE XL SA
November 2019, Version 03.01
020704410020000017

SikaBitE15-15HDPEXLSA-en-AE-(11-2019)-3-1.pdf

