

## PRODUCT DATA SHEET

# SikaEmaco® S 443

(formerly MEmaco S 443)

SINGLE COMPONENT MICRO CONCRETE FOR CORROSION DAMAGED CONCRETE REPAIR BASED ON APPLIED NANOTECHNOLOGY

### DESCRIPTION

SikaEmaco® S 443 is a cementitious, pre-bagged, free flowing, one component, non-shrink precision micro-concrete with high early and ultimate strength. Suitable for use in hot and tropical climatic conditions.

### USES

SikaEmaco® S 443 precision micro-concrete is used for repair and grouting in various applications such as:

- Structural repair of deteriorated concrete
- Columns in precast construction
- Casting sections or members where the volumes required are too large for conventional grouts, and too small and inaccessible for normal concreting applications.
- Cavities, gaps and recesses
- Re-profiling of damaged concrete members and re-profiling of pile tops using formwork for both pouring and pumping techniques.

### FEATURES

SikaEmaco® S 443 is an easy to use precision micro-concrete requiring only the addition of water. It offers the following beneficial properties:

- Easy to mix
- Very good flow characteristics
- Adjustable consistency
- Moderate heat of hydration
- Shrinkage compensated
- High final strength
- Non-flammable
- Vapour permeable
- Compatible with the properties of typical concrete

### PRODUCT INFORMATION

<b>Composition</b>	Portland cement, selected fillers and aggregates, special additives
<b>Packaging</b>	25 kg bag
<b>Appearance and colour</b>	Grey powder
<b>Shelf life</b>	12 months from date of production
<b>Storage conditions</b>	Store in original unopened packaging in a cool and dry condition between +5 °C and +35 °C. Protect from direct sunlight, heat and moisture.

## TECHNICAL INFORMATION

Compressive strength	+25 °C	28 Days	(BS EN 12190)
	w/p = 0.13	≥ 65 N/mm <sup>2</sup>	
Chloride ion permeability	Low		(AASHTO T 277 93) (ASTM C 1202)

## APPLICATION INFORMATION

Fresh mortar density	~2.3 kg/l (25 °C)		
Yield	~12.2 L / 25 kg bag		
Layer thickness	Min. 15 mm per pour Max. 200 mm per pour Note: For repair areas greater than 200 mm, aggregate "bulking" is required.		
Ambient air temperature	+5 °C min. / +35 °C max.		
Mixing ratio	<b>Consistency</b>	<b>L water per bag</b>	<b>Water / Powder Ratio</b>
	Flowable	3.0 - 3.5 per 25 kg bag	0.12 - 0.14
Substrate temperature	+5 °C min. / +35 °C max.		

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER DOCUMENTATION

General Method Statement (GMS)

## IMPORTANT CONSIDERATIONS

- Ensure formwork is secure and watertight to prevent movement and leaking during placing and curing.
- At high temperatures, use chilled water for mixing to keep the grout temperature below +32°C.
- In hot weather, base plates and foundations must be shaded from direct sunlight. Condition the bags below 30°C prior to use.
- When maximum thickness exceeds 200 mm, the addition of dry, clean coarse aggregates is required (Sikadur®-510 AE or SikaEmaco® FL 100) up to 20 kg per each 50 kg of the dry micro-concrete powder. Trials are recommended to confirm suitability of aggregates to be employed.
- For additional information on SikaEmaco® S 443 or other grouting materials contact Sika Technical Department.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY / PRE-TREATMENT

#### Concrete:

The repair area should be regular in shape with no sharp returns or internal corners and should be delineated with a 20 mm deep saw cut. The concrete shall be thoroughly clean, rough, free from dust, loose material, surface contamination and materials which reduce bond or prevent suction or wetting by repair materials. De-laminated, weak, damaged and deteriorated concrete and where necessary sound concrete shall be removed by suitable means. Absorbent surfaces should be saturated thoroughly with clean water.

The application of a suitable bonding agent, such as Sikadur®-32 LP, Sikadur® ADH 1414 or SikaTop® Armatec®-110 EpoCem®, will improve adhesion on large areas or where particularly dense concrete substrates are involved.

### Steel Reinforcement:

Rust, scale, mortar, concrete, dust and other loose and deleterious material which reduces bond or contributes to corrosion shall be removed. Surfaces shall be prepared using abrasive blast cleaning techniques or high pressure water-blasting to SA 2 (ISO 8501-1). Embedded steel reinforcing should be treated with a suitable anticorrosion coating such as SikaTop® Armatec®-110 EpoCem® or SikaEmaco®-8100 AP.

Reference shall be made to EN 1504-10 for specific requirements.

### MIXING

Add water according to the desired consistency into a clean mixing vessel before slowly adding the SikaEmaco® S 443 powder. SikaEmaco® S 443 is best mixed in a forced action mixer, for 3 to 5 minutes or until the mix is free of lumps. Slow speed drill (maximum 500 rpm) can be also used for mixing. Normal tumble type concrete mixers are not suitable. Do not mix more grout than can be laced within 15 to 20 minutes. Do not add extra water or other ingredients. Mix only full bags for the best result.

**Note: Always start with the minimum recommended quantity of water (water/powder ratio), only if required, gradually add water to desired consistency. Do not exceed maximum allowed limit of water per bag weight.**

### APPLICATION

Before pouring let the mixed grout stand for approximately 5 minutes after mixing to allow entrapped air to escape. Pour into the prepared area such that the grout has the shortest distance to travel. Ensure that air displaced by the grout is allowed to escape. When carrying out the base plate grouting, ensure a sufficient head of pressure to keep the mortar flowing. All exposed areas of the mortar surface should be kept as small as possible.

### CURING TREATMENT

Treatment of exposed surfaces with Sika® Antisol® range curing compound, is highly recommended for large areas of application. Use other approved curing methods such as polyethylene sheeting or wet hessian only for small exposed areas. Do not commence fogging until final set has been reached.

### CLEANING OF EQUIPMENT

Clean equipment and mixer immediately after application with water. Hardened material can only be removed mechanically.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

**Sika Gulf B.S.C. (c)**  
Tel: +973 177 38188  
Email: info@bh.sika.com  
Sika Kuwait Cons. Mat. & Paints Co WLL  
Tel: +965 22 282 296  
Email: sika.kuwait@kw.sika.com  
Web: gcc.sika.com

**Sika UAE LLC**  
Sika MB Construction Chemicals LLC  
Sika International Chemicals LLC  
Tel: +971 4 439 8200  
Email: info@ae.sika.com  
Web: gcc.sika.com

**Sika Saudi Arabia Limited**  
Sika Construction Chemicals for Manufacturing LLC  
Riyadh / Jeddah / Dammam / Rabigh  
Tel: +966 12 692 7079  
Email: info@sa.sika.com  
Web: gcc.sika.com

**Sika LLC - Oman**  
Master Builders Solutions LLC (part of Sika)  
Tel: +968 22 826 500  
Email: info@om.sika.com  
Web: gcc.sika.com



ISO 9001, ISO 14001, ISO 45001 - SGS  
- Sika UAE LLC  
- Sika International Chemicals LLC  
- Sika Gulf B.S.C. (c)  
- Sika MB Construction Chemicals LLC  
- Sika Saudi Arabia Limited  
- Sika MB Construction Chemicals for Manufacturing LLC  
- Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



**Product Data Sheet**  
**SikaEmaco® S 443**  
October 2024, Version 03.01  
02030200000002097

SikaEmacoS443-en-AE-(10-2024)-3-1.pdf

