

PRODUCT DATA SHEET

Sikafloor®-31 PurCem® (AE)

WATER BASED POLYURETHANE CEMENTITIOUS HYBRID COATING

DESCRIPTION

Sikafloor®-31 PurCem® (AE) is a multi-component, water-based coloured polyurethane hybrid flooring coating. It has a matt, impervious, chemical resistant, hard wearing surface.

Suitable for use in hot and tropical climatic conditions.

USES

Sikafloor®-31 PurCem® (AE) may only be used by experienced professionals.

Sikafloor®-31 PurCem® (AE) is used as top and wear coat layer in Sikafloor® PurCem® anti-slip system build-ups and coating on horizontal surfaces

CHARACTERISTICS / ADVANTAGES

- Good wear resistance
- High mechanical resistance
- Good chemical resistance
- Non tainting / odourless
- VOC free
- Can be applied to substrates with high moisture content (7 days old or mature damp concrete)

APPROVALS / CERTIFICATES

- EN1186, EN 13130, and prCEN/TS 14234 standards, and the Decree on Consumer Goods, representing the conversion of directives 89/109/EEC, 90/128/EEC and 2002/72/EC for contact with food stuffs, according to test report by ISEGA, 32758 U11 and 32759 U11, both dated December 6th, 2011. (Tests performed on Sikafloor® -20/21/22/29 and 31 PurCem® in standard and LP versions).
- Campden and Chorleywood Food Research Association, reference S/REP/125424/1a and 2a, dated 8th February, 2012
- Liquid water transmission rate test report from the Technology Centre, reference 15456 dated January 25th, 2012
- Impact resistance values tested at PRA, reference no. 75221-151, dated January 11th, 2012

PRODUCT INFORMATION

Composition	Water-based polyurethane cement hybrid	
Packaging	Part A	1.50 kg plastic drums
	Part B	1.40 kg plastic jerry can
	Part D	1.80 kg plastic bags
	Part A + B + D	4.70 kg ready to mix units
Appearance / Colour	Part A	White liquid
	Part B	Brown liquid
	Part D	Colourpack as per list below
	Available colours: beige, maize yellow, dusty grey, oxide red, grass green, slate grey, traffic grey.	

Shelf life	Part A	12 months from date of production. Protect from freezing.
	Part B	12 months from date of production. Protect from freezing.
	Part D	12 months from date of production. Must be protected from humidity.

Storage conditions The package must be stored properly in original, unopened and undamaged sealed packaging, in dry conditions at temperatures between +5 °C and +30 °C.

Density Part A + B + D mixed: ~1.25 kg/l (+20 °C)

TECHNICAL INFORMATION

Shore D Hardness ~80 (ASTM D 2240)

Tensile Adhesion Strength > 2.0 N/mm² (failure in concrete) (EN 1542)

SYSTEMS

Systems	Please refer to the System Data Sheet of:	
	Sikafloor® PurCem® HB-21	Heavy to medium duty, broadcasted, light anti-slip PUCEM, hybrid screed
	Sikafloor® PurCem® HB-22	Heavy to medium duty, broadcasted, medium anti-slip PUCEM, hybrid screed
	Sikafloor® PurCem® HB-23	Heavy to medium duty, broadcasted, high anti-slip PUCEM, hybrid screed
	Sikafloor® -29 PurCem® (AE)	As a coating for coving mortar

APPLICATION INFORMATION

Mixing Ratio Mix full units only.

Ambient Air Temperature +10 °C min. / +40 °C max.

Consumption ~0.4 - 1.0 kg/m² (depending on the system build-up)

Relative Air Humidity 85 % max.

Dew Point Beware of condensation!
The substrate and uncured floor must be at least 3 °C above dew point to reduce the risk of condensation or blooming on the floor finish.

Substrate Temperature +10 °C min. / +40 °C max.

Substrate Moisture Content Can be installed on substrates with higher moisture content. No ponding water. Check rising moisture. The substrate needs to be visibly dry and have adequate pull-off strength min 1.5 N/mm².

Pot Life	Temperatures	Time
	+10 °C	~35 - 40 min
	+20 °C	~22 - 25 min
	+30 °C	~15 - 18 min
	+35 °C	~12 - 15 min

Curing Time

Before overcoating Sikafloor®-31 PurCem® (AE) allow:

Substrate temperature	Minimum	Maximum
+10 °C	16 h	72 h
+20 °C	8 h	48 h
+30 °C	4 h	24 h
+35 °C	4 h	24 h

Times are approximate and will be affected by changing ambient and substrate conditions, particularly temperature and relative humidity.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY / PRE-TREATMENT

The surface must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings and surface treatments, etc. All dust, loose and friable material must be completely removed from all surfaces before application of the product, preferably by vacuum. Pull of strength shall not be less than 1.5 N/mm². If in doubt apply a test area first.

MIXING

Premix Part A with a low speed electric stirrer and then add Part B and mix for 30 seconds, until a uniform colour is achieved.

Use a double paddle (axis) mixer and gradually add Part D (pigment powder) to the mixed resin. Allow Part D to blend for further 2 minutes minimum, to ensure complete mixing and a uniform moist mix is obtained. During the operations, scrape down the sides and bottom of the container with a flat or straight edge trowel at least once (Parts A + B + D) to ensure complete mixing.

Mixing Tools

A low speed electric stirrer (300 - 400 r.p.m.) and an Exomixer-type mixing paddle suited to the size of the mixing container to minimise the air entrapment.

APPLICATION

On smooth screeds apply the mixed Sikafloor®-31 PurCem® (AE) using a short or medium nap roller directly from a paint tray. On broadcasted screeds pour the material and spread it using a squeegee and then back-roll the excess using a medium knap roller.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with Thinner C immediately after use. Hardened / cured material can only be mechanically removed.

FURTHER INFORMATION

- Sikafloor® PurCem® Method Statement
- Sika® Method Statement Mixing and Application of Flooring Systems
- Sika® Method Statement Surface Evaluation & Preparation
- Sikafloor® PurCem® System Data Sheets

IMPORTANT CONSIDERATIONS

- Do not apply to PCC (polymer modified cement mortars) that may expand due to moisture when sealed with an impervious resin.
- Always ensure good ventilation when using Sikafloor®-31 PurCem® (AE) in a confined space, to prevent excessive ambient humidity.
- Freshly applied Sikafloor®-31 PurCem® (AE), must be protected from damp, condensation and direct water contact (rain) for at least 24 hours.
- Protect the substrate during application from condensation from pipes or any overhead leaks.
- Do not apply to cracked or unsound substrates.
- Always allow a minimum of 48 hours after product application prior to placing into service in proximity with food stuffs.
- Products of the Sikafloor® PurCem® product range are subject to discolouration when exposed to UV radiation. Extend depends on colour. There are no measurable losses of any properties when this occurs and it is a purely aesthetical matter. Products can be used outside provided the change in appearance is acceptable by the customer.
- In some slow curing conditions, soiling of the surface may occur when opened to foot traffic, even though mechanical properties have been achieved. It is advised to remove dirt using a dry mop or cloth. Avoid scrubbing with water for the first three days.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA SOUTHERN GULF
UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA NORTHERN GULF
Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SAUDI ARABIA
Riyadh / Jeddah / Damman
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied
under a management
system certified to conform
to the requirements of the
quality, environmental and
occupational health &
safety standards ISO 9001,
ISO 14001 and OHSAS
18001.

Sikafloor-31PurCemAE-en-AE-(06-2018)-2-1.pdf

Product Data Sheet
Sikafloor®-31 PurCem® (AE)
June 2018, Version 02.01
020814020030000008

