

PRODUCT DATA SHEET

Sikasil[®]-122 Universal

General Purpose Acetoxy Cure Silicone Sealant

DESCRIPTION

Sikasil[®]-122 Universal is a versatile, one-part acetoxy silicone sealant, which cures with atmospheric moisture to form an elastic rubber-like seal.

Suitable for use in hot and tropical climatic conditions.

USES

The use of Sikasil[®]-122 Universal includes, but is not limited to:

- Glazing and weatherproofing applications on non-porous substrates.
- For sanitary or other sealing applications where mildew resistance is required.
- Glass, glazed surfaces, ceramic and porcelain, coated metal substrates and for tile parameter joints.
- For inside and outside applications.

FEATURES

- Contains fungicide
- Low shrinkage
- Weathering and UV resistance
- Good adhesion to a variety of non-porous substrates
- Good elasticity and flexibility
- Easy application

TECHNICAL INFORMATION

Shore A hardness	~ 23 (after 28 d)	(ASTM D2240)
Tear strength	~ 3.5 N/mm	(ISO 37)
Service temperature	-40 °C min. to +100 °C max.	
Joint design	The joint width must be designed to suit the joint movement required and the movement capability of the sealant. For joints ≥ 10 mm and ≤ 20 mm wide, a joint depth of 10 mm is recommended. For larger joints please contact our Technical Department.	
Elongation at break	~ 700%	(ASTM D412)

PRODUCT INFORMATION

Composition	Acetoxy silicone
Packaging	280 mL cartridges, 12 cartridges per box
Shelf life	Sikasil®-122 Universal has a shelf life of 12 months from the date of production, if it is stored properly in undamaged, original, sealed packaging, and if the storage conditions are met.
Storage conditions	Sikasil®-122 Universal shall be stored in dry conditions, protected from direct sunlight and at temperatures between +5 °C and +25 °C.
Colour	Clear, white, grey and black
Density	~ 1.0 kg/l (ISO 1183-1)

APPLICATION INFORMATION

Consumption	Joint length (m) per 280 mL	Joint width (mm)	Joint depth (mm)
	~2.70	10	10
	~1.80	15	10
	~1.35	20	10
Sag flow	<2 mm		
Ambient air temperature	+5 °C min. / +40 °C max. (min. 3 °C above dew point temperature)		
Substrate temperature	+5 °C min. / +40 °C max.		
Tooling time	~ 10 minutes (23°C)		

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTATION

- Safety Data Sheet
- Pre-treatment Chart Sealing and Bonding

IMPORTANT CONSIDERATIONS

- Do not use Sikasil®-122 Universal on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might bleed oils, plasticizers or solvents that could attack the sealant.
- Do not use in totally confined spaces, Sikasil®-122 Universal requires atmospheric moisture to cure.
- Sikasil®-122 Universal is not recommended for porous substrates, such as concrete, stone, marble and granite. Bleeding can occur when Sikasil®-122 Universal is used on these substrates.
- Sikasil®-122 Universal is not recommended for use on submerged joints, joints where physical abuse or abrasion are likely to occur, structural glazing or insulated glazing, and food contact applications.
- Do not use Sikasil®-122 Universal for medical or pharmaceutical uses.
- Acetic acid released during the curing of Sikasil®-122 Universal can cause the corrosion of mirror silver and sensitive metals such as copper, brass and lead.
- Do not use Sikasil®-122 Universal on alkaline surfaces such as concrete, plaster and brick.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles. Paint, cement laitance and other poorly adhering contaminants must be removed.

SUBSTRATE PREPARATION

Sikasil®-122 Universal adheres without primers and/or activators. However, for optimum adhesion and critical, high performance applications, such as on multi-story buildings, highly stressed joints, extreme weather exposure or water immersion, the following priming and/or pre-treatment procedures shall be followed: Aluminium, anodised aluminium, stainless steel, galvanised steel, powder coated metals or glazed tiles have to be cleaned and pre-treated using Sika® Aktivator-205, wiped on with a clean towel. Before sealing, allow a flash-off time of >15 minutes (<2 hours). Other metals, such as copper, brass and titanium-zinc, also have to be cleaned and pre-treated using Sika® Aktivator-205, wiped on with a clean towel. After the necessary flash-off time, use a brush to apply Sika® Primer-3 N and allow a further flash-off time of >30 minutes (<4 hours) before sealing the joints. PVC has to be cleaned and pre-treated using Sika® Primer-215 applied with a brush. Before sealing, allow a flash-off time of >30 minutes (<4 hours). Glass shall be cleaned with isopropyl alcohol before application.

Note: Primers are adhesion promoters. They are neither a substitute for the correct cleaning of a surface, nor do they improve the strength of the surface significantly. For more detailed advice and instructions please contact our Technical Department.

APPLICATION METHOD / TOOLS

Sikasil®-122 Universal is supplied ready to use. After the necessary substrate preparation, insert a suitable backing rod to the required depth and apply any primer if necessary. Insert a cartridge into the sealant gun and extrude Sikasil®-122 Universal into the joint making sure that it comes into full contact with the sides of the joint and avoids any air entrapment. Sikasil®-122 Universal sealant must be firmly tooled against the joint sides to ensure adequate adhesion. It is recommended to use masking tape where exact joint lines or neat lines are required. Remove the tape within the skin time. Do not use tooling products containing solvents.

CLEANING OF EQUIPMENT

Clean all tools and application equipment immediately after use with Sika® Remover-208. Once cured, residual material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188

Email: info@bh.sika.com

Sika Kuwait Cons. Mat. & Paints Co WLL

Tel: +965 22 282 296

Email: sika.kuwait@kw.sika.com

Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC

Sika International Chemicals LLC

Tel: +971 4 439 8200

Email: info@ae.sika.com

Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC

Riyadh / Jeddah / Dammam / Rabigh

Tel: +966 12 692 7079

Email: info@sa.sika.com

Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC (part of Sika)

Tel. +968 22 826 500

Email: info@om.sika.com

Web: gcc.sika.com



ISO 9001, 14001, 45001 + S&E
- Sika UAE LLC
- Sika International Chemicals LLC
- Sika Gulf B.S.C. (c)
ISO 9001, 14001 + S&E
- Sika Saudi Arabia Limited
ISO 9001, 14001 + S&E
- Sika MB Construction Chemicals LLC
- Sika Construction Chemicals for Manufacturing LLC
- Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

Sikasil®-122 Universal

November 2024, Version 02.01

020514030000000213