

## PRODUCT DATA SHEET

# Sikaflex<sup>®</sup> CR 460

(formerly MSeal CR 460)

Two-part, polyurethane, chemical and traffic resistance joint filler

## DESCRIPTION

Sikaflex<sup>®</sup> CR 460 is a two-part polyurethane joint filler. It is pourable and self-leveling. The Product is used together with Sika<sup>®</sup> Ucrete<sup>®</sup> P 460, a two-part clear polyurethane primer.

## USES

Sikaflex<sup>®</sup> CR 460 is used for sealing induced joints in resin floors and around stainless steel channels and gullies. It is used in environments with heavy traffic and high levels of heat and chemical exposure.

Sikaflex<sup>®</sup> CR 460 is used for:

- Industrial floors and warehouses
- Food industry
- Civil engineering structures
- Metal industry

## FEATURES

- Long working life
- Very good resistance to specific chemicals
- Very good mechanical and wear resistance
- Hygienic
- Non-tainting after curing
- Easy application

## PRODUCT INFORMATION

Composition	Polyurethane
Packaging	3.0 kg
Shelf life	12 months from date of production
Storage conditions	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to the packaging. Refer to the current Safety Data Sheet for information on safe handling and storage.
Density	1.6 kg/L (ISO 1183-1)

## TECHNICAL INFORMATION

Shore A hardness	Cured 28 days at +20 °C	~80	(DIN 53505)
Tensile strength	Cured 28 days at +20 °C	1.6–2.0 N/mm <sup>2</sup>	(EN ISO 527-3)

## Chemical resistance

Sikaflex® CR 460 has very good resistance to:

- Dilute mineral acids: chromic, hydrochloric, nitric, phosphoric and sulphuric
- Dilute alkalis
- Most dilute organic acids
- Fats, oils and sugars
- Mineral oils, most hydrocarbons, fuels, alcohols and salts
- Cleaning agents and detergents

Sikaflex® CR 460 has limited resistance to:

- Concentrated mineral
- Organic acids
- Alkalis

Sikaflex® CR 460 is not resistant to:

- Aggressive organic solvents such as xylene and acetone

Contact Sika Technical Services for additional information.

---

## Elongation at break

Cured 28 days at +20 °C 20–23 %

(EN ISO 527-3)

---

## APPLICATION INFORMATION

---

### Consumption

Joint width	Joint depth	Coverage in g/linear meter	Coverage in linear meter/unit
7 mm	5 mm	55 g/m	55 m/unit
10 mm	6 mm	100 g/m	30 m/unit
15 mm	10 mm	235 g/m	13 m/unit
20 mm	10 mm	320 g/m	9 m/unit
30 mm	15 mm	720 g/m	4 m/unit

---

### Sag flow

20 mm profile tested at < 2 mm  
+23 °C

(EN ISO 7390)

---

### Material temperature

Maximum +40 °C  
Minimum +5 °C

---

### Ambient air temperature

Maximum +40 °C  
Minimum +5 °C

---

### Dew point

The substrate temperature must be at least +3 °C above dew point to reduce the risk of condensation decreasing adhesion.

---

### Substrate temperature

Maximum +40 °C  
Minimum +5 °C

---

### Backing material

Use closed cell, polyethylene foam backing rod.

---

### Pot Life

100–120 minutes

---

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

**Poor adhesion due to inadequate surface preparation**  
Note: Primers are adhesion promoters. Primers cannot replace proper surface preparation and surface cleaning.

1. Do not use primers for improving poorly prepared or poorly cleaned joint surfaces.

## IMPORTANT

### Poor adhesion due to incorrect priming procedure

Incorrectly defined or uncontrolled priming procedures may lead to a variation in Product performance.

1. Test adhesion on project-specific substrates and agree on procedures with all parties before full project application. For more information contact Sika Technical Services.

The substrate must be sound, clean, dry and free of contaminants such as dirt, oil, grease, cement laitance, sealant residues and poorly bonded coatings which could affect adhesion of the primer and sealant.

The substrate must be of sufficient strength to withstand the stress induced by the sealant during movement.

1. Use techniques such as wire brushing, grinding, grit blasting or other suitable mechanical methods to remove all weak substrate material.
2. Repair all damaged joint edges with suitable Sika repair products.
3. Remove dust, loose and friable material from all surfaces before applying the sealant.

Use the following priming or pre-treatment procedures to ensure optimum adhesion and joint durability, or if the Product is used for high-performance applications such as joints on multi-storey buildings, highly stressed joints, or joints exposed to extreme weather.

## MIXING

1. Using a slow speed stirrer, mix the content of the Part A pail for 30 seconds to disperse any separated material.
2. Add the content of the Part B.
3. **IMPORTANT** Do not mix excessively to minimise air entrainment. Mix the two parts for a further 1–2 minutes.
4. Ensure that no undispersed Part A is left on the side of the pail.

## APPLICATION

### IMPORTANT

#### Strictly follow installation procedures

Strictly follow installation procedures as defined in Method Statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

1. Apply the primer to the substrate using a brush. A thin layer ( $\pm 100 \mu\text{m}$ ) should be applied to the joint edges.
2. While the Sika® Ucrete® P 460 is still tacky (30 minutes to 2 hours, depending on the temperature), pour in the mixed Product to fill the joint flush to the surface. The Product can be applied on angled surfaces up to 2 % without slumping.
3. When the primer has become tack-free, apply a

second coat before pouring the Product to ensure proper bonding.

4. Use a spatula to smooth the surface and remove trapped air.

## CLEANING OF EQUIPMENT

Clean all tools and application equipment immediately after use with Sika® Remover-208 or Sika® Cleaning Wipes-100. Once cured, hardened material can only be removed mechanically.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Gulf B.S.C. (c)

Tel: +973 177 38188

Email: info@bh.sika.com

Sika Kuwait Cons. Mat. & Paints Co WLL

Tel: +965 22 282 296

Email: sika.kuwait@kw.sika.com

Web: gcc.sika.com

### Sika UAE LLC

Sika MB Construction Chemicals LLC

Sika International Chemicals LLC

Tel: +971 4 439 8200

Email: info@ae.sika.com

Web: gcc.sika.com

### Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC

Riyadh / Jeddah / Dammam / Rabigh

Tel: +966 12 692 7079

Email: info@sa.sika.com

Web: gcc.sika.com

### Sika LLC - Oman

Master Builders Solutions LLC (part of Sika)

Tel. +968 22 826 500

Email: info@om.sika.com

Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS  
- Sika UAE LLC  
- Sika International Chemicals LLC  
- Sika Gulf B.S.C. (c)  
- Sika Saudi Arabia Limited  
- Sika MB Construction Chemicals for Manufacturing LLC  
- Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



### Product Data Sheet

Sikaflex® CR 460

November 2024, Version 02.01

02051500000002008

