

PRODUCT DATA SHEET

SikaInject®-233

(formerly MInject 1335)

PU-Based 1-Component Flexible Injection Foam

DESCRIPTION

SikaInject®-233 is solvent free, single component polyurethane foam. Suitable for use in hot and tropical climatic conditions.

USES

SikaInject®-233 may only be used by experienced professionals.

- Pre-injection of cracks and joints in concrete
- Stopping of flowing water / leaking water through voids, cracks and joints in concrete structures
- Cavity-filling (water bearing)

FEATURES

- Reacts in moist surroundings.
- Good bonding to wet surfaces.
- Stops running water.

PRODUCT INFORMATION

Packaging	1 L kit: 1.055 kg (Base resin) 0.105 kg (CAT, 10 %, = maximum recommended) Note: Accelerator (CAT) dosage can be varied to suite site conditions.
Colour	Yellowish
Shelf life	12 months from date of production
Storage conditions	Store in original, unopened and undamaged sealed packaging in dry conditions at temperature between +5 °C and +35 °C
Density	~1.16 kg/l (20 °C)
Viscosity	~700 - 900 cps (25 °C)

TECHNICAL INFORMATION

Expansion	~20x – 30x (Max. 10 % CAT)
------------------	----------------------------

APPLICATION INFORMATION

Reaction time

SikaInject®-233 / CAT				
Values with 10 % Cat				
Initial Temperature (°C)	+5	+10	+15	+20
Reaction Start (sec)	130	65	30	15
Reaction End (sec)	350	250	120	60
Free Foaming Factor	20	25	25	30

- Reaction time depends not only by the temperature of the structure, but also by the temperature of the product itself
- For filling of large voids it is recommended to apply in layers
- The examples of reaction times with the maximum accelerator dosage (see table) have been measured in the laboratory
- However, it is advisable to check the required reaction time on site
- Site trials should always be performed prior to commencing of the works

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LIMITATIONS OF USE

SikaInject®-233 is generally used for the temporary stopping of high water infiltration. To achieve permanent watertight crack sealing, the subsequent injection of SikaInject®-232 is recommended.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

EQUIPMENT

Use injection pumps suitable for single part injection products.

APPLICATION

WET CONDITIONS:

- Add 2 % – 10 % CAT (depending on the required reaction time) to SikaInject®-233 (base resin)
- Mix quickly and thoroughly
- Inject this mixture through a 1-component injection pump
- Moisture / water in ground or structure will initiate the foaming reaction

DRY CONDITIONS:

- Flush cracks and voids with water prior to injecting
- Follow the standard procedure as in wet conditions

CLEANING OF EQUIPMENT

Clean all tools and application equipment as soon as possible and in accordance the Product Data Sheet for the Sika® Injection Cleaning System. Alternatively Sika® Colma Cleaner can be used to remove any polyurethane residue immediately after use. Do not leave Sika® Colma Cleaner in the injection pump. Hardened / cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188

Email: info@bh.sika.com

Sika Kuwait Cons. Mat. & Paints Co WLL

Tel: +965 22 282 296

Email: sika.kuwait@kw.sika.com

Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC

Sika International Chemicals LLC

Tel: +971 4 439 8200

Email: info@ae.sika.com

Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for

Manufacturing LLC

Riyadh / Jeddah / Dammam / Rabigh

Tel: +966 9200 22167

Email: info@sa.sika.com

Web: gcc.sika.com

Sika LLC - Oman

Sika MB LLC

Tel. +968 22 826 500

Email: info@om.sika.com

Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
Sika MB LLC
Sika International Chemicals LLC
Sika Gulf B.S.C. (c)
ISO 9001, 14001 – SGS
Sika Saudi Arabia Limited
ISO 9001, 14001 – TÜV
Sika MB Construction Chemicals LLC
Sika Construction Chemicals for Manufacturing LLC
ISO 9001 – LMS
Sika MB LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

SikaInject®-233

January 2025, Version 01.03

020707010020000079