

PRODUCT DATA SHEET

Sikament® RB 3250 SA

WATER REDUCING SUPERPLASTICISING ADMIXTURE FOR THE PRODUCTION OF WORKABLE CONCRETE

DESCRIPTION

Sikament® RB 3250 SA is a liquid admixture for concrete based on sulphonated naphthalene. The product may be used to effect substantial water reductions or to produce workable concrete with normal setting times.

USES

- Production of workable ready mixed concrete.
- Low water/cement ratio concrete.
- In complicated formwork or with congested reinforcement.

FEATURES

- Powerful plasticising action reduces or eliminates the need for compaction.
- Increased compressive, tensile and flexural strength can be achieved as a benefit of water reduction.

CERTIFICATES AND TEST REPORTS

Sikament® RB 3250 SA SA follows the requirements of ASTM C494; Types B, D & G and BS EN 934-2

PRODUCT INFORMATION

Composition	Sulphonated naphthalene.	
Packaging	210 L drum, 1000 L flowbin or bulk supply in tanker	
Appearance and colour	Dark brown/black liquid	
Shelf life	12 months from date of production if stored properly	
Storage conditions	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5°C and +45°C. Mix well before using.	
Density	~1.20 kg/l (+25°C)	
Total chloride ion content	Nil	(EN 934-2)

TECHNICAL INFORMATION

Concreting	guidance
COLLCIENTS	guiualice

The standard rules of good concreting practice for production and placing must be observed when using Sikament® RB 3250 SA in concrete. Refer to relevant standards. Fresh concrete must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Use Sika® Antisol® products as a curing agent or apply wet hessian.

APPLICATION INFORMATION

Recommended dosage

Sikament® RB 3250 SA is normally dispensed at a rate of 0.7-2.3 litres per 100kg of cementitious materials. Other dosages may be used, depending on the mix design, raw materials, climatic conditions and concrete requirements. Trial mixes must be performed to establish the exact dosage rate required.

Compatibility

Sikament® RB 3250 SA is suitable for mixes containing all types of cement and supplementary cementitious materials such as: Microsilica (Silica Fume), Fly Ash (PFA), GGBS (ground granulated blast furnace slag) and the following Sika products:

- SikaPump®
- Sika®FerroGard®
- SikaFume®
- SikaFiber®
- Sika® Aer
- Sika®Stabilizer
- SikaControl®

We recommend to perform trial mixes to establish the required performance when combining Sikament® RB 3250 SA with the above products or other admixtures. Sikament® RB 3250 SA should not be premixed with any other admixtures. If other admixtures are to be used, those should be dispensed separately. Please consult our Sika Technical Department for further assistance.

Dispensing

Sikament® RB 3250 SA is introduced into the mixer together with mixing water. The plasticizing effect or water reduction wil be higher if Sikament® RB 3250 SA is added to the concrete after 50-70% of the mixing water has been added. The addition of Sikament® RB 3250 SA to dry aggregate or cement is not recommended.

BASIS OF PRODUCT DATA

 All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Before pouring, suitability tests on the fresh concrete must be carried out. With high workability mixes take special care that all formwork is properly installed and secured. If frozen and/or if precipitation has occurred, it may only be used after thawing slowly at room temperature and intensive mixing. When using Sikament® RB 3250 SA a suitable concrete mix must be designed for the local material sources and trial mixes performed to verify suitability. When accidental overdosing occurs the set retarding effect and workability increases along with bleeding. Additional air may also be entrained. During this period the concrete must be kept moist in order to prevent premature drying out.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

Product Data Sheet Sikament® RB 3250 SA December 2024, Version 01.01 021302011000004110



LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC Sika International Chemicals LLC Tel: +971 4 439 8200 Email: info@ae.sika.com Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC Riyadh / Jeddah / Dammam / Rabigh Tel: +966 12 692 7079 Email: info@sa.sika.com Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC (part of Sika) Tel. +968 22 826 500 Email: info@om.sika.com Web: gcc.sika.com



SO 9601, 14031, 45901 – 565: Sits UNELLC Sits Lovel State Terminal LLC Sits Cost 55.0. 80 50 9601, 14001 – 565: Sits South Anabla United 50 9601, 14003 – 150: Sits Most Grantsruction Chemicals LLC Sits Construction Chemicals for Mostaficturing LLC Manter Builders Soldstons LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



SikamentRB3250SA-en-AE-(12-2024)-1-1.pdf



Product Data Sheet Sikament® RB 3250 SA December 2024, Version 01.01 021302011000004110