

## PRODUCT DATA SHEET

# Sika® Separol® W-320

### DESCRIPTION

Sika® Separol® W-320 is a ready to use, solvent free mould release agent. It is an emulsion, based on a refined mineral oil.

### USES

Sika® Separol® W-320 can be applied on sites and in precast plants.

It has been specially developed for use on:

- Smooth non-absorbent formwork
- Absorbent formwork
- Heated formwork (up to +70°C)

Sika® Separol® W-320 is also suitable for:

- Textured formwork

### CHARACTERISTICS / ADVANTAGES

Sika® Separol® W-320 has the following characteristics:

- Low viscous
- Excellent 'sticking' ability on vertical mould surfaces
- Self leveling after spray application
- Highly pore suppressing
- No combustible vapor
- No creation of resin
- Reduced 'dusty' residues on the formwork
- Safe for the operatives to handle

This provides the following advantages:

- Easy and precise separation of the formwork from the hardened concrete
- High quality surface finish
- No reduction of the concrete quality at the surface
- Protection of formwork from steel corrosion and early ageing

### APPROVALS / CERTIFICATES

Sika® Separol® W-320 is tested according to Sika® internal testing procedures.

### PRODUCT INFORMATION

<b>Composition</b>	Refined mineral oils, miscible in water.
<b>Packaging</b>	Plastic can: 20 liter Drum: 210 liter IBC: 1000 liter
<b>Shelf life</b>	6 months from date of production if stored properly in original unopened undamaged and sealed packaging.
<b>Storage conditions</b>	Protect from frost, direct sunlight and contamination. Opened units should be stored closed.
<b>Appearance and colour</b>	Liquid, milky white.
<b>Density</b>	0.97 g/cm <sup>3</sup> (at +20°C).

### APPLICATION INFORMATION

<b>Consumption</b>	Sika® Separol® W-320 yields an efficiency, depending on application circumstances and used formwork, of up to ~ 140 m <sup>2</sup> /kg for non absorbent formwork (e.g. steel or plastic).
<b>Ambient air temperature</b>	+5°C min. / +50°C max.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### APPLICATION

Before application, Sika® Separol® W-320 should be thoroughly stirred.  
Sika® Separol® W-320 is a ready to use. Do not dilute or mix it with other materials!  
The moulds should be dry and clean.  
Any residues of rust and concrete must be removed.  
Sika® Separol® W-320 is applied in thin, uniform layers having a fine, white dotted appearance, covering the complete surface (an additional application may be necessary in case of highly absorbent formwork).  
We recommend the use of a special spray gun with an operating pressure of 3-6 bar and a flat spraying nozzle (01 F 110 i.e. 652.307 or 652.245).  
Accumulations of Sika® Separol® W-320 should be avoided. Any excess should be wiped off using a cloth or sponge.  
After application, an evaporation period of 20 minutes at +20°C should be observed.  
Before concreting preliminary tests are recommended to optimise the procedure for each project.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA NORTHERN GULF

Bahrain / Kuwait  
Tel: +973 177 38188  
info@bh.sika.com  
gcc.sika.com

### SIKA SOUTHERN GULF

UAE / Oman / SIC  
Tel: +971 4 439 8200  
info@ae.sika.com  
gcc.sika.com

### Sika Saudi Arabia

Riyadh / Jeddah / Dammam  
Tel. +966 11 217 6532  
info@sa.sika.com  
gcc.sika.com



ISO 9001: Sika UAE LLC,  
Sika Gulf B.S.C. (C),  
Sika Saudi Arabia Limited,  
Sika International Chemicals LLC  
ISO 14001: Sika UAE LLC,  
Sika Gulf B.S.C. (C),  
Sika Saudi Arabia Limited,  
Sika International Chemicals LLC,  
ISO 45001: Sika UAE LLC,  
Sika Gulf B.S.C. (C),  
Sika International Chemicals LLC.

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.

SikaSeparolW-320-en-AE-(07-2022)-1-1.pdf

### Product Data Sheet

Sika® Separol® W-320  
July 2022, Version 01.01  
021405021000000160

