

BUILDING TRUST

PRODUCT DATA SHEET

Sikafloor®-377

Polyurethane crack-bridging self-smoothing flooring resin

DESCRIPTION

Sikafloor®-377 is a 2-part polyurethane, coloured, low-viscosity flooring resin for medium to heavy wear conditions. It provides a hard-wearing finish and a slip-resistant finish when broadcast with different aggregate grades.

Suitable to use in hot and tropical climatic conditions.

USES

Sikafloor®-377 may only be used by experienced professionals.

The Product is used as a:

 Broadcast slip-resistant wearing course with crackbridging properties

The Product is used for:

Interior and exterior use

FEATURES

- Seamless
- Good crack-bridging ability
- Good mechanical resistance
- Low sensitivity to moisture during application
- Impermeable to liquids

- Smooth matt finish
- Low maintenance
- Easy to apply
- Low VOC emissions

SUSTAINABILITY

- Contributes towards satisfying Indoor Environmental Quality (EQ) Credit: Low-Emitting Materials under LEED® v4
- Contributes towards satisfying Materials and Resources (MR) Credit: Building product disclosure and optimization Environmental Product Declarations under LEED® v4
- Environmental Product Declaration (EPD) in accordance with EN 15804. EPD independently verified by Institut für Bauen und Umwelt e.V. (IBU)

CERTIFICATES AND TEST REPORTS

- CE marking and declaration of performance based on EN 13813:2002 Screed material and floor screeds — Screed material — Properties and requirements — Synthetic resin screed material
- CE marking and declaration of performance based on EN 1504-2:2004 Products and systems for the protection and repair of concrete structures — Surface protection systems for concrete — Coating

PRODUCT INFORMATION

Composition	Polyurethane		
Packaging	Container Part A	20.25 kg	
	Container Part B	4.75 kg	
	Container Part A + Part B	25.0 kg	
	Refer to the current price list for availabe packaging variations.		
Shelf life	12 months from date of production		

Product Data Sheet

Sikafloor®-377 September 2023, Version 03.01 020812040020000136

Storage conditions	The Product must be stored in original, unopened and undamaged sealed packaging in dry conditions at temperatures between +5 °C and +30 °C. Always refer to packaging. Refer to the current Safety Data Sheet for information on safe handling and storage.				
Appearance and colour	Part A		Coloured		
••	Part B		Cear		
	Cured appearance Smoo		Smooth, matt finis	oth, matt finish	
	Cured colour Bei		Beige	eige	
Density	Mixed Product	Mixed Product ~1.38 kg/l (Filled resin		(EN ISO 2811-1)	
Solid content by mass	~100 %				
Solid content by volume	~100 %				
TECHNICAL INFORMATIO	N				
Tensile adhesion strength	> 1.5 N/mm² (failu	> 1.5 N/mm² (failure in concrete)		(EN 1542)	
APPLICATION INFORMAT	ION				
Mixing ratio	Part A : Part B (by weight)		81:19		
Consumption	Filled	Filled		1.4 kg/m² per mm	
Material temperature	Maximum		+30 °C		
·	Minimum		+10 °C		
Ambient air temperature	Maximum		+30 °C		
	Minimum		+10 °C		
Relative air humidity	Maximum		80 % r.h.		
Dew point	Beware of condensation. The substrate and uncured applied product must be at least +3 °C above dew point to reduce the risk of condensation on the surface of the applied product.				
Substrate temperature	Maximum		+30 °C		
	Minimum		+10 °C		
		Refer to the individual primer Product Data Sheet.			
Substrate moisture content	Refer to the individ	addi primer i rod			
	+10 °C	addi piiliei i rod	40 minutes		
		addi primer i rod			
	+10 °C	audi prinici i rod	40 minutes		
Pot Life	+10 °C +20 °C +30 °C	top coat over bro	40 minutes 30 minutes 20 minutes adcast Sikafloor®-37	7, allow:	
Pot Life	+10 °C +20 °C +30 °C		40 minutes 30 minutes 20 minutes adcast Sikafloor®-37	•	
Pot Life	+10 °C +20 °C +30 °C	top coat over bro	40 minutes 30 minutes 20 minutes adcast Sikafloor®-37 Maxi No m	•	
Substrate moisture content Pot Life Waiting time to overcoating	+10 °C +20 °C +30 °C Before applying a t Temperature	top coat over bro	40 minutes 30 minutes 20 minutes adcast Sikafloor®-37 Maxi No m time	mum	





conditions, particularly temperature and relative humidity.

Applied product ready for use

Temperature	Foot traffic	Light traffic	Full cure
+10 °C	24 hours	3 days	9 days
+20 °C	12 hours	2 days	5 days
+30 °C	8 hours	1 day	3 days

Note: Times are approximate and will be affected by changing ambient conditions, particularly temperature and relative humidity.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

Refer to the following method statements:

- Sika Method Statement Sikafloor® and Sikagard® evaluation and preparation of surfaces
- Sika Method Statement Sikafloor® mixing and application

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

EQUIPMENT

MIXING EQUIPMENT

Electric double paddle mixer (>700 W, 300 to 400 rpm)

APPLICATION EQUIPMENT

- Pin leveller
- Trowels, including serrated
- Spiked roller

SUBSTRATE QUALITY

IMPORTANT

Incorrect treatment of cracks

The incorrect assessment and treatment of cracks may lead to a reduced service life and reflective cracking. TREATMENT OF JOINTS AND CRACKS

Construction joints and existing static surface cracks in substrate require pre-treating before full layer application. Use Sikadur® or Sikafloor® resins.

SUBSTRATE CONDITION

Cementitious substrates must be structurally sound and of sufficient compressive strength (minimum 25 N/mm^2) with a minimum tensile strength of 1.5 N/mm^2

Substrates must be clean, dry and free of all contaminants such as dirt, oil, grease, coatings, laitance, surface treatments and loose friable material.

SUBSTRATE PREPARATION

MECHANICAL SUBSTRATE PREPARATION IMPORTANT

Surface defects due to voids in the substrate

Voids and blow holes in the substrate will result in surface weakness and damage to the covering product if not repaired during the preparation process.

- 1. Fully expose blow holes and voids during surface preparation to identify the required repairs.
- 1. Remove weak cementitious substrates.
- 2. Prepare cementitious substrates mechanically using abrasive blast cleaning, planing or scarifying equipment to remove cement laitance.
- 3. Before applying thin layer resins, remove high spots by grinding.
- 4. Use industrial vacuuming equipment to remove all dust, loose and friable material from the application surface before applying the Product.
- 5. Use products from the Sikafloor®, Sikadur® and Sikagard® range of materials to level the surface or fill cracks, blow holes and voids.

Contact Sika® Technical Services for additional information on products for levelling and repairing defects. SUBSTRATE PREPARATION OF NON-CEMENTITIOUS SUBSTRATES

For information on substrate preparation of non-cementitious substrates, contact Sika technical services.



MIXING

- 1. Mix Part A (resin) until the coloured pigment is dispersed and a uniform colour is achieved.
- 2. Add Part B (hardener) to Part A.
- IMPORTANT Do not mix excessively. Mix Part A + B continuously for ~3 minutes until a uniformly coloured mix is achieved.
- 4. Add the quartz sand and mix for a further 2 minutes until a uniform mix has been achieved.
- To ensure thorough mixing, pour materials into another container and mix again to achieve a smooth and uniform mix.
- During the final mixing stage, scrape down the sides and bottom of the mixing container with a flat or straight edge trowel at least once to ensure complete mixing.

APPLICATION

IMPORTANT

Strictly follow installation procedures

Strictly follow installation procedures as defined in Method Statements, application manuals and working instructions which must always be adjusted to the actual site conditions.

IMPORTANT

Protect from moisture

After application, protect the Product from damp, condensation and direct water contact for at least 24 hours.

IMPORTANT

Uncured material reacts with water

Uncured material reacts with water of any kind, which leads to foaming.

1. During the application, wear head and wrist bands to avoid sweat falling onto the uncured material.

IMPORTANT

No application on rising moisture

Do not apply on substrates with rising moisture. IMPORTANT

Damaged finish due to heating with fossil fuel heaters Fossil fuel heaters powered by gas, oil or paraffin produce large quantities of both carbon dioxide and water vapour, which may adversely affect the finish.

1. For temporary heating, use only electrically powered warm air blower systems. Do not use gas, oil, paraffin or other fossil fuel heaters.

IMPORTANT

Surface exposure

Do not leave the surface of the Product exposed, application of a seal coat is mandatory.

SELF-SMOOTHING WEARING LAYER

Pour the mixed Product onto the substrate.
 Note: The consumption is specified in Application Information.

- Apply the Product evenly over the surface with a serrated trowel.
- 3. To achieve a smooth finish, smooth the surface with the flat side of a trowel.
- 4. Back roll the surface in two directions at right angles with a steel spike roller.

SLIP-RESISTANT BROADCAST LAYER

- 1. Pour the mixed Product onto the prepared substrate.
- Apply the Product evenly over the surface with a serrated trowel.
- 3. Back roll the surface in two directions at right angles with a steel spike roller.
- Broadcast the surface with quartz sand or silicon carbide, lightly at first, then to excess.
 Note: The aggregate is dependent on the system build-up. Refer to the relevant System Data Sheet.
- 5. Allow the Product to initially cure and use vacuum extraction equipment to remove all loose sand.



CLEANING OF EQUIPMENT

Clean all tools and application equipment with Sika® Thinner C immediately after use. Hardened material can only be removed mechanically.

To prevent the nozzle from blocking, regularly clean the spraying equipment during application.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Kuwait Tel: +973 177 38188 info@bh.sika.com gcc.sika.com SIKA SOUTHERN GULF

UAE / Oman / SIC Tel: +971 4 439 8200 info@ae.sika.com gcc.sika.com Sika Saudi Arabia

Riyadh / Jeddah / Dammam Tel. +966 11 217 6532 info@sa.sika.com gcc.sika.com







All products are supplied under a management yuten cutified to conform to the requirements of the quality, environmental and occupational health & safety standards as follows: \$50.9001, 14001, \$184 U.C. \$184 U.C. \$184 Gulf 8.5.C. 0 \$10.0001, 14001; \$185 See Saudi Arabis Umited

Sikafloor-377-en-AE-(09-2023)-3-1.pdf



