

PRODUCT DATA SHEET

Sikadur[®]-42 MP SG (AE)

3-PART, ECONOMICAL EPOXY GROUTING SYSTEM

DESCRIPTION

Sikadur[®]-42 MP SG (AE) is an economical three-component, multipurpose, moisture tolerant, epoxy grouting system.

Suitable for use in hot and tropical climatic conditions.

USES

Sikadur[®]-42 MP SG (AE) may only be used by experienced professionals.

Grouting and fixing of:

- Starter bars
- Anchors
- Fasteners
- Tie rods
- Crash barrier posts
- Fence and railing posts

FEATURES

- High early strength
- Ready-to-mix, pre-batched units
- Moisture tolerant
- Non-shrink
- Corrosion and chemically resistant
- Stress and impact resistant
- High compressive strength
- High vibration resistance
- Excellent adhesion to steel and concrete

PRODUCT INFORMATION

Composition	Epoxy resin, selected fillers and aggregates			
Packaging	Pre-batched units:			
	Component A	Component B	Component C	Total A + B + C
	3.34 kg	0.66 kg	26 kg	30 kg
	16.7 kg	3.3 kg	5 * 26 kg	150 kg
Shelf life	Component A	24 months from the date of production		
	Component B	24 months from the date of production		
	Component C	12 months from the date of production		
Storage conditions	Stored properly in original, unopened, sealed and undamaged packaging in dry conditions at temperatures between +5 °C and +30 °C. Protect from direct sunlight, heat and moisture.			

Appearance and colour	Concrete Grey
Density	~2100 kg/m ³ (A+B+C mixed)

TECHNICAL INFORMATION

Compressive strength	Curing time at +25 °C	Result	(ASTM C579)
	1 day	~80 N/mm ²	
	7 days	~95 N/mm ²	
	28 days	~100 N/mm ²	
Note: Product cured and tested at temperatures indicated. Test specimen size: 50 * 50 * 50 mm			
Tensile adhesion strength	≥1.5 N/mm ² (or concrete failure)		(BS EN 1881-Part 207)

APPLICATION INFORMATION

Mixing ratio	Component A : B : C = 5 : 1 : 39 by weight Solid / liquid = 6.5 : 1 by weight		
Consumption	~2.1 kg/m ² /mm This figure is theoretical and does not include for any additional material required due to surface porosity, surface profile, variations in level and wastage etc..		
Layer thickness	Minimum: 10 mm Maximum: 150 mm		
Material temperature	Sikadur®-42 MP SG (AE) must be applied at temperatures between +20 °C and +35 °C. Condition the material by also storing at this temperature for min. 48 hours before use.		
Ambient air temperature	+20 °C min. / +40 °C max.		
Dew point	Substrate temperature during application must be at least 3 °C above dew point to avoid condensation.		
Substrate temperature	+20 °C min. / +40 °C max.		
Substrate moisture content	≤ 4 % pbw		
Pot Life	(200 g, adiabatic testing)		
		+23 °C	+40 °C
	5 : 1 : 39	~90 min	~40 min
The potlife begins when the resin and hardener are mixed. It is shorter at high temperatures and longer at low temperatures. The greater the quantity mixed, the shorter the potlife. To obtain longer workability at high temperatures chill the components A, B and C before mixing them (that is only when application temperatures are above +20 °C).			

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

General Method Statement: "Sikadur-42: Epoxy resin based grouts"

IMPORTANT CONSIDERATIONS

- Do not add / mix with solvents. Solvents will prevent proper curing and change mechanical properties.
- Sikadur®-42 MP SG (AE) is a vapour barrier when cured.
- Mix complete units only.
- Cold ambient, substrate or material temperatures will influence the curing and flow characteristics of Sikadur®-42 MP SG (AE).
- Do not subject cured epoxy grout to sudden temperature changes, especially during early curing stages.
- Sikadur® resins are formulated to have low creep under permanent loading. However due to the creep behaviour of all polymer materials under load, the long term structural design load must account for creep. Generally the long term structural design load must be lower than 20 - 25 % of the failure load. Please consult a structural engineer for load calculations for your specific application.
- Where higher flow material is required (e.g. for application under base plates), consider using Sikadur®-42 MP Slow.
- Never mix component A and B without adding component C, as the exothermic reaction between A and B alone generates excess heat.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE QUALITY

Mortar and concrete must be older than 28 days (dependent on minimum strength requirements). Verify the substrate strength (concrete, natural stone, etc.).
The substrate surface (all types) must be clean, dry and free from contaminants such as dirt, oil, grease, existing surface treatments and coatings etc.
Steel substrates must be de-rusted to a standard equivalent to Sa 2.5.
The substrate must be sound and all loose particles must be removed.
Substrate must be dry or mat damp and free from any standing water, ice, etc.

SUBSTRATE PREPARATION

Concrete, mortar, stone:

Substrates must be sound, dry, clean and free from laitance, ice, standing water, grease, oils, old surface treatments or coatings and all loose or friable particles must be removed to achieve a laitance and contaminant free, open textured surface.

Steel:

Must be cleaned and prepared thoroughly to an acceptable quality standard equivalent to SA 2.5 by blastcleaning and vacuum. Avoid dew point conditions. Surface contact area must be clean and sound. For best results, the substrate shall be dry. Remove dust, laitance, oils, grease, impregnations, waxes, foreign particles, coatings, and disintegrated materials by mechanical means, blastcleaning etc.
All anchor pockets or sleeves must be free of water. Apply grout immediately to prevent re-oxidizing / rust formation.

MIXING

Pre-batched units:

Mix components A and B in the component A pail for approximately 30 - 60 seconds with a paddle attached to a low speed drill (300 - 450 rpm). Avoid aeration while mixing until the material becomes uniformly blended in colour and viscosity. Place the mixed epoxy into an appropriate mixing vessel. Slowly add the component C and mix until uniform and homogeneous (approximately 3 minutes).

Mix only that quantity which can be used within its potlife.

Never mix component A and B without adding component C (as the exothermic reaction between A and B alone generates excess heat)

Leave Sikadur®-42 MP SG (AE) in the mixing vessel until the majority of entrained air bubbles have dispersed.

APPLICATION

Forming:

The consistency of the Sikadur®-42 MP SG (AE) epoxy grout system requires the use of permanent or temporary forms to contain the material. In order to prevent leakage or seepage, all of these formers must be sealed. Apply polyethylene film or wax to all forms to prevent adhesion of the grout. Prepare the formwork to maintain more than 150 mm liquid head to facilitate placement. A grout box equipped with an inclined trough attached to the form will enhance the grout flow and minimize air encapsulation.

Application:

Pour the mixed grout into the prepared forms from one side only, to eliminate air entrapment. Maintain the liquid head to ensure intimate contact to substrate. Place sufficient epoxy grout in the forms to rise slightly above the underside (3 mm). The minimum void depth shall be 12 mm. Where the thickness requirements are greater than 150 mm, place the epoxy grout in successive 150 mm layers or less, once the preceding lift has cooled. Once hardened check the adhesion by tapping with a hammer.

CLEANING OF EQUIPMENT

Sweep excess grout into appropriate containers for disposal before it has hardened.
Dispose of in accordance with applicable local regulations.
Uncured material can be removed with Sika Colma Cleaner.
Cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Kuwait
Tel: +973 177 38188
info@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

Sika Saudi Arabia

Riyadh / Jeddah / Dammam
Tel. +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001, 14001, 45001 –
Lloyd's Register
Sika S.A.C. LLC
Sika International Chemicals LLC
ISO 9001, 14001, 45001 – SGS
Sika Gulf S.S.C. O.
ISO 9001, 14001 – SGS
Sika Saudi Arabia Limited

All products are supplied under
a management system certified
to conform to the requirements
of the quality, environmental
and occupational health &
safety standards ISO 9001, ISO
14001 and ISO 45001.



Sikadur-42MPSGAE-en-AE-(07-2023)-1-1.pdf

Product Data Sheet

Sikadur®-42 MP SG (AE)
July 2023, Version 01.01
020202010010000103