

PRODUCT DATA SHEET

SikaInject®-315 PS

(formerly TPH.® POLINIT)

Polymeric strengthening (PS) compound for SikaInject® Acrylate Resins

DESCRIPTION

SikaInject®-315 PS is a polymeric strengthening compound for the acrylate resin SikaInject-304 DE. PS compound is used instead of water for preparation of component B with SikaInject-3** acrylate resins.

USES

SikaInject®-315 PS may only be used by experienced professionals.

Use with further SikaInject-3** acrylate resins on request, please refer to related technical data sheets.

FEATURES

When used with SikaInject-3** range :

- Increase of flexibility
 - Increase of adhesion on siliceous surfaces
 - Reduction of shrinkage in case of ventilation
 - Resistant to alternating freeze and thaw exposure
- Once cured, the product is insoluble in water and hydrocarbons and resistant to alkalis

CERTIFICATES AND TEST REPORTS

- CE-Mark, DOP, concrete injection for (S) filling of cracks, joints, honeycombs acc. to EN 1504-5
- Renovation of defective expansion joints; MFPA Leipzig
- Resistance test to freeze-thaw cycling; MFPA Leipzig
- Resistance test to concrete-corrosive fluids; MFPA Leipzig
- Watertightness-Test 7 bar, acc. to DIN EN 14068; MFPA Leipzig

Note: Tested with SikaInject®-304 DE

PRODUCT INFORMATION

Packaging	20 kg Larger packaging on request.
Colour	white, liquid
Shelf life	12 months in original packaging
Storage conditions	dry, between 15-25°C, protected from heat, frost and direct sunlight
Density	~1.01 kg/l (DIN EN ISO 3675)
Viscosity	8 - 15 mPas (DIN EN ISO 2555)

TECHNICAL INFORMATION

Modulus of elasticity in flexure	~ 0.49 MPa (DIN EN ISO 527) with SikalInject®-304 DE
Tensile strength	~ 0.16 MPa (DIN EN ISO 527) with SikalInject®-304 DE
Water absorption	~ 40 % (DIN EN ISO 62) with SikalInject®-304 DE
Elongation at break	~ 710 % (DIN EN ISO 527) with SikalInject®-304 DE

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER DOCUMENTATION

SikalInject®-315 PS can also be used in combination with other SikalInject®-3** acrylate resins. Reaction and performance data can be found in the respective product data sheet.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheets (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

MIXING

SikalInject®-315 PS is used instead of water for preparing component B of SikalInject®-304 DE. At least 3 minutes of mixing are required for dissolving the part B (salt). The component B prepared in this way is ready-for-use and remains stable for ~ 5 hours (depending on temperature). The product is pumped in a mixing ratio of 1 : 1 (parts by volume, A : B) using a 2-component injection pump.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC
Sika International Chemicals LLC
Tel: +971 4 439 8200
Email: info@ae.sika.com
Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC
Riyadh / Jeddah / Dammam / Rabigh
Tel: +966 9200 22167
Email: info@sa.sika.com
Web: gcc.sika.com

Sika LLC - Oman

Sika MB LLC
Tel: +968 22 826 500
Email: info@om.sika.com
Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
Sika MB LLC
Sika International Chemicals LLC
Sika Gulf B.S.C. (c)
ISO 9001, 14001 – SGS
Sika Saudi Arabia Limited
ISO 9001, 14001 – TÜV
Sika MB Construction Chemicals LLC
Sika Construction Chemicals for Manufacturing LLC
ISO 9001 – LMS
Sika MB LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

SikalInject®-315 PS
January 2025, Version 01.01
020707020030000018