

## PRODUCT DATA SHEET

# SikaCeram<sup>®</sup>-214 Premium

HIGH PERFORMANCE, POLYMER CONTAINING, WATER RESISTANT CEMENTITIOUS ADHESIVE FOR THIN BED APPLICATION OF LARGE TILES

### DESCRIPTION

SikaCeram<sup>®</sup>-214 Premium is a high performance, onepack, polymer containing, water resistant, pre-mixed adhesive. Consisting of high resistance cements, selected silicon / quartz mineral charges and specific additives, used as thin bed tile adhesive for permanent fixing of ceramic tiles. Suitable for use in hot and tropical climatic conditions.

### USES

- Suitable for bonding of high absorption ceramic tiles, earthenware, extruded and refined porcelain tiles
- Suitable for bonding of large size tiles used in industrial environment, wet areas, swimming pools, facades
- Suitable for bathrooms, kitchens, balconies, terraces, etc.
- Indoor and outdoor application over concrete, cement mortars, bricks and plaster
- For horizontal and vertical areas
- Suitable for moisture tolerant natural stone
- Suitable to tile directly on various Sika waterproofing products

### PRODUCT INFORMATION

<b>Composition</b>	White ordinary portland cement, selected aggregates and polymers
<b>Packaging</b>	20 kg and 50 kg bags
<b>Shelf life</b>	12 months minimum from date of production
<b>Storage conditions</b>	Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between 5 °C and 35 °C. Protect from direct sunlight, heat and moisture.
<b>Appearance and colour</b>	white powder

### FEATURES

- Water resistant
- Easy to mix and use
- Single component system
- No sagging
- Extended open time
- Excellent workability and thixotropic consistency
- Very good adhesion

### CERTIFICATES AND TEST REPORTS

SikaCeram<sup>®</sup>-214 Premium follows the main requirements of EN 12004 class C2 TE.

Tensile adhesion strength	w/p = 0.26	Value	Requirement EN 12004, class C2	(EN 12004-2)
Initial		≥ 1.0 N/mm <sup>2</sup>	≥ 1.0 N/mm <sup>2</sup>	
After water immersion		≥ 1.0 N/mm <sup>2</sup>	≥ 1.0 N/mm <sup>2</sup>	

## APPLICATION INFORMATION

Fresh mortar density	~1.55 kg/l (25 °C)			
Consumption	The consumption depends on the surface profile and roughness of the substrate trowel size, size of the tiles and the placing technique (simple placing "floating" or back to back "buttering-floating"). As a guide for solid bed application: For 1 mm thickness over 1m <sup>2</sup> area approximately 1.5 kg of material.			
Layer thickness	Min. 2 mm Max. 5 mm (locally up to 12 mm thickness possible, for leveling purpose)			
Ambient air temperature	+5 °C min. / +35 °C max.			
Mixing ratio	5.0 - 5.2 L of water per 20 kg bag 12.5 - 13.0 L of water per 50 kg bag			
Substrate temperature	+5 °C min. / +35 °C max.			
Pot Life	~45 min. (23 °C)			
Open Time	~30 min. (23 °C)			(EN 12004-2)
Adjustability time	~30 min. (23 °C)			
Applied product ready for use	Floor tiles can be grouted	After 24 - 36 h		
	Wall tiles can be grouted	After 4 - 6 h		
	Full traffic / use	After 14 d		
		After 21 d - for swimming pools		

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## IMPORTANT CONSIDERATIONS

- Protect freshly applied material from rain, wind, etc.
  - Make a test area prior to carrying out any work with natural stones.
  - It is usually not necessary to pre-dampen the tiles.
  - For gypsum based substrates, primer need to be applied, please contact Sika Technical Department.
- SikaCeram®-214 Premium shall not be applied on the following cases:
- On metal surfaces and wood
  - On old outdoor ceramic tiles
  - For large stoneware and porcelain tiles (side > 60 cm)

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and con-

tains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE QUALITY / PRE-TREATMENT

- Substrates must be properly cured, structurally sound, free of any loose or friable particles, clean, dry and free of any contaminants such as dust, dirt, oil, grease, cement laitance or efflorescence.
- Depending on the substrate condition and contaminants to be removed from the surface, perform adequate preparation techniques, such as water-jet washing or blastcleaning, in order to remove all traces of any materials that could reduce the product's adhesion to the substrate.
- Any small surface defects and variations in level, profile, or around exposed aggregates for example, can be prefilled and levelled with an additional layer of SikaCeram®-214 Premium, to a maximum thickness of 12 mm, applied at least 24 h before laying the ceramic tiling. For larger and thicker areas of surface reprofiling and making good, appropriate mortars from the SikaRep®, Sika MonoTop® or Sikafloor® Level range should be used.
- Cracks in substrates must be identified and sealed appropriately e.g. with Sikadur epoxy resins.

- When laying tiles on non-absorbent or substrates with limited absorbency, such as existing ceramic tiles, painted surfaces etc., check to confirm that these surfaces are all firmly and securely bonded and stable, then use suitable degreasing/descaling products to thoroughly and completely clean the surface.
- For applications in hot climates / environments and /or on absorbent substrates, thoroughly pre-dampen the surface immediately prior to the product application, but avoid any ponding / standing water on the surface, which must not be damp to touch and not with a dark-matt / wet surface appearance i.e. it must be saturated surface dry (SSD).
- For tiling in frequently damp or wet rooms, a suitable Sika® waterproofing product / system should be applied before the tiling.

## MIXING

Mix 20 kg bag with the necessary, above mentioned, amount of water, using an electric blender with a suitable mixing spiral at low speed, in a clean bucket, and up to obtain a smooth paste free of lumps. Use a blender at 500 rpm maximum; do not mix at faster rate because of mechanical strength decay of the cured product. After blending, leave the product curing for 5 minutes in the mixing container and then briefly stir the mix prior to application. The obtained mix results very creamy, easily spreadable and thixotropic.

## APPLICATION

SikaCeram®-214 Premium is applied using notched trowel. The amount of product should be enough to ensure complete wetting of the tiles' rear. Tiling has to be carried out on fresh glue, exerting an adequate pressure to ensure contact with the adhesive, and thus the perfect bonding. In case a surface film is formed on the adhesive, it is necessary to wipe the trowel on the adhesive layer previously applied. Avoid wetting with water the adhesive already applied, it damages the adhesive.

## CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be mechanically removed

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### Sika Gulf B.S.C. (c)

Tel: +973 177 38188  
 Email: info@bh.sika.com  
 Sika Kuwait Cons. Mat. & Paints Co WLL  
 Tel: +965 22 282 296  
 Email: sika.kuwait@kw.sika.com  
 Web: gcc.sika.com

### Sika UAE LLC

Sika MB Construction Chemicals LLC  
 Sika International Chemicals LLC  
 Tel: +971 4 439 8200  
 Email: info@ae.sika.com  
 Web: gcc.sika.com

### Sika Saudi Arabia Limited

Riyadh / Jeddah / Dammam / Rabigh  
 Tel: +966 11 217 6532  
 Email: info@sa.sika.com  
 Web: gcc.sika.com

### Sika LLC - Oman

Master Builders Solutions LLC  
 (part of Sika)  
 Tel: +968 22 826 500  
 Email: info@om.sika.com  
 Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS  
 -Sika UAE LLC  
 -Sika International Chemicals LLC  
 -Sika Gulf B.S.C. (c)  
 ISO 9001, 14001 – SGS  
 -Sika Saudi Arabia Limited  
 ISO 9001, 14001 – TÜV  
 -Sika MB Construction Chemicals LLC  
 -Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



### Product Data Sheet

SikaCeram®-214 Premium  
 April 2024, Version 01.02  
 02171010200000628

