

PRODUCT DATA SHEET

Sikament® NNG

Superplasticizer / High range water-reducer

DESCRIPTION

Sikament® NNG is a highly effective admixture for concrete especially suitable for the production of free flowing concrete and for the production of high strengths concrete, especially in hot climatic conditions.

Suitable for use in hot and tropical climatic conditions.

USES

Sikament® NNG acting as superplasticizer or as high range water-reducer, promotes a very high plasticity and good slump keeping properties to concrete.

Sikament® NNG is mainly used for the following applications:

- Concrete with strong fluidity.
- High quality concrete.
- Concrete applied in precast.
- Concrete submitted to long transportation, delayed placing and high temperatures.
- Concrete with high water reduction while maintaining favourable consistency enabling good early strength development.

CHARACTERISTICS / ADVANTAGES

Sikament® NNG provides the following properties:

As superplasticizer

- Workability is greatly improved.
- Increase place ability in slender components with densely packed reinforcement.
- Enables easy placing, less vibration needed.
- Good slump keeping effect.

As high range water-reducer

- Up to 25% of water reduction.
- Pronounced increase of final strengths.
- Reduced permeability for water.

PRODUCT INFORMATION

Composition	Based on naphthalene formaldehyde sulphonate
Packaging	1000 L flowbin. Bulk supply in tanker trucks possible on request
Appearance / Colour	Dark Brown Liquid
Shelf life	12 months minimum from production date if stored in undamaged and unopened, original sealed packaging, in dry conditions at temperatures between +5 and +35 °C. Protect from direct sunlight.
Storage conditions	Store in a dry area between 5°C and 35°C. Protect from direct sunlight
Density	1.2 ± 0.015
pH-Value	8.5 ± 1

Total chloride ion content	< 0.1%.
Recommended dosage	According to the main goal we recommend the following dosages : <ul style="list-style-type: none"> ▪ 0.5 – 3.0% by weight of cement. Carry out trial mixes to establish the exact dosage rate required.
Dispensing	Sikament® NNG can be added to the mixing water prior to its addition to the aggregates or directly to the freshly mixed concrete (the plasticizing effect is more pronounced). Never add Sikament® NNG directly to dry cement or aggregates (efficiency reduction). Sikament® NNG can also be added to the concrete immediately prior to discharge and after further mixing has taken place for at least three more minutes.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

Sikament® NNG allows the production of high performance concrete, as long as the composition is well design and standard rules of good concreting practice are followed (production as well as placing). Fresh concrete must be cured properly and as early as possible especially in hot climatic conditions in order to prevent plastic and drying shrinkage.

- We recommend previous tests to determine the correct dosage of the admixture and whenever concrete composition is changed.
- When accidental overdosing occurs, the set retarding effect increases. During this period the concrete must be kept moist in order to prevent premature drying out.
- For further details contact our Technical Department.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF
Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF
UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA SAUDI ARABIA
Riyadh / Jeddah / Dammam
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and OHSAS 18001.

Product Data Sheet
Sikament® NNG
June 2021, Version 01.01
021302011000001037

SikamentNNG-en-AE-(06-2021)-1-1.pdf

