

# PRODUCT DATA SHEET

## Sika® Permacor®-2230 VHS

### HIGH SOLID 2-PACK-ACRYLIC-POLYURETHANE TOPCOAT

#### DESCRIPTION

Sika® Permacor®-2230 VHS is a 2-pack Acrylic-Polyurethane topcoat, with extremely low solvent content and with very good optical and mechanical properties. Low solvent content according to Protective Coatings Directive of German Paint Industry Association (VdL-RL 04). Suitable for use in hot and tropical climatic conditions.

#### USES

Sika® Permacor®-2230 VHS may only be used by experienced professionals.

Sika® Permacor®-2230 VHS is used as mechanically resistant top coat for atmospheric exposed steel surfaces for example bridges, pipelines, industrial and harbour installations, tanks, wind power stations as well as sewage treatment plants and steel structures in common.

Together in combination with 2-pack primers and intermediate coats of SikaCor® and Sika® Permacor® results in mechanically resistant coating systems for long life corrosion protection with extremely high weather resistance up to corrosivity category C5-M high, according to ISO 12944-2.

#### CHARACTERISTICS / ADVANTAGES

- Excellent weather resistance due to high gloss and colour retention
- Fast curing characteristics, short recoating time
- Economical due to high volume solids
- VOC-value of approximately 250 g/l

#### APPROVALS / CERTIFICATES

- Tested according to NORSOK Standard M-501, Rev. 6, system no. 1.

#### PRODUCT INFORMATION

<b>Packaging</b>	Sika® Permacor®-2230 VHS	25 kg and 10 kg
	Sika® Thinner P	25 L and 5 L
<b>Appearance / Colour</b>	RAL, NCS, others on request.	
<b>Shelf life</b>	2 years	
<b>Storage conditions</b>	In originally sealed containers in a cool and dry environment.	
<b>Density</b>	~1.4 kg/l	
<b>Solid content</b>	~70 % by volume	
	~82 % by weight	

## TECHNICAL INFORMATION

<b>Chemical Resistance</b>	Water, sea water, sewage, diluted inorganic acids and lyes, salt, detergents, grease, oil and for short term contact to solvents and gasoline.
<b>Temperature Resistance</b>	Dry heat up to approximately +120 °C, short term up to + 150 °C Damp heat up to approximately +50 °C

## SYSTEMS

<b>Systems</b>	<p><u>Steel:</u> As a topcoat on the following primers and intermediate coats: Sika® Permacor®-2204 VHS Sika® Permacor®-2215 EG VHS SikaCor®-6205 VHS Turbo, SikaCor® EG-1 and SikaCor® EG-1 VHS</p> <p>1 x Sika Poxicolor® Primer HE NEW or SikaCor® Zinc R 1 x SikaCor® EG-1 VHS 1 x Sika® Permacor®-2230 VHS</p> <p><u>Galvanized steel, stainless steel and aluminium:</u> 1 x SikaCor® EG-1 or SikaCor® EG-1 VHS 1 x Sika® Permacor®-2230 VHS</p> <p>In case of exposure to permanent condensation use SikaCor® Zinc R or Sika® Permacor®-2311 Rapid as primer.</p>
----------------	--

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	Components A : B	
	By weight	100 : 18
	By volume	3.8 : 1
<b>Thinner</b>	Sika® Thinner P If necessary max. 5 % Sika® Thinner P may be added to adapt the viscosity.	
<b>Consumption</b>	Theoretical material-consumption/VOC without loss for medium dry film thickness:	
	Dry film thickness	~80 µm
	Wet film thickness	~115 µm
	Consumption	~0.160 kg/m <sup>2</sup>
	VOC	~28.8 g/m <sup>2</sup>
<b>Product Temperature</b>	Min. + 5 °C	
<b>Relative Air Humidity</b>	Max. 85 %, except the surface temperature is significantly higher than the dew point temperature, it shall be at least 3 °C above dew point.	
<b>Surface Temperature</b>	Min. + 5 °C 0 °C when accelerated with SikaCor® PUR Accelerator.	
<b>Pot Life</b>	At +10 °C	~4 h
	At +20 °C	~2 h
	At +30 °C	~1 h
<b>Drying Stage 6</b>	<b>Dry film thickness ~80 µm</b>	(ISO 9117-5)
	+5 °C after	~20 h
	+15 °C after	~10 h
	+20 °C after	~6 h
	+30 °C after	~3 h

## Waiting Time / Overcoating

	Dry film thickness ~80 µm
min. +5 °C after	min. ~18 h
min. +15 °C after	min. ~9 h
min. +20 °C after	min. ~5 h
min. +30 °C after	min. ~2 h

Max. unlimited

Prior to further applications possible contamination must be removed (see surface preparation).

## Drying time

### Final drying time

Depending on film thickness and temperature full hardness is achieved after 1 - 2 weeks.

## APPLICATION INSTRUCTIONS

### SURFACE PREPARATION

#### Steel:

Blast cleaning to Sa 2 ½ according to ISO 12944, part 4. Free from dirt, oil and grease.

#### Galvanized steel, stainless steel and aluminium:

Free from dirt, oil, grease and corrosion products. In case of condensation the surfaces must be slightly sweep blasted with a ferrite-free blasting abrasive.

For contaminated surfaces e.g. galvanized or primed areas we recommend to clean with SikaCor® Wash.

### MIXING

Stir component A thoroughly using an electric mixer (start slowly, then increase up to approximately 300 rpm). Add component B carefully and mix both components thoroughly (including sides and bottom of the container). Mix for at least 3 minutes until a homogeneous mixture is achieved. Pour mixed material into clean container and mix again shortly as described above.

### APPLICATION

The method of application has a major effect on achieving uniform thickness and appearance. Spray application will give the best results. The indicated dry film thickness is easily achieved by airless spray. Adding solvents reduces the sag resistance and the dry film thickness. In case of application by roller or brush, additional applications may become necessary to achieve the required coating thickness, depending on type of construction, site conditions, colour shade etc. Prior to major coating operations a test application on site may be useful to ensure the selected application method will provide the requested results.

#### Airless-spraying:

- Pressure minimum 150 bar
- Nozzle size 0.38 - 0.53 mm (0.015 - 0.021 inch)
- Spraying angle 40 ° - 80 °

### CLEANING OF EQUIPMENT

Sika® Thinner C

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, user shall refer to the most recent Safety Data Sheets (SDS) containing physical, ecological, toxicological and other safety related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait  
Tel: +973 177 38188  
sika.gulf@bh.sika.com  
gcc.sika.com

### SIKA SOUTHERN GULF

UAE / Oman / SIC  
Tel: +971 4 439 8200  
info@ae.sika.com  
gcc.sika.com

### SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman  
Tel: +966 11 217 6532  
info@sa.sika.com  
gcc.sika.com



ISO 9001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd,  
Sika Qatar LLC  
ISO 14001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd  
OHSAS: Sika UAE LLC,  
Sika Gulf B.S.C. (c)

All products are supplied  
under a management  
system certified to conform  
to the requirements of the  
quality, environmental and  
occupational health &  
safety standards ISO 9001,  
ISO 14001 and OHSAS  
18001.

SikaPermacor-2230VHS-en-AE-(08-2017)-3-1.pdf

### Product Data Sheet

Sika® Permacor®-2230 VHS  
August 2017, Version 03.01  
020602000200000005

