

BUILDING TRUST

PRODUCT DATA SHEET

Sikament[®] RB 3251

(formerly MRheobuild 3251)

WATER REDUCING SUPERPLASTICISING ADMIXTURE FOR THE PRODUCTION OF WORKABLE CONCRETE

DESCRIPTION

Sikament[®] RB 3251 is a liquid admixture for concrete based on sulphonated naphthalene. The product may be used to effect substantial water reductions or to produce workable concrete with normal setting time. Suitable for use in hot and tropical climatic conditions.

USES

- Production of workable ready mixed concrete
- Low water/cement ratio concrete
- In complicated formwork or with congested reinforcement

FEATURES

- Powerful plasticising action reduces or eliminates the need for compaction
- Imrpoved physical properties such as compressive, tensile and flexural strength due to water reduction.

CERTIFICATES AND TEST REPORTS

Sikament[®] RB 3251 follows the requirements of ASTM C494; Types A & F and BS EN 934-2

Composition	Sulphonated naphthalene	
Packaging	210 L drum, 1000 L flowbin or bulk supply in tanker	
Appearance and colour	Dark brown liquid	
Shelf life	12 months from date of production when stored properly	
Storage conditions	Store in undamaged, unopened, original sealed packaging in dry condi- tions at temperatures between +5°C and +45°C. Mix well before use.	
Density	~1.13 kg/l (+25°C)	
Total chloride ion content		
	Nil	(EN 934-2)

PRODUCT INFORMATION

TECHNICAL INFORMATION

Concreting guidance	The standard rules of good concreting practice for production and pla- cing must be observed when using Sikament [®] RB 3251 in concrete. Refer to relevant standards. Fresh concrete must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Use Sika [®] Antisol [®] products as a curing agent or apply wet hessian.
APPLICATION INFORM	ATION
Recommended dosage	Sikament [®] RB 3251 is normally dispensed at a rate of 0.7 – 2.0 litres per 100 kg of total binder. Other dosages may be used, depending on the mix design, raw materials, climatic conditions and concrete require- ments. Trial mixes must be performed to establish the exact dosage rate required.
Compatibility	 Sikament® RB 3251 is suitable for mixes containing all types of cement and supplementary cementitious materials such as: Microsilica (Silica Fume), Fly Ash (PFA), GGBS (Ground Granulated Blast Furnace Slag) and the following Sika products: Sikament® SikaPump® Sika® FerroGard®, SikaFiber® Sika® Aer Sika® Stabilizer SikaControl® We recommend for trial mixes to be performed to establish the required performance when combining Sikament® RB 3251 with the above products or other admixtures. Please consult our Sika Technical Department for further assistance.
Dispensing	Sikament [®] RB 3251 should be added to the mix with the gauging water. No extension to the mixing time is necessary. Never add Sikament [®] RB 3251 to dry cement. When using Sikament [®] RB 3251 to produce flowing con- crete at site using ready mix trucks, it can be added to the concrete via the feed hopper at the rear of the truck. Mix before discharge for 5 minutes at 10 rpm to produce a fully homogenous mix.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

Before pouring, suitability tests on the fresh concrete must be carried out. With high workability mixes take special care that all formwork is properly installed and secured. If frozen and/or if precipitation has occurred, it may only be used after thawing slowly at room temperature and intensive mixing. When using Sikament® RB 3251 a suitable concrete mix must be designed for the local material sources and trial mixes performed to verify suitability. When accidental overdosing occurs the set retarding effect and workability increases along with bleeding. Additional air may also be entrained. During this period the concrete must be kept moist in order to prevent premature drying out.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

Product Data Sheet Sikament® RB 3251 December 2024, Version 01.02 02130200000002100



BUILDING TRUST

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188 Email: info@bh.sika.com Sika Kuwait Cons. Mat. & Paints Co WLL Tel: +965 22 282 296 Email: sika.kuwait@kw.sika.com Web: gcc.sika.com



Product Data Sheet



Sika UAE LLC

Sika MB Construction Chemicals LLC Sika International Chemicals LLC Tel: +971 4 439 8200 Email: info@ae.sika.com Web: gcc.sika.com

der fied

Sika Saudi Arabia Limited

Sika Construction Chemicals for Manufacturing LLC Riyadh / Jeddah / Dammam / Rabigh Tel: +966 9200 22167 Email: info@sa.sika.com Web: gcc.sika.com

Sika LLC - Oman Sika MB LLC Tel. +968 22 826 500 Email: info@om.sika.com Web: gcc.sika.com

SikamentRB3251-en-AE-(12-2024)-1-2.pdf



Sikament® RB 3251 December 2024, Version 01.02 02130200000002100

BUILDING TRUST