

# PRODUCT DATA SHEET

## Sika® Permacor®-2330

### 2-PACK AY-PUR TOP COAT

#### DESCRIPTION

Sika® Permacor®-2330 is a 2-pack acrylic polyurethane top coat.  
Suitable for use in hot and tropical climatic conditions.

#### USES

Sika® Permacor®-2330 may only be used by experienced professionals.  
Sika® Permacor®-2330 is used as mechanical resistant topcoat for atmospherically exposed steel surfaces - also for condensation - particularly for machinery, paper mills, engines, rollercoasters and commercial vehicles.  
In combination with 2-pack primers and intermediate coats of the SikaCor® and Sika® Permacor® range Sika® Permacor®-2330 offers a mechanical resistant coating system for long-life corrosion protection with high weather resistance up to corrosivity category C5-I respectively C5-M, 'high', according ISO 12944-5.

#### CHARACTERISTICS / ADVANTAGES

- Very high weather resistance and gloss- and colour retention
- Applicable also at low temperatures down to 0 °C

#### APPROVALS / CERTIFICATES

- Approved according to German standard 'TL/TP-KOR-Stahlbauten', page 87 and page 97.
- Tested according to NORSOK Standard M-501, rev. 6, system no. 1.

#### PRODUCT INFORMATION

<b>Packaging</b>	Sika® Permacor®-2330	28.75 kg and 11.5 kg net.
<b>Appearance / Colour</b>	RAL- and NCS-colour shades, glossy Others upon request.	
<b>Shelf life</b>	2 years	
<b>Storage conditions</b>	In originally sealed containers in a cool and dry environment.	
<b>Density</b>	~1.3 kg/l	
<b>Solid content</b>	~56 % by volume ~69 % by weight	

## TECHNICAL INFORMATION

<b>Chemical Resistance</b>	Weathering, water, sewage, seawater, smoke, de-icing salts, acid and lye vapours, oils, grease and short term exposure to fuels and solvents.
<b>Temperature Resistance</b>	Dry heat up to approximately +120 °C, short term up to +150 °C Damp heat up to approximately +50 °C

## SYSTEMS

<b>Systems</b>	Suitable as topcoat on primers and intermediate coats of Sika® Permacor® Systems 2000, 2200 and 2300.  <u>Steel:</u> 1 x Sika® Permacor®-2204 VHS 1 x Sika® Permacor®-2330 or 1 x Sika® Permacor®-2311 Rapid 1 x Sika® Permacor®-2215 VHS 1 x Sika® Permacor®-2330  Also possible as alternative top coat in SikaCor® EG-System and SikaCor® EG-System Rapid.  <u>Hot dip galvanized steel, stainless steel and aluminium:</u> 1 x SikaCor® EG-1 1 x Sika® Permacor®-2330
----------------	---

## APPLICATION INFORMATION

<b>Mixing Ratio</b>	Components A : B		
	By weight	100 : 15	
	By volume	5.1 : 1	
<b>Thinner</b>	Sika® Thinner P If necessary maximum 5 % Sika® Thinner P may be added to adapt the viscosity.		
<b>Consumption</b>	Theoretical material-consumption/VOC without loss for medium dry film thickness:		
	Dry film thickness	50 µm	80 µm
	Wet film thickness	90 µm	145 µm
	Consumption	~0.115 kg/m <sup>2</sup>	~0.185 kg/m <sup>2</sup>
	VOC	~36.0 g/m <sup>2</sup>	~57.6 g/m <sup>2</sup>
	These figures are theoretical and do not allow for any additional material due to surface colour, surface porosity and surface profile variations in level and wastage etc.		
<b>Product Temperature</b>	Min. +5 °C		
<b>Relative Air Humidity</b>	Maximum 85 %, except the surface temperature is significantly higher than the dew point temperature, it shall be at least 3 K above dew point. The surface must be dry and free from ice.		
<b>Surface Temperature</b>	Min. 0 °C / Max. 40 °C		
<b>Pot Life</b>	At +10 °C	~8 h	
	At +20 °C	~6 h	
	At +30 °C	~3 h	

## Drying Stage 6

Drying stage 6 and waiting time between coats:

	Dry film thickness 80 µm	(ISO 9117-5)
0 °C after	48 h	
+5 °C after	24 h	
+10 °C after	18 h	
+15 °C after	10 h	
+20 °C after	8 h	
+25 °C after	6 h	
+30 °C after	4 h	

### Drying time

#### Final drying time

The full hardness is achieved within approximately 7 days at +20 °C. Tests of the completed coating system should only be carried out after final curing.

## APPLICATION INSTRUCTIONS

### SURFACE PREPARATION

#### Steel:

Blast cleaning to Sa 2 ½ according to ISO 12944, part 4. Free from dirt, oil and grease.

#### Hot dip galvanized steel, stainless steel and aluminium:

Free from dirt, oil, grease and corrosion products. In case of exposure to permanent condensation the surfaces must be slightly sweep blasted with a ferrite-free blasting abrasive.

For contaminated surfaces for example galvanized or primed areas we recommend to clean with SikaCor® Wash.

### MIXING

Stir component A very thoroughly using an electric mixer (start slowly, then increase up to approximately 300 rpm). Add component B carefully and mix both components very thoroughly (including sides and bottom of the container). Mix for at least 3 minutes until a homogeneous mixture is achieved. Fill mixed material into clean container and mix again shortly as described above. During mixing and handling of the materials always wear protective goggles, suitable gloves and other protective clothings.

### APPLICATION

The method of application has a major effect on achieving uniform thickness and appearance. Spray application will give the best results. The indicated dry film thickness is easily achieved by airless spray. Adding solvents reduces the sag resistance and the dry film thickness. In case of application by roller or brush, additional applications may become necessary to achieve the required coating thickness, depending on type of construction, site conditions, colour shade etc. Prior to major coating operations a test application on site may be useful to ensure the selected application method will provide the requested results.

#### By brush or roller

#### Airless-Spraying:

- Pressure minimum 150 bar
- Nozzle size 0.38 - 0.53 mm (0.015 - 0.021 inch)
- Spraying angle 40° - 80°

### CLEANING OF EQUIPMENT

Sika® Thinner P

## IMPORTANT CONSIDERATIONS

Overcoating after two months exposure, the surface needs light grinding to remove residues from the surface and to develop a surface profile, and then wash all surface with clean water, drinking water quality. Be aware that impact of heavy rain or rain showers can physically damage the still liquid membrane.

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

## ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait  
Tel: +973 177 38188  
sika.gulf@bh.sika.com  
gcc.sika.com

### SIKA SOUTHERN GULF

UAE / Oman / SIC  
Tel: +971 4 439 8200  
info@ae.sika.com  
gcc.sika.com

### SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman  
Tel: +966 11 217 6532  
info@sa.sika.com  
gcc.sika.com



ISO 9001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd,  
Sika Qatar LLC  
ISO 14001: Sika UAE LLC,  
Sika Gulf B.S.C. (c),  
Sika Saudi Arabia Co. Ltd  
OHSAS: Sika UAE LLC,  
Sika Gulf B.S.C. (c)

All products are supplied  
under a management  
system certified to conform  
to the requirements of the  
quality, environmental and  
occupational health &  
safety standards ISO 9001,  
ISO 14001 and OHSAS  
18001.

### Product Data Sheet

Sika® Permacor®-2330

November 2018, Version 03.01  
020602000210000007

SikaPermacor-2330-en-AE-(11-2018)-3-1.pdf

