

PRODUCT DATA SHEET

Sikaflex[®]-717 WS

LOW-MODULUS WEATHER SEALANT FOR WINDOWS / DOORS PERIMETER AND WEATHER PROOFING APPLICATIONS

DESCRIPTION

Sikaflex[®]-717 WS is a 1-component, hybrid silicone, UV-stable, moisture curing, low-modulus elastic weather sealant. Suitable for use in hot and tropical climatic conditions.

USES

Sikaflex[®]-717 WS is designed for perimeter joints between windows and/or doors, building parts and common weather proofing applications.

FEATURES

- Very good weathering resistance
- Low extrusion force
- Over-paintable
- Movement capability $\pm 50\%$ (ASTM C 719)
- Good adhesion to porous and non-porous substrates
- Low VOC

SUSTAINABILITY

- Certified according "Low Emitting Materials as per Al Sa'fat - Dubai Green Building Evaluation System" by Dubai Central Laboratory (DCL)

CERTIFICATES AND TEST REPORTS

- ASTM C 920, class 50
- VOC test report (US EPA 24)
- VOC Emission Test Report (CDPH)

PRODUCT INFORMATION

Composition	Silane terminated polymer
Packaging	300 ml cartridge, 12 cartridges per box 600 ml foil pack, 20 foil packs per box
Shelf life	Sikaflex [®] -717 WS has a shelf life of 12 months from the date of production, if it is stored in undamaged, original, sealed packaging, and if the storage conditions are met.
Storage conditions	Sikaflex [®] -717 WS shall be stored in dry conditions, where it is protected from direct sunlight and at temperatures between +5°C and +25°C.
Colour	Black, white, grey, beige, brown and champagne (other colors on request)
Density	~1.4 kg/l

TECHNICAL INFORMATION

Shore A hardness	~30 (28 days)	(CQP023-1 / ASTM C 661)
Tensile strength	~1.5 MPa	(CQP036-1 / ISO 527)
Elongation at break	~700 %	(CQP036-1 / ISO 527)
Movement capability	± 50 %	(ASTM C 719)
Service temperature	-40°C to +90°C	

Joint design

The joint width must be designed to suit the joint movement required and the movement capability of the sealant. The joint width shall be ≥ 6 mm and ≤ 45 mm. The joint depth shall be ≥ 6 mm and ≤ 15 mm. A width to depth ratio of 2:1 must be maintained (for exceptions, see table below).

Typical joint dimensions

Joint Width [mm]	Joint Depth [mm]
10	6
15	8
20	10
30	15
45	15

All joints must be correctly designed and dimensioned in accordance with the relevant standards, before their construction. The basis for calculation of the necessary joint widths are the type of structure and its dimensions, the technical values of the adjacent building materials and the joint sealing material, as well as the specific exposure of the building and the joints. For larger joints please contact Sika technical service.

APPLICATION INFORMATION

Consumption	Joint length [m]	Joint width [mm]	Joint depth [mm]
	per 600 ml foil pack		
	10	10	6
	5	15	8
	3	20	10
	2	25	12
	1.3	30	15

Ambient air temperature	+5°C to +40°C, min. 3°C above dew point temperature
Substrate temperature	+5°C to +40°C
Backing material	Use closed cell, polyethylene foam backing rods.
Curing rate	~2 mm/24 hours (23°C / 50% r.h.) (CQP 049-2)
Skinning time	~45 min (23°C / 50% r.h.) (CQP 019-1)

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

FURTHER INFORMATION

- Safety Data Sheet (SDS)
- Pre-treatment Chart Sealing & Bonding
- General Guidelines Sikasil Weather Sealants

IMPORTANT CONSIDERATIONS

- Colour variations may occur due to exposure to chemicals or other extreme external influences. However, a change in colour is purely of aesthetic nature and does not adversely influence the technical performance or durability of the product.
- Do not use Sikaflex®-717 WS on natural stone.
- Do not use Sikaflex®-717 WS on bituminous substrates, natural rubber or any building materials which might bleed oils, plasticizers or solvents that could attack the sealant. EPDM or other gaskets in direct contact with Sikaflex®-717 WS have to be tested for compatibility prior to application. For specific advice contact Sika technical service.
- Do not use Sikaflex®-717 WS on pre-stressed polyacrylate and polycarbonate as it may cause environmental stress cracking (crazing).
- Do not use Sikaflex®-717 WS to seal joints in and around swimming pools.
- Do not use Sikaflex®-717 WS for joints under water pressure or for permanent water immersion.
- Do not expose uncured Sikaflex®-717 WS to alcohol containing products as this may interfere with the curing reaction.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles. The following priming and/or pre-treatment procedures shall be followed:

Non-porous substrates

Float glass, coated glass, anodised aluminium and stainless steel have to be pre-treated using Sika® Aktivator-205, Sika® Aktivator-100 or Sika® Cleaner P. Powder coated and PVDF coated metals have to be pre-treated using Sika® Aktivator-205. For details like application and flash-off times refer to the most recent PDS of the respective pre-treatment product.

Porous substrates

Concrete, aerated concrete and cement based renders, mortars and bricks shall be primed using Sika® Primer-3 N or Sika® Primer-210. For details like application and flash-off times refer to the most recent PDS of the respective pre-treatment product. Adhesion tests on project specific substrates must be performed prior to application. For more detailed advice and instructions please contact Sika technical service.

Note: Primers are adhesion promoters. They are neither a substitute for the correct cleaning of a surface, nor do they improve the strength of the surface significantly.

APPLICATION METHOD / TOOLS

Sikaflex®-717 WS is supplied ready to use. After the necessary substrate preparation, insert a suitable backing rod to the required depth and apply pre-treatment if necessary. Insert a foil pack or cartridge into the sealant gun and extrude Sikaflex®-717 WS into the joint making sure that it comes into full contact with the sides of the joint and avoids any air entrapment. Sikaflex®-717 WS sealant must be firmly tooled against the joint sides to ensure adequate adhesion. It is recommended to use masking tape where exact joint lines or neat lines are required. Remove the tape within the skin time

CLEANING OF EQUIPMENT

Clean all tools and application equipment immediately after use with Sika® Remover-208 and/or Sika® Cleaning Wipes-100. Once cured, residual material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

Sika UAE LLC

Master Builders Solutions Construction Chemicals LLC (part of Sika)
Sika International Chemicals LLC
Tel: +971 4 439 8200
Email: info@ae.sika.com
Web: gcc.sika.com

Sika Saudi Arabia Limited

Riyadh / Jeddah / Dammam / Rabigh
Tel: +966 11 217 6532
Email: info@sa.sika.com
Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC (part of Sika)
Tel: +968 22 826 500
Email: info@om.sika.com
Web: gcc.sika.com



ISO 9001, 14001, 45001 - SGS:
Sika UAE LLC
Sika International Chemicals LLC
Sika Gulf B.S.C. (c)
ISO 9001, 14001 - SGS:
Sika Saudi Arabia Limited
ISO 9001, 14001 - TÜV:
Master Builders Solutions
Construction Chemicals LLC
Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

Sikaflex®-717 WS

October 2023, Version 02.01
02051102000000063