

PRODUCT DATA SHEET

SikaTop®-578 Seal

(formerly MSeal 578)

An elastomeric, highly flexible cementitious waterproof coating for concrete and masonry structures

DESCRIPTION

SikaTop®-578 Seal is a two-component, cement based, flexible coating for waterproofing and protection of concrete and masonry structures.

Component A is a powder blend of Portland cements, selected silica sands and modifying agents. When mixed to a slurry consistency with Component B, liquid, an acrylic polymer emulsion, it can be easily applied by brush or roller.

Suitable for use in hot and tropical climatic conditions.

USES

- Suitable for internal and external applications.
- Waterproofing and protection of terraces, balconies, bathrooms and other wet areas where tiles are to be installed directly on top of the membrane using a proprietary tile adhesive.
- Waterproofing of water retaining and hydraulic structures.
- Flexible protection of concrete structures subject to minor deformation under load.
- Protection of concrete structural elements repaired with products from the SikaEmaco® or Sikadur® ranges against the penetration of carbon dioxide.
- Protection of concrete surfaces from sea-water and deicing salts, chloride attack and carbonation.

FEATURES

- High performance: accommodates movement
- Excellent elongation at failure
- Excellent mechanical characteristics
- Easy application due to product's consistency
- Compatible with ceramic, mosaic and natural stone coverings
- Excellent adhesion
- Retains flexibility when submerged
- Flexible under all environmental conditions
- Good chemical resistance against soft water, domestic waste water, manure or other liquids moderately aggressive to mineral substrates

CERTIFICATES AND TEST REPORTS

SikaTop®-578 Seal meets the requirements defined by EN 1504-9 and EN 1504-2.

PRODUCT INFORMATION

Packaging	Supplied in 30 kg unit
	Comp. A - Powder <u>20 kg</u>
	Comp. B - Liquid <u>10 kg</u>
Shelf life	12 months from date of production
Storage conditions	Store in original unopened packaging in a cool and dry condition between +5°C and +35°C. Protect from direct sunlight, heat and moisture. Avoid excessive compaction. Do not stack pallets.
Appearance and colour	Grey
Density	~1.6 kg/l (fresh mortar at +20°C)

TECHNICAL INFORMATION

Crack bridging ability	Static crack-bridging (after 28 days at +20°C and 50% R.H.)	Class A5 (> 2.5 mm)	(EN 1504-2 / EN 1062-7)
	Dynamic crack-bridging (at +20°C expressed as resistance to cracking cycles)	class B4.2	
	at +23°C	> 1 mm	(EN 1504-2 / EN 14891-A.8.2)
Tensile adhesion strength	~0.8 N/mm ² (on concrete surface, at 28 days, +20°C and 50% R.H.) and (Thermal compatibility to freeze/thaw cycles with de-icing salts, measured as Adhesion)		(EN 1504-2 / EN 1542)
	Initial adhesion strength	~1 N/mm ²	(EN 1504-2 / EN 14891-A.6.2)
	Adhesion after application of heat source	~1.3 N/mm ²	(EN 1504-2 / EN 14891-A.6.5)
	Adhesion after freeze-thaw cycles	~0.7 N/mm ²	(EN 1504-2 / EN 14891-A.6.6)
	Adhesion after immersion in basic water	~0.7 N/mm ²	(EN 1504-2 / EN 14891-A.6.9)
Elongation at break	~120 % (after 28 days at +20°C and 50% R.H.)		(ASTM D412)
Watertightness	1.5 bar - no penetration (for 7 days of positive lift)		(EN 1504-2 / EN 14891-A.7)
Water permeability	~ 0.05 kg/m ² ·h ^{0.5} (Expressed as capillary absorption)		(EN 1504-2 / EN 1062-3)
Permeability to water vapour	Class 1 (SD < 5) (Equivalent air thickness)		(EN 1504-2 / EN ISO 7783-1)
Permeability to carbon dioxide	> 100 m (diffusion in equivalent air layer thickness CO ₂ (S _b))		(EN 1504-2 / EN 1062-6)
Resistance to UV exposure	Resistant (500 hrs)		(ASTM G154-16)

APPLICATION INFORMATION

Consumption	~1 L / m ² / mm per layer (min. 2 layers recommended) An additional 0.5 kg/m ² is required when embedding approved mesh
Yield	~19 L / 30 kg unit
Ambient air temperature	+8°C to +45°C
Pot Life	~60 min. (at 20°C)

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The surface to be coated must be clean and sound. Remove all traces of formwork, release agents, previous coatings, laitance, organic growth and any other contaminants that may affect the bond adversely. Suitable cleaning methods include ultra high-pressure water jetting and grit blasting. Aggressive percussive methods such as scabbling or scarifying are not recommended unless followed by grit blasting, wire brushing or high-pressure water jetting. After the above treatment, surfaces must be thoroughly rinsed with clean potable water to remove all dust and loose particles.

Cracks bolt holes and large surface defects must be cut out and filled solid with SikaTop®-590 Seal or one of the SikaEmaco® range of repair material. Small blowholes in the concrete should be filled with a thixotropic mix of SikaTop®-578 Seal Powder with reduced liquid content.

MIXING

SikaTop®-578 Seal is supplied in premeasured units and should be mixed on site utilising clean containers. Slowly add the powder to the liquid and mix, using a slow speed drill fitted with a suitable paddle. MIX AND USE. Do not mix more material than can be used in one hour.

APPLICATION

Apply SikaTop®-578 Seal in two coats at minimum 1 mm thickness per coat. Apply subsequent coats once the initial coat has dried.

SikaTop®-578 Seal must be reinforced with mesh across all construction joints and cracks. The reinforcing mesh may be either 100 % polypropylene or an alkali resistant glass-fibre mesh, depending on which particular enhanced tensile properties are required. Please consult your local Sika® Technical Service Representative for further advice on the correct selection of mesh.

CURING TREATMENT

Under hot or excessive drying conditions adequate protective shielding should be foreseen. In cold, humid or unventilated areas it may be necessary to leave the application for a longer curing period.

SikaTop®-578 Seal needs to cure under dry-air conditions. Additional heating and/or ventilation can assist proper curing.

Do not use dehumidifiers during curing periods.

CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened / cured material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC
Sika International Chemicals LLC
Tel: +971 4 439 8200
Email: info@ae.sika.com
Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for
Manufacturing LLC
Riyadh / Jeddah / Dammam / Rabigh
Tel: +966 12 692 7079
Email: info@sa.sika.com
Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC
(part of Sika)
Tel. +968 22 826 500
Email: info@om.sika.com
Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
- Sika UAE LLC
- Sika International Chemicals LLC
- Sika Gulf B.S.C. (c)
- Sika MB Construction Chemicals for Manufacturing LLC
- Sika Saudi Arabia Limited
- Sika MB Construction Chemicals for Manufacturing LLC
- Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

SikaTop®-578 Seal

September 2024, Version 03.01
02070100000002036