

PRODUCT DATA SHEET

Sika® ViscoCrete® ACE 507 M

(formerly MGlenium ACE 507M)

A NEW GENERATION OF HIGH-PERFORMANCE POLYCARBOXYLATE ETHER (PCE) SUPERPLASTICIZERS FOR THE PRECAST INDUSTRY. ESSENTIAL COMPONENT OF ZERO ENERGY SYSTEM

DESCRIPTION

Sika® ViscoCrete® ACE 507 M (Admixture Controlled Energy) consists of a range of innovative superplasticizers based on newly developed polycarboxylate ether polymer. The particular molecular configuration of Sika® ViscoCrete® ACE 507 M accelerates the cement hydration by exposing increased surface of the cement grains to react with water. As a result, it is possible to obtain earlier development of the heat of hydration, rapid development of the hydration products and, as a result, higher strengths achievement at very early age. The polymer structure of Sika® ViscoCrete® ACE 507 M is specially designed to improve the rheology of precast concrete, making it very flowable and low viscous even at very low water/cement ratio, without increasing stickiness. Robustness is a distinctive feature of the precast concrete produced with Sika® ViscoCrete® ACE 507 M. Suitable for use in hot and tropical climatic conditions.

ZERO ENERGY SYSTEM

Zero Energy System is based on a combination of the latest Sika® ViscoCrete® superplasticizers and advanced self-compacting concrete technology. The Zero Energy System has been developed to help the precast concrete producer to rationalize his production process and save on energy costs combined with improved quality of the product and the working conditions.

USES

- Sika® ViscoCrete® ACE 507 M is suitable for making precast concrete elements with highly-fluid concrete without segregation but with low water cement ratio, consequently, high early and final strengths.
- Sika® ViscoCrete® ACE 507 M may be used in combination with Sika® Stabilizer for producing advanced self-compacting concrete like Smart Dynamic Concrete (SDC, latest V-type SCC), without the aid of vibration, for economic, ecological and ergonomic precast production.

FEATURES

Sika® ViscoCrete® ACE 507 M offers the following benefits for the precast concrete industry:

- Production of highly flowable self-compacting concrete having a low water cement ratio along with an optimal rheology.
- Enhanced robustness and consistency in concrete quality with low stickiness.
- Environmentally friendly, CO₂ reduced mix design optimization.
- Elimination of heat curing.
- Improved surface appearance.
- Durable precast concrete elements as per BS EN 206-1.
- Elimination of the energy required for placing, compaction and curing (ZERO ENERGY).
- Optimization of the curing temperature.
- Increased productivity.

CERTIFICATES AND TEST REPORTS

Sika® ViscoCrete® ACE 507 M meets the requirements of ASTM C-494 Type A, E & F and BS EN 934-2

PRODUCT INFORMATION

| | | |
|----------------------------|--|---------------|
| Composition | Aqueous solution of modified polycarboxylates, co-polymers | |
| Packaging | 210 L drum, 1000 L flowbin or bulk supply in tanker | |
| Appearance and colour | Whitish to light yellow liquid | |
| Shelf life | 12 months from date of production if stored properly | |
| Storage conditions | Store in undamaged, unopened, original sealed packaging in dry conditions at temperatures between +5°C and +45°C. Protect from direct sunlight. Mix well before using. | |
| Density | ~1.08 kg/l (+25°C) | |
| pH-Value | 3.5 - 7.0 | |
| Total chloride ion content | Nil | (BS EN 934-2) |

TECHNICAL INFORMATION

| | |
|---------------------|---|
| Concreting guidance | The standard rules of good concreting practice for production and placing must be observed when using Sika® ViscoCrete® ACE 507 M in concrete. Refer to relevant standards. Fresh concrete must be cured properly especially at high temperatures in order to prevent plastic and drying shrinkage. Use Sika® Antisol® products as a curing agent or apply wet hessian. |
|---------------------|---|

APPLICATION INFORMATION

| | |
|--------------------|--|
| Recommended dosage | 0.3 - 3.0 L per 100 kg of total binder. Trial mixes must be performed to establish the exact dosage rate required. |
| Compatibility | <p>Sika® ViscoCrete® ACE 507 M is suitable for mixes containing all types of cement and supplementary cementitious materials such as: Microsilica (Silica Fume), Fly Ash (PFA), GGBS (Ground Granulated Blast Furnace Slag) and the following Sika products:</p> <ul style="list-style-type: none">▪ SikaPump®▪ Sika® FerroGard®▪ SikaFume®▪ SikaFiber®▪ Sika® Aer▪ Sika® Stabilizer▪ SikaControl® <p>We recommend to perform trial mixes to establish the required performance when combining Sika® ViscoCrete® ACE 507 M with the above products or other admixtures. Please consult our Sika Technical Department for further assistance.</p> |
| Dispensing | Sika® ViscoCrete® ACE 507 M is a ready-to-use admixture to be added to the concrete as a separate component. Optimal result is obtained if Sika® ViscoCrete® ACE 507 M is poured into the concrete mix right after the addition of the first 80 % of the mixing water, i.e. when all solids are wetted. Avoid adding the admixture to the dry aggregates. |

BASIS OF PRODUCT DATA

- All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.
- Internal Reference - Version: MBS_CC-KSA/GI_ACE 507M_02-14/03-21/04-24

IMPORTANT CONSIDERATIONS

When using Sika® ViscoCrete® ACE 507 M a mix design must be selected for the local material sources used and trial mixes performed to verify suitability. If frozen and/or if precipitation has occurred, it may only be used after thawing slowly at room temperature and intensive mixing.

Sika® ViscoCrete® ACE 507 M should not be added to dry cement. Before pouring, suitability tests on the fresh concrete must be carried out. Due to the extended workability take special care that formwork is properly installed and secured. In case the setting time of concrete is extended, if cured properly, other properties may not be affected and higher ultimate strength may be achieved. **Sika® ViscoCrete® products are not compatible with admixtures based on sulfonated naphthalene or melamine.** When accidental overdosage occurs, bleeding and segregation of the concrete and retardation of initial set may be observed.

ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188

Email: info@bh.sika.com

Sika Kuwait Cons. Mat. & Paints Co WLL

Tel: +965 22 282 296

Email: sika.kuwait@kw.sika.com

Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC

Sika International Chemicals LLC

Tel: +971 4 439 8200

Email: info@ae.sika.com

Web: gcc.sika.com

Sika Saudi Arabia Limited

Sika Construction Chemicals for

Manufacturing LLC

Riyadh / Jeddah / Dammam / Rabigh

Tel: +966 12 692 7079

Email: info@sa.sika.com

Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC

(part of Sika)

Tel. +968 22 826 500

Email: info@om.sika.com

Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
- Sika UAE LLC
- Sika International Chemicals LLC
- Sika Gulf B.S.C. (c)
- Sika MB Construction Chemicals LLC
- Sika Saudi Arabia Limited
- Sika MB Construction Chemicals for Manufacturing LLC
- Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

Sika® ViscoCrete® ACE 507 M

November 2024, Version 01.01

021301011000005700