

PRODUCT DATA SHEET

SikaHyflex[®]-300 EU

WEATHER SEALANT FOR CURTAIN WALL, GLASS AND METAL FACADES



DESCRIPTION

SikaHyflex[®]-300 EU is a silicone based, 1-component, moisture curing, low-modulus elastic weather sealant. Suitable for use in hot an tropical climatic conditons.

USES

SikaHyflex[®]-300 EU is designed for weather proofing and sealing applications where the sealants appearance is of importance (translucent/metallic look). SikaHyflex[®]-300 EU is particularly suited as a sealant for shop front, glass partition walls and other applications.

CHARACTERISTICS / ADVANTAGES

- Very good weathering resistance
- Movement capability of $\pm 25\%$ (ASTM C 719)
- Very good workability
- Transparent, metallic look
- Solvent-free
- Neutral cure

SUSTAINABILITY

SikaHyflex[®]-300 EU conforms to LEED[®] EQc 4.1

- VOC content < 50 g/l (US EPA Method 24)
- SCAQMD, Rule 1168
- BAAQMD, Regulation 8, Rule 51

APPROVALS / CERTIFICATES

- ASTM C 920, class 25
- EN 15651-1 F EXT-INT CC 25 LM
- EN 15651-2 G CC 25 LM
- ISO 11600 F 25 LM and G 25 LM

PRODUCT INFORMATION

Composition	Neutral cure silicone
Packaging	300 mL cartridge, 25 cartridges per box 600 mL foil pack, 20 foil packs per box
Colour	Translucent, aluminum and champagne
Shelf life	SikaHyflex [®] -300 EU has a shelf life of 12 months for cartridges and 15 months for foil packs from the date of production, if it is stored in undamaged, original, sealed packaging, and if the storage conditions are met.
Storage conditions	SikaHyflex [®] -300 EU shall be stored in dry conditions, where it is protected from direct sunlight and at temperatures between +5 °C and +25 °C.
Density	~1.05 kg/l (ISO 1183-1)

TECHNICAL INFORMATION

Shore A Hardness	~20 (after 28 d)	(ISO 868)
Secant Tensile Modulus	~0.30 N/mm ² at 100% elongation (23 °C) ~0.30 N/mm ² at 100% elongation (-20 °C)	(ISO 8339)
Elongation at Break	~600 %	(ISO 37)
Elastic Recovery	~90 %	(ISO 7389)
Tear Propagation Resistance	~3.5 N/mm	(ISO 34)
Movement Capability	±25 %	(ASTM C 719)
Service Temperature	-40 °C min. / +150 °C max.	

Joint Design

The joint width must be designed to suit the joint movement required and the movement capability of the sealant. The joint width shall be ≥ 6 mm and ≤ 30 mm. The joint depth shall be ≥ 6 mm and ≤ 15 mm. A width to depth ratio of 2 : 1 must be maintained (for exceptions, see table below).

Typical joint dimensions

Joint Width [mm]	Joint Depth [mm]
6	6
10	6
15	8
20	10
30	15

All joints must be correctly designed and dimensioned in accordance with the relevant standards, before their construction. The basis for calculation of the necessary joint widths are the type of structure and its dimensions, the technical values of the adjacent building materials and the joint sealing material, as well as the specific exposure of the building and the joints. For larger joints please contact our Technical Department.

SYSTEMS

Compatibility

SikaHyflex®-300 EU is compatible with most SikaHyflex® and Sikasil® silicone weather sealants, Sikasil® SG adhesives and Sikasil® IG sealants. All other sealants and adhesives have to be approved by Sika before using them in direct contact with SikaHyflex®-300 EU.

Where two or more different reactive sealants and/or adhesives are used, allow the first one to cure completely before applying the next one. For specific information regarding compatibility contact our Technical Department.

APPLICATION INFORMATION

Consumption	Joint length [m] per 600 mL foil pack	Joint width [mm]	Joint depth [mm]
	16.7	6	6
	10	10	6
	5	15	8
	3	20	10
	2	25	12
	1.3	30	15

Backing Material	Use closed cell, polyethylene foam backing rods.		
Sag Flow	~2 mm (20 mm profile, 50 °C)		(ISO 7390)
Ambient Air Temperature	+5 °C min. / +40 °C max. (min. 3 °C above dew point temperature)		
Substrate Temperature	+5 °C min. / +40 °C max.		
Curing Rate	~2 mm/24 h (23 °C / 50 % r.h.)		(CQP 049-2)
Skimming time	~40 min (23 °C / 50 % r.h.)		(CQP 019-1)
Tack free time	~180 min (23 °C / 50 % r.h.)		(CQP 019-1)

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The substrate must be clean, dry, sound and homogeneous, free from oils, grease, dust and loose or friable particles. The following priming and/or pre-treatment procedures shall be followed:

Non-porous substrates

Float glass, coated glass, anodised aluminium and stainless steel have to be pre-treated using Sika® Aktivator-205, Sika® Aktivator-100 or Sika® Cleaner P. Powder coated and PVDF coated metals have to be pre-treated using Sika® Aktivator-205. For details like application and flash-off times refer to the most recent Product Data Sheet of the respective pre-treatment product.

Porous substrates

Concrete, aerated concrete and cement based renders, mortars and bricks shall be primed using Sika® Primer-3 N or Sika® Primer-210. For details like application and flash-off times refer to the most recent Product Data Sheet of the respective pre-treatment product.

Adhesion tests on project specific substrates must be performed prior to application. For more detailed advice and instructions please contact our Technical Department. Note: Primers are adhesion promoters. They are neither a substitute for the correct cleaning of a surface, nor do they improve the strength of the surface significantly.

APPLICATION METHOD / TOOLS

SikaHyflex®-300 EU is supplied ready to use. After the necessary substrate preparation, insert a suitable backing rod to the required depth and apply pre-treatment if necessary. Insert a foil pack or cartridge into the sealant gun and extrude SikaHyflex®-300 EU into the joint making sure that it comes into full contact with the sides of the joint and avoids any air entrapment. SikaHyflex®-300 EU sealant must be firmly tooled against the joint sides to ensure adequate adhesion.

It is recommended to use masking tape where exact joint lines or neat lines are required. Remove the tape within the skin time.

Do not use tooling products containing solvents.

CLEANING OF EQUIPMENT

Clean all tools and application equipment immediately after use with Sika® Remover-208 and/or Sika® Top-Clean T. Once cured, residual material can only be removed mechanically.

FURTHER INFORMATION

- Safety Data Sheet (SDS)
- Pre-treatment Chart Sealing & Bonding
- General Guidelines SikaHyflex and Sikasil Weather Sealants

IMPORTANT CONSIDERATIONS

- SikaHyflex®-300 EU cannot be overpainted.
- Do not use SikaHyflex®-300 EU on natural stone.
- Do not use SikaHyflex®-300 EU on bituminous substrates, natural rubber or on any building materials which might bleed oils, plasticizers or solvents that could attack the sealant. EPDM rubber needs to be tested for compatibility and approved by Sika Technical Department.
- Do not use SikaHyflex®-300 EU on pre-stressed polyacrylate and polycarbonate as it may cause environmental stress cracking (crazing).
- Do not use SikaHyflex®-300 EU to seal joints in and around swimming pools.
- Do not use SikaHyflex®-300 EU for joints under water pressure or for permanent water immersion.
- Do not expose uncured SikaHyflex®-300 EU to alcohol containing products as this may interfere with the curing reaction.

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for the exact product data and uses.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

SIKA NORTHERN GULF

Bahrain / Qatar / Kuwait
Tel: +973 177 38188
sika.gulf@bh.sika.com
gcc.sika.com

SIKA SOUTHERN GULF

UAE / Oman / SIC
Tel: +971 4 439 8200
info@ae.sika.com
gcc.sika.com

SIKA SAUDI ARABIA

Riyadh / Jeddah / Damman
Tel: +966 11 217 6532
info@sa.sika.com
gcc.sika.com



ISO 9001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd,
Sika Qatar LLC
ISO 14001: Sika UAE LLC,
Sika Gulf B.S.C. (c),
Sika Saudi Arabia Co. Ltd
OHSAS: Sika UAE LLC,
Sika Gulf B.S.C. (c)

All products are supplied
under a management
system certified to conform
to the requirements of the
quality, environmental and
occupational health &
safety standards ISO 9001,
ISO 14001 and OHSAS
18001.

Product Data Sheet

SikaHyflex®-300 EU

January 2017, Version 01.02

020511030000000045

SikaHyflex-300EU-en-AE-(01-2017)-1-2.pdf

