

## PRODUCT DATA SHEET

# Sikacryl®-625 Fire+

Fire resistant ablative coating for linear seals and penetrations



### DESCRIPTION

Sikacryl®-625 Fire+ is a 1-part fire resistant, ablative acrylic coating used to enhance the fire resistance of mineral fiber boards. Suitable for use in hot and tropical climatic conditions.

### USES

- Covers linear seals up to 120 mm in combination with mineral fibre backing
- Edge coating of SikaSeal®-626 Fire Board+ when installed on the outer face of a wall or floor

### CHARACTERISTICS / ADVANTAGES

- Up to 4 hours fire resistance
- 1-part ready to use, easy to apply
- Easy to clean

### PRODUCT INFORMATION

<b>Composition</b>	Water based acrylic
<b>Packaging</b>	3 L container. Refer to current price list for packaging variations.
<b>Shelf life</b>	12 months from the date of production.
<b>Storage conditions</b>	The product must be stored in original, unopened, and undamaged packaging in dry conditions at temperatures between +5 °C and +25 °C. Always refer to packaging.
<b>Colour</b>	White
<b>Density</b>	~1.3 kg/l (ISO 1183-1)

### SUSTAINABILITY

- Conformity with LEED v4 EQc 2: Low-Emitting Materials
- VOC emission classification M1

### APPROVALS / CERTIFICATES

- CE Marking and Declaration of Performance to European Technical Assessment ETA 21/1034, based on EAD 350141-00-1106:2017 - Fire stopping and fire sealing products, linear joint and gap seals
- Fire Resistance EN 13501-2, UL-EU, Certificate No.UL-EU-01214-CPR

## TECHNICAL INFORMATION

<b>Service temperature</b>	-20 °C min. / +70 °C max.
<b>Resistance to fire</b>	Refer to SikaSeal®-626 Fire Board 'Approvals / Certificates' or contact Sika Technical Services for specific information.

## APPLICATION INFORMATION

<b>Ambient air temperature</b>	+5 °C min. / +40 °C max.
<b>Substrate temperature</b>	+5 °C min. / +40 °C max., min. +3 °C above dew point temperature

## BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

## FURTHER INFORMATION

- Sika Application Manual: Sikacryl®-625 Fire+ for linear seals
- Sika Application Manual: SikaSeal®-626 Fire Board+ for penetration seals
- Brochure Sika Fire Protection Solutions

## IMPORTANT CONSIDERATIONS

- Colour variations may occur due to exposure to chemicals, high temperatures and/or UV-radiation (especially with the colour shade white). However, a change in colour is purely of aesthetic nature and does not adversely influence the technical performance or durability of the product.
- Do not use Sikacryl®-625 Fire+ as glass sealer, for floor joints, sanitary joints or on natural stone.
- Do not use Sikacryl®-625 Fire+ on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might leach oils, plasticizers or solvents that could attack the sealant.
- Do not use Sikacryl®-625 Fire+ for joints under water pressure or for permanent water immersion.
- Sikacryl®-625 Fire+ may only be used for applications and in combination with products it was tested for.

## ECOLOGY, HEALTH AND SAFETY

User must read the most recent corresponding Safety Data Sheets (SDS) before using any products. The SDS provides information and advice on the safe handling, storage and disposal of chemical products and contains physical, ecological, toxicological and other safety-related data.

## APPLICATION INSTRUCTIONS

### SUBSTRATE PREPARATION

The substrate must be clean, dry, sound, free from oils, grease, dust and loose or friable particles. Sikacryl®-625 Fire+ adheres without primers and/or activators.

### APPLICATION METHOD / TOOLS

Reference must be made to the relevant Sika Application Manual or contact Sika Technical Services for additional information.

### CLEANING OF EQUIPMENT

Clean all tools and application equipment with water immediately after use. Hardened material can only be removed mechanically.

## LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

## LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

### SIKA NORTHERN GULF

Bahrain / Kuwait  
Tel: +973 177 38188  
info@bh.sika.com  
gcc.sika.com

### SIKA SOUTHERN GULF

UAE / Oman / SIC  
Tel: +971 4 439 8200  
info@ae.sika.com  
gcc.sika.com

### Sika Saudi Arabia

Riyadh / Jeddah / Dammam  
Tel. +966 11 217 6532  
info@sa.sika.com  
gcc.sika.com



ISO 9001: Sika UAE LLC,  
Sika Gulf B.S.C. (C),  
Sika Saudi Arabia Limited,  
Sika International Chemicals LLC  
ISO 14001: Sika UAE LLC,  
Sika Gulf B.S.C. (C),  
Sika Saudi Arabia Limited,  
Sika International Chemicals LLC,  
ISO 45001: Sika UAE LLC,  
Sika Gulf B.S.C. (C),  
Sika International Chemicals LLC.

All products are supplied under  
a management system certified  
to conform to the requirements  
of the quality, environmental  
and occupational health &  
safety standards: ISO 9001,  
ISO 14001 and ISO 45001.

Sikacryl-625Fire+-en-AE-(03-2022)-1-1.pdf

### Product Data Sheet

Sikacryl®-625 Fire+

March 2022, Version 01.01  
020517010040000010

