

PRODUCT DATA SHEET

Sikasil®-112 BH

General purpose acetoxy cure silicone sealant

DESCRIPTION

Sikasil®-112 BH is a 1-component, general purpose silicone sealant.
Suitable for use in hot and tropical climatic conditions.

USES

Sikasil®-112 BH is a general-purpose silicone sealant which bonds strongly to clean uncoated glass, ceramics and glazed or painted surfaces. Sikasil®-112 BH offers good performance on many different applications where weather tightness is required:

- Display cases, panels and signs
- Plumbing, drains, guttering
- HVAC ducting
- DIY general purpose sealing

FEATURES

- Low shrinkage
- Good UV and weathering resistant
- Good adhesion to a variety of non-porous substrates
- Suitable for vertical jointing and underside applications

PRODUCT INFORMATION

Composition	Acetoxy silicone
Packaging	280 ml cartridges, 12 cartridges per box
Shelf life	Sikasil®-112 BH has a shelf life of 12 months from the date of production, if it is stored properly in undamaged, original, sealed packaging, and if the storage conditions are met.
Storage conditions	Sikasil®-112 BH shall be stored in dry conditions, protected from direct sunlight and at temperatures between +5°C and +25°C.
Colour	Transparent, Black, and White
Density	~0.97 kg/L (ISO 1183-1)
Shore A hardness	~20 (28d / 23°C / 50 % r.h.) (ASTM D-2240)
Elongation at break	~ 420% (ASTM D-412)
Service temperature	-30°C to+ 120°C

APPLICATION INFORMATION

Sag flow	Non-sag
Ambient air temperature	+5°C to +40°C
Substrate temperature	+5°C to +40°C
Curing rate	~3 mm/24 h (23°C / 50 % r.h.)
Skimming time	~ 8 min. (23 °C / 50 % r.h.)
Tack free time	~ 15 min. (23 °C / 50 % r.h.)

BASIS OF PRODUCT DATA

All technical data stated in this Data Sheet are based on laboratory tests. Actual measured data may vary due to circumstances beyond our control.

IMPORTANT CONSIDERATIONS

- Do not use Sikasil®-112 BH on bituminous substrates, natural rubber, EPDM rubber or on any building materials which might bleed oils, plasticizers or solvents that could attack the sealant.
- Do not use in totally confined spaces, Sikasil®-112 BH requires atmospheric moisture to cure.
- Sikasil®-112 BH is not recommended for porous substrates, such as concrete, stone, marble and granite. Bleeding can occur when Sikasil®-112 BH is used on these substrates.
- Sikasil®-112 BH is not recommended for use on submerged joints, joints where physical abuse or abrasion are likely to occur, structural glazing or insulated glazing, and food contact applications.
- Do not use Sikasil®-112 BH for medical or pharmaceutical uses.
- Do not use Sikasil®-112 BH on alkaline surfaces such as concrete, plaster and brick.

ECOLOGY, HEALTH AND SAFETY

For information and advice on the safe handling, storage and disposal of chemical products, users shall refer to the most recent Safety Data Sheet (SDS) containing physical, ecological, toxicological and other safety-related data.

APPLICATION INSTRUCTIONS

SUBSTRATE PREPARATION

The substrate must be clean, dry, sound, and homogeneous, free from oils, grease, dust and loose or friable particles. Paint, cement laitance and other poorly adhering contaminants must be removed. Sikasil®-112 BH adheres without primers and/or activators.

However, for optimum adhesion and critical, high-performance applications, such as on multi-story buildings, highly stressed joints, extreme weather exposure or water immersion, the following priming and/or pre-treatment procedures shall be followed: Aluminum, anodized aluminum, stainless steel, galvanised steel, powder coated metals or glazed tiles must be cleaned and pre-treated using Sika® Aktivator-205, wiped on with a clean towel. Before sealing, allow a flash-off time of >15 minutes (<2 hours). Other metals, such as copper, brass, and titanium-zinc, also must be cleaned and pre-treated using Sika® Aktivator-205, wiped on with a clean towel. After the necessary flash-off time, use a brush to apply Sika® Primer-3 N and allow a further flash-off time of >30 minutes (<4 hours) before sealing the joints. PVC must be cleaned and pre-treated using Sika® Primer-215 applied with a brush. Before sealing, allow a flash-off time of >30 minutes (<4 hours). Glass shall be cleaned with isopropyl alcohol before application.

Note: Primers are adhesion promoters. They are neither a substitute for the correct cleaning of a surface, nor do they improve the strength of the surface significantly. For more detailed advice and instructions please contact our Technical Department.

APPLICATION METHOD / TOOLS

Sikasil®-112 BH is supplied ready to use. After the necessary substrate preparation, insert a suitable backing rod to the required depth and apply any primer if necessary. Insert a cartridge into the sealant gun and extrude Sikasil®-112 BH into the joint making sure that it comes into full contact with the sides of the joint and avoids any air entrapment. Sikasil®-112 BH sealant must be firmly tooled against the joint sides to ensure adequate adhesion. It is recommended to use masking tape where exact joint lines or neat lines are required. Remove the tape within the skin time.
Do not use tooling products containing solvents.

CLEANING OF EQUIPMENT

Clean all tools and application equipment immediately after use with Sika® Remover-208. Once cured, residual material can only be removed mechanically.

LOCAL RESTRICTIONS

Note that as a result of specific local regulations the declared data and recommended uses for this product may vary from country to country. Consult the local Product Data Sheet for exact product data and uses.

LEGAL NOTES

The information, and, in particular, the recommendations relating to the application and end-use of Sika products, are given in good faith based on Sika's current knowledge and experience of the products when properly stored, handled and applied under normal conditions in accordance with Sika's recommendations. In practice, the differences in materials, substrates and actual site conditions are such that no warranty in respect of merchantability or of fitness for a particular purpose, nor any liability arising out of any legal relationship whatsoever, can be inferred either from this information, or from any written recommendations, or from any other advice offered. The user of the product must test the product's suitability for the intended application and purpose. Sika reserves the right to change the properties of its products. The proprietary rights of third parties must be observed. All orders are accepted subject to our current terms of sale and delivery. Users must always refer to the most recent issue of the local Product Data Sheet for the product concerned, copies of which will be supplied on request.

Sika Gulf B.S.C. (c)

Tel: +973 177 38188
Email: info@bh.sika.com
Sika Kuwait Cons. Mat. & Paints Co WLL
Tel: +965 22 282 296
Email: sika.kuwait@kw.sika.com
Web: gcc.sika.com

Sika UAE LLC

Sika MB Construction Chemicals LLC
Sika International Chemicals LLC
Tel: +971 4 439 8200
Email: info@ae.sika.com
Web: gcc.sika.com

Sika Saudi Arabia Limited

Riyadh / Jeddah / Dammam / Rabigh
Tel: +966 11 217 6532
Email: info@sa.sika.com
Web: gcc.sika.com

Sika LLC - Oman

Master Builders Solutions LLC
(part of Sika)
Tel: +968 22 826 500
Email: info@om.sika.com
Web: gcc.sika.com



ISO 9001, 14001, 45001 – SGS
-Sika UAE LLC
-Sika International Chemicals LLC
-Sika Gulf B.S.C. (c)
ISO 9001, 14001 – SGS
-Sika Saudi Arabia Limited
ISO 9001, 14001 – TÜV
-Sika MB Construction Chemicals LLC
-Master Builders Solutions LLC

All products are supplied under a management system certified to conform to the requirements of the quality, environmental and occupational health & safety standards ISO 9001, ISO 14001 and ISO 45001.



Product Data Sheet

Sikasil®-112 BH

March 2024, Version 02.02
02051403000000022

